

INDEX

ADMIRALTY BRASS 10
ALUMINUM 2, 3
ALUMINUM BRONZE 12
ANTIMONY 4
ARSENIC 4

BATTERY ALLOY 13
BISMUTH 4
BRASS 9, 10
BRONZE 11, 12

CADMIUM 4
CHROMIUM 4
COPPER 5, 6, 7, 8, 9, 10, 11, 12
COPPER ANODE 5
COPPER CONCENTRATE 6
COPPER IN VARIOUS FORMS 5
COPPER-NICKEL-SILVER 8
CUPRO-NICKEL 8

ENVIROBRASS 6

FEDERALLOY 6

GUN METAL 8

IN 100 18

LEAD 13
LEAD-SILVER 13
LEADED BRASS 10
LEADED BRONZE 12

MAGNESIUM 14
MANGANESE 14
MANGANESE BRASS 10

NAVAL BRASS 10
NICKEL 14, 15, 16, 17, 18

PHOSPHOR BRONZE 12
PHOSPHORUS DEOXIDIZED COPPER 5

SEBILOY 6
SILICON BRASS 10
SOLDER 19
SPELTER 22
SUPERALLOYS 18

TIN 19
TITANIUM 20, 21
TITANIUM POWDER 20
TUNGSTEN 22

ZINC 22, 23, 24
ZINC SPELTER 22
ZIRCALOY-4 24
ZIRCONIUM 24

CRM ALUMINUM BASE CHIPS

analysis listed in mass % except * which is mg/kg

Number	Si	Cr	Cu	Fe	Mg	Mn	Ni	Pb	Sn	Sr	Ti	V	Zn	Zr	Al	B*	Be	Cd	Ga	Units
BAM 201	13.20	.	0.009	0.18	0.0024	0.38	0.20	0.09	0.17	.	0.011	.	0.038	100 g
BCS 505	12.8	.	0.05	0.30	0.05	0.52	0.046	0.056	0.027	.	0.03	.	0.24	100 g
BCS 182/3	11.03	.	0.037	0.51	0.067	0.26	0.37	0.11	0.10	0.018	0.065	(0.014)	0.128	(0.003)	.	Ca:(0.002)	.	.	100 g	
SRM 856a	9.21	0.060	3.50	0.85	0.063	0.35	0.046	0.056	0.027	.	0.065	.	0.96	30 g	
SRM 855a	7.07	0.013	0.13	0.14	0.37	0.060	0.016	0.019	0.010	0.018	0.15	(0.012)	0.085	(0.003)	.	Ca:(0.001)	.	.	30 g	
NGS HC28974-A1	7.03	.	3.73	0.51	0.071	0.062	0.048	0.093	0.057	.	0.005	<0.01	0.385	0.020	50 g	
SRM 87a	6.24	0.11	0.30	0.61	0.37	0.26	0.57	0.093	0.057	.	0.18	.	0.16	0.020	75 g	
NM 511	6.150	.	0.295	0.790	0.195	0.195	0.195	0.093	0.057	100 g	
NM 251.1	6.1	.	0.28	0.75	0.63	0.22	0.017	0.055	0.016	.	(0.008)	.	0.079	100 g	
BCS 268/1	5.49	.	1.35	0.47	0.49	0.24	0.16	0.028	0.031	.	.	.	0.028	100 g	
BCS 380/1	1.93	.	0.91	1.24	0.24	0.094	0.94	0.028	0.031	.	0.024	.	0.025	100 g	
SRM 2426	1.925	.	0.91	1.24	0.24	0.094	0.94	0.028	0.031	.	0.024	.	38.92	.	58.18	.	.	.	40 g	
BCS 349	1.19	<0.001	3.40	0.154	0.024	0.111	0.0006	0.077	0.074	.	0.034	.	0.299	.	.	<0.0001	.	.	100 g	
SRM 858	0.79	0.0011	0.84	0.078	1.01	0.48	0.048	0.052	0.052	.	0.042	.	1.04	0.086	35 g	
BCS 216/3	0.74	0.110	5.45	0.77	0.76	0.76	0.24	0.052	0.052	.	0.20	.	0.214	100 g	
BCS 343	0.52	0.14	0.28	0.39	0.70	0.69	0.69	0.052	0.052	.	0.024	.	0.028	100 g	
BCS 181/3	0.30	0.04	2.48	0.72	1.57	1.10	2.00	0.101	0.074	.	0.058	.	2.52	100 g	
IARM 111B	0.192	0.205	1.38	0.225	2.20	0.093	0.0098	0.0663	(0.002)	(0.0004)	0.0427	0.0035	5.70	0.0132	.	(0.8)	0.00087(0.0003)	0.008	100 g	
SRM 853a	0.1810	<0.0005	0.1504	0.504	1.092	1.251	0.00429	<0.0033	(0.0003)	<0.0001	0.0205	0.01842	0.0514	(0.0023)	.	.	.	0.0176	40 g	
GBW 02202	0.18	.	0.095	0.38	0.021	1.38	0.013	0.032	0.032	.	0.036	.	0.10	100 g	
BCS 262/1	0.16	(0.002)	0.039	0.20	10.75	0.084	0.071	(0.05)	(0.04)	.	0.005	.	0.085	.	.	<0.01	(0.0006)	0.0185	100 g	
SRM 854a	0.1553	0.0340	0.0494	0.1990	4.474	0.3753	0.0195	0.0195	.	(0.0002)	0.0335	0.0174	0.0505	0.0185	40 g	
BCS 300/1	0.14	0.13	1.27	0.24	2.74	0.33	0.33	0.014	.	.	0.09	.	5.87	0.18	100 g	
BAM 300	0.14	0.216	0.040	0.198	2.68	0.018	.	0.014	.	.	0.012	.	0.128	100 g	
BCS 263/2	0.14	0.074	0.019	0.26	4.67	0.36	0.022	.	0.056	.	.	<0.01	.	.	100 g	
BAM 301	0.062	.	0.0018	0.054	0.0008	(0.001)	0.046	0.0018	0.036	100 g	
IARM 109C	0.616	0.102	0.302	0.529	0.83	0.108	0.0123	0.0072	(0.004)	.	0.0176	0.009	0.121	0.0018	.	(12)	(0.001)	0.013	100 g	
BCS 1959	0.035	.	0.001	0.080	0.001	0.001	0.004	0.015	.	99.85	.	.	0.009	100 g	
IARM 104B	0.150	0.0088	4.63	0.262	1.56	0.645	0.0053	0.014	(0.003)	(0.0003)	0.056	0.006	0.065	(0.0010)	.	0.00021	.	0.011	100 g	
BAM M319	0.104	(0.060)	0.0015	0.29	4.96	0.371	(0.037)	<0.001	<0.001	.	0.030	(0.0093)	0.073	0.32	.	Sc: 0.84%	(0.015)	0.012	100 g	
IARM 343A	0.050	0.0009	2.29	0.084	2.04	(0.002)	(0.005)	0.0012	.	(0.0003)	0.0175	0.0058	8.15	0.152	.	.	(0.0002)	0.012	100 g	
JSAC 0121-C	0.00110	0.000113	0.000348	0.00094	0.000282	0.000173	0.000196	.	0.000203	0.000202	.	1.98	.	.	50 g	
BW Al (RM)	<0.0001	<0.0001	<0.0001	<0.0005	<0.00005	.	<0.0001	<0.0001	<0.0001	.	.	<0.0001	<0.0005	.	99.999	Trace As,Ca Cd, Na	.	last	100 g	

RM ARSENIC

Number	As	Units
BM As	99.999	50 g chips last of stock

RM ANTIMONY

Number	Sb	As	Fe	Pb	Si	Sn	Units
BM Sb	99.999	<0.0002	<0.0002	<0.0001	<0.0001	<0.0001	100 g chips

RM BISMUTH

Number	Bi	Ag	As	Co	Cu	Fe	Pb	Sb	Zn	Units
BM Bi	99.97	<0.0001	<0.0001	<0.003	<0.0001	<0.001	<0.02	<0.0002	<0.003	100 g chips

RM CADMIUM

Number	Cd	Cu	Fe	Pb	Ti	Zn	Units
BM Cd	99.96	<0.01	<0.002	<0.02	<0.003	<0.004	100 g chips

CRM CHROMIUM

analysis listed in mass %

BCS: 100 g powder VS: 100 g chips

Number	Cr	Al	C	Ca	Cu	Fe	N	Ni	O	S	Si	V
VS F36/1	99.9	0.0009	0.0030	(0.0003)	0.00023	0.005	0.0026	0.00019	.	0.0023	0.0034	0.0037
BCS 361	.	(0.083T)	0.0039	.	.	0.0920	0.0079	.	0.1010	0.0043	0.0449	.

CRM COBALT BASE CHIPS

100 g

Number	Cr	Co	C	Fe	Mn	Mo	N	Nb	Ni	Si	W
IARM Co6B-18	30.7	57.0	1.02	2.68	1.48	0.020	0.017	(0.014)	2.59	0.61	3.92
ECRM 378-1C	28.22	.	1.181	0.606	0.0579	0.0503	.	.	0.617	1.172	4.43
BAM 328-1	20.54	41.65	0.390	2.40	1.395	4.41	0.027	3.61	20.54	0.629	4.16
IARM CoElgiloy-18	20.4	40.4	0.008	12.6	2.36	8.6	0.0034	(0.006)	15.9	0.05	(0.008)
SRM 862	20.0	51.5	0.120	1.80	1.59	.	0.026	.	9.74	0.017	15.1

Number	Al	B	Cu	O	P	S	Ta	Ti	V
IARM Co6B-18	(0.07)	.	(0.015)	.	.	(<0.0010)	.	(0.007)	0.011
ECRM 378-1C	(0.0023)	0.0055	.	.	.
BAM 328-1	0.070	.	0.013	.	0.005	.	0.18	.	.
IARM CoElgiloy-18	(0.011)	(0.002)	(0.005)	0.009	0.0019	(0.0018)	(0.01)	(0.004)	(0.009)
SRM 862	.	.	0.0010	.	0.002	0.0008	.	.	0.005

CRM COPPER IN VARIOUS FORMS

analysis listed in mg/g each of the blow available in 3 forms A: disc 39 mm Ø x 30 mm B: Rod 8 mm Ø x 100 mm C: Chips 50 g

Number	Ag	Al	As	Au	Be	Bi	Cd	Co	Cr	Fe	Ind	Mg	Mn	Ni	P	Pb	S	Sb	Se	Si	Sn	Te	Ti	Zn	Zr
ERM-EB075	10.8	2.3	3.18	1.46	1.08	1.79	2.69	2.64	1.4	9.3	1.83	7.0	1.35	2.18	2.59	4.8	25	2.93	1.69	2.6	2.13	1.78	3.2	6.51	.
ERM-EB074	1.03	.	1.23	0.52	0.31	0.51	0.4	0.83	0.37	5.8	0.49	2.03	0.93	0.61	1.53	2.7	(3.3)	0.57	0.55	.	(1.5)	0.5	0.97	2.2	(8.8)

CRM COPPER CHIPS AND PINS

analysis listed in mg/kg except % which is mass % IMN 001: 50 g of 0.31 g pins all others: chips as noted

Number Units	Ag	As	Au	Bi	Cd	Co	Cr	Cu%	Fe	Mn	Ni	P	Pb	S	Sb	Se	Si	Sn	Te	Zn		
SRM 454	286	46	7.5	19	.	.	99.84	.	66	.	.	.	66	.	24	479	.	2.2	27	7	35 g	
SRM 400	181	140	.	24.5	.	0.6	.	99.70	41	.	603	.	128	.	102	214	last	.	153	114	50 g	
SRM 399	117	47	.	10.5	.	0.5	.	99.79	20.0	.	506	.	114	.	30	95	.	.	50	45	50 g	
IMN 001	27.59	3.17	.	1.42	(0.11)	2.04	3.55	.	4.28	(6.0)	2.33	1.38	.	.	2.33	1.38	.	3.31	1.23	4.57	above	
IMN 5	10	4.0	.	0.096	.	8.1	.	4.5	(1.3)	4.4	.	27	.	.	(0.92)	.	(2.6)	4.6	.	(13)	200 g	
BCR 017B	6.9	10.4	50 g

CRM COPPER CHIPS

analysis listed in mass % C39X: typical analysis 50 g BAM, BCS, IARM: 100 g IPT: 50 g IMN: 200 g

Number	Cu	Ag	Al	As	Au	B	Be	Bi	C	Cd	Co	Cr	Fe	Mg
IPT 64	99.98	0.0010	(<0.0006)	(0.0002)	.	.	.	(<0.0001)	0.00045	.
IARM 70C	99.94	(0.0011)	(0.0014)	.	.	(0.0004)	<0.002	(0.002)	(0.002)	(0.0008)	(0.0014)	(0.0002)	(0.0016)	(0.0003)
BAM M365	99.73	0.0159	.	0.00404	.	.	.	0.00300	.	.	0.000213	.	0.00061	.
IARM 278A	99.5	(0.001)	<0.002	(0.001)	.	.	.	(0.001)	(0.003)	.	(0.001)	(0.001)	0.004	.
BCS 399	REM	.	<0.001	(0.001)	.	.	.	(0.001)	.	(0.003)	.	.	(0.006)	.
C39X 178700	.	0.0468	0.0012	0.0033	0.0009	.	.	0.0470	.	0.0305	0.0017	.	.	.
C39X 178710	.	0.025	<0.0005	0.029	0.0048	.	.	0.069	.	0.0031	0.0008	.	.	.
C39X 178680	.	0.0249	0.0072	0.0226	0.0101	.	.	0.0308	.	0.0130	0.0248	.	0.110	0.0085
C39X 178660	.	<0.001	<0.002	0.037	.	.	.	0.001	.	<0.001	0.003	0.002	<0.001	<0.001

Number	Mn	Ni	O	P	Pb	S	Sb	Se	Si	Sn	Te	Zn
IPT 64	.	0.00018	.	.	0.00006	.	(0.0002)	(<0.0002)	.	(<0.0005)	(<0.0001)	(0.001)
IARM 70C	(0.0002)	(0.0004)	(0.002)	(0.0014)	(0.0013)	0.0008	(0.003)	(0.001)	(0.0006)	0.0005	(0.001)	(0.002)
BAM M365a	.	0.0235	(0.1712)	.	0.0141	.	0.00121	0.0179	.	(0.0029)	0.000127	0.0030
IARM 278A	(0.0004)	<0.005	(0.0004)	0.011	(0.003)	0.002	<0.005	.	(0.002)	(0.001)	0.53	(0.002)
BCS 399	.	(0.002)	.	0.045	(0.002)	.	(0.001)	.	.	(0.003)	.	(0.003)
C39X 178700	Ge: 0.0076	0.0062	In: 0.0078	0.0012	0.0447	0.0026	0.0478	0.0261	.	0.0031	0.0011	0.129
C39X 178710	0.0010	0.027	.	<0.0005	0.0092	0.0080	0.017	0.028	<0.0005	.	0.011	.
C39X 178680	0.0123	0.0222	.	0.0507	0.1040	0.022	0.0295	0.0133	.	0.103	0.0206	0.197
C39X 178660	<0.001	0.034	.	<0.002	<0.001	0.003	<0.001	.	<0.005	0.013	<0.001	0.005

RM PHOSPHORUS DEOXIDIZED COPPER CHIPS

analysis listed in mass % except * which is mg/kg 100 g chips

Number	Ag%	Al*	As%	Bi*	Co*	Cu%	Fe*	Mn*	Ni*	P%	Pb%	Sb*	Si%	Sn%	Te%	Zn%
CURM 09.03	0.012	<3	<0.001	<3	<3	99.92	33	<3	<3	0.056	<0.0005	<5	<0.001	<0.001	<0.001	<0.001
CURM 09.01	0.011	<5	<0.001	<3	<3	99.82	19	<3	<3	0.151	<0.0005	<5	<0.001	<0.001	<0.001	0.0008
CURM 09.02	0.0055	<5	<0.001	<5	<5	99.90	42	<5	<5	0.078	<0.001	<5	<0.002	<0.001	<0.001	<0.001

CRM COPPER ANODE

analysis listed in mg/kg 425 g chips

Number	Ag	Au	As	Fe	Pb	Sn	Te
CAN CUAR-1	294	2.3	145	76	864	113	33

CRM COPPER CONCENTRATE POWDER

analysis listed in mass %							analysis listed in mg/kg			
Number	Cu	Cd	Fe	Pb	S	SiO ₂	Zn	Ag	Re	Units
VS 2891-84	40.4	0.029	(5.78)	2.25	(15.98)	(21.74)	2.89	7.077	28.2	100 g

CRM SEBILOY / ENVIROBRASS / FEDERALLOY CHIPS

analysis listed in mass %				C32X: 50 g units, typical analysis						IARM: 100 g units			
Number	Bi	Se	Sn	Zn	Cu	As	Co	Fe	Ni	P	Pb	Sb	Si
C32X SEB10	5.77	0.895	3.83	11.57	(76.7)	0.051	0.0108	0.059	0.118	0.025	0.564	0.354	.
C32X SEB20	4.35	0.027	9.40	3.75	81.8	0.009	0.013	0.078	0.078	0.014	0.42	0.013	.
IARM 264A	3.6	(0.001)	3.03	5.33	(87.3)	(0.004)	(0.001)	0.048	0.54	0.027	0.057	0.074	0.003
IARM 263A	2.55	(0.002)	3.5	15.8	(78)	0.003	0.001	0.047	0.66	0.040	0.022	0.06	0.003
IARM 265A	2.4	(0.002)	4.4	2.45	(90)	(0.005)	(0.001)	0.013	0.69	0.024	0.011	0.015	0.003
IARM 266A	2.37	0.001	6.9	3.48	(87)	0.004	(0.001)	0.035	0.46	0.032	0.010	0.010	0.002
C32X SEB40	2.69	0.115	9.29	8.55	78.58	0.0011	0.476	0.365	0.0092	0.006	0.010	0.0055	.
IARM 227A	2.3	1.21	5.1	4.70	85.9	0.003	0.001	0.060	0.53	0.003	0.042	<0.01	0.002
IARM 226A	1.7	0.93	5.1	4.8	86.7	0.003	0.001	0.054	0.54	0.005	0.040	0.004	0.002
IARM 228A	1.53	0.67	4.1	4.1	89.0	0.003	0.001	0.052	0.45	0.032	0.026	0.010	0.002
C32X SEB50	1.17	0.512	5.28	6.64	85.5	0.0121	0.0048	0.360	0.308	0.183	0.0149	0.0344	.

Number	Ag	Al	B	C	Cd	Cr	Mn	N	O	S
C32X SEB10
C32X SEB20
IARM 264A	(0.005)	0.003	.	(0.004)	.	(0.002)	(0.002)	.	.	0.0013
IARM 263A	(0.006)	(0.002)	.	<0.005	.	(0.002)	(0.002)	.	.	(0.002)
IARM 265A	(0.002)	0.003	.	.	.	(0.001)	(0.002)	.	.	(0.002)
IARM 266A	(0.001)	0.002	.	(0.002)	.	(0.002)	(0.002)	.	.	(0.002)
C32X SEB40	.	.	0.0021	.	0.0004
IARM 227A	0.004	0.002	.	0.003	.	(0.001)	0.001	(0.0002)	0.0013	0.005
IARM 226A	0.004	0.002	.	0.003	.	(0.001)	0.002	<0.0005	(0.001)	0.005
IARM 228A	0.003	0.002	.	0.003	.	0.001	0.001	<0.0005	(0.002)	0.004
C32X SEB50	.	.	0.0028	.	0.0067

COPPER BASE CHIPS

= class, where 1 = CRM and 2 = RM C3x, DH: typical analysis 50 g GBW: 95 g SRM: 50 g others: 100 g

#	Number	Sn	Al	Fe	Mn	Ni	Pb	Zn	Be	Bi	Co	Se
2	DH 0209	11.92	.	.	.	0.265	0.542
1	BAM 228	9.76	(0.0001)	0.036	(<0.001)	0.109	1.24	3.32	.	0.0086	.	0.0012
2	DH 0201	8.84	0.022	0.677	0.035	0.795	1.17	6.30	.	0.006	.	.
2	DH 0208	4.78	4.15	2.54	0.711	2.82	1.31	1.85
2	DH 0206	2.78	0.059	1.79	0.044	0.221	0.891	10.89
2	DH 0203	2.17	12.50	5.76	0.057	.	0.59	1.36
2	DH 0204	2.16	12.51	5.70	0.057	.	0.58	1.36
2	DH 0205	2.14	12.53	5.66	0.056	.	0.76	1.36
2	DH 0207	0.74	.	0.936	0.027	0.174	2.16	30.20
2	DH 0202	0.381	.	0.911	0.007	0.034	0.139	0.229
1	C37X2180	0.018	0.0025	0.075	0.084	2.51	0.0025	0.029
2	C36XCBC40	0.01	0.06	0.09	0.003	0.04	0.30	0.02	1.82	.	2.44	.
1	IARM 158B	0.01	0.002	0.090	0.019	0.32	0.01	0.014	.	.	0.002	.
1	IARM 158C	0.01	0.002	0.090	0.019	0.32	0.01	0.014	.	.	0.002	.
1	IARM Cu172-18	0.0009	0.022	0.029	0.0017	0.010	(0.005)	0.008	1.79	.	0.344	.
1	SRM 460	0.006	0.048	0.098	.	0.031	0.258	0.004	1.86	.	0.217	.
1	SRM 459	0.005	0.044	0.079	.	0.039	0.001	0.002	1.82	.	0.221	.
1	SRM 458	0.004	0.030	0.060	.	1.60	0.002	0.002	0.360	.	0.076	.
2	C36XCBC20	0.004	0.03	0.02	(<0.01)	0.07	0.004	0.03	0.56	.	0.13	.
1	C37X2260	0.0032	0.0020	1.52	0.582	0.0024	(0.001)	2.82
2	IARM 160A	(<0.01)	(<0.01)	(<0.01)	(<0.01)	(<0.01)	(<0.01)	(<0.01)	.	.	(<0.01)	.
2	IARM 159A	(<0.01)	(<0.01)	(<0.01)	(<0.01)	(<0.01)	(<0.01)	(<0.01)	.	.	(<0.01)	.
2	C36XCBC30	(<0.002)	0.02	0.04	(<0.01)	0.02	0.003	0.02	1.81	.	.	.

Number	Ag	As	C	Cr	Mg	O	P	S	Sb	Si	Zr	Cu
DH 0209	87.07
BAM 228	.	0.024	0.019	0.036	0.078	.	.	85.34
DH 0201	.	0.076	0.046	.	0.104	.	.	81.84
DH 0208	.	.	.	0.009	.	.	0.027	.	0.083	0.052	.	81.67
DH 0206	.	0.025	0.017	0.059	0.060	0.043	.	83.05
DH 0203	0.329	0.23	.	76.88
DH 0204	.	.	.	0.009	.	.	0.007	.	0.336	0.22	.	77.00
DH 0205	0.008	.	0.350	0.22	.	76.82
DH 0207	0.014	.	.	65.66
DH 0202	.	.	.	0.003	.	.	.	0.037	0.008	.	.	98.15
C37X2180	.	.	(0.002)	0.033	.	.	0.0015	0.006	.	0.56	.	96.60
C36XCBC40	.	.	.	0.01	0.09	.	.
IARM 158B	(0.01)	(0.001)	0.002	0.85	.	0.002	0.005	0.003	0.002	0.02	.	98.5
IARM 158C	(0.01)	(0.001)	0.002	1.04	.	0.002	0.005	0.003	0.002	0.02	.	98.5
IARM Cu172-18	.	.	.	0.0007	.	.	(0.003)	.	.	0.057	.	97.7
SRM 460	.	.	.	0.005	0.005	0.077	.	(97.5)
SRM 459	.	.	.	0.005	0.007	0.077	.	(97.7)
SRM 458	.	.	.	0.004	0.003	0.035	.	(97.9)
C36XCBC20	.	.	.	0.005	0.05	.	.
C37X2260	.	.	0.006	0.003	.	.	0.0025	0.0005	.	3.54	.	91.58
IARM 160A	3.03	.	0.003	(<0.01)	.	.	(0.004)	(<0.003)	.	(<0.01)	0.40	.
IARM 159A	3.48	.	(0.002)	(<0.01)	.	.	(<0.01)	(<0.01)	.	(<0.01)	.	.
C36XCBC30	.	.	.	0.005	0.06	.	.

CUPRO-NICKEL AND COPPER-NICKEL-SILVER CHIPS

= class, where 1 = CRM and 2 = RM

C3x: 50 g units, typical analysis

others: 100 g units

#	Number	Ni	Zn	Ag	Al	C	Co	Cr	Cu	Fe	Mg	Mn	P	Pb	S	Si
1	C36XCN60	33.46	0.026	.	(0.0024)	0.0180	0.0440	1.10	63.35	0.878	.	0.451	0.031	0.0066	0.0109	0.144
1	IARM 85C	31.3	0.057	<0.002	<0.01	0.008	0.016	0.002	67.3	0.63	0.01	0.65	(0.003)	0.004	(0.002)	0.01
1	IARM Cu715-20	31.0	(0.007)	.	(0.004)	(0.005)	(0.004)	.	67.4	0.51	(0.005)	0.80	(0.009)	(0.001)	(0.002)	0.09
1	BCS 180/2	30.35	.	.	.	0.04	.	.	68.12	0.68	.	0.75	.	(0.003)	0.006	(0.018)
2	C36XCN40	30.2	0.04	.	.	0.50	0.003	0.33	.	0.015	.	0.54
1	IARM 236A	30.0	0.002	.	0.003	0.010	0.004	0.002	66.7	0.91	.	1.04	0.003	0.004	0.003	0.19
1	C36XCN100	29.3	.	.	.	0.064	0.081	1.59	61.01	4.28	0.0026	0.262	(0.020)	0.004	0.055	1.02
2	C36XCN90	28.1	.	.	.	0.02	<0.01	2.19	.	0.93	.	1.20	0.016	0.05	0.002	0.56
1	IARM 298A	19.6	5.8	(0.009)	(0.003)	(0.013)	(0.016)	(0.005)	65.3	0.73	0.0004	0.34	(0.004)	4.0	(0.011)	0.019
1	SRM 880	18.13	27.3	54.51	(0.004)	.	<0.001	.	(0.002)	.	.
1	C34XNS50	17.16	(23)	0.0102	0.674	.	0.197	0.0014	55.11	0.717	0.704	0.127	0.067	1.29	.	0.158
1	GBW 02104	14.87	20.81	Rem	0.47	0.033	0.32	0.0048	0.019	.	0.146
1	IARM CuH130-18	14.6	0.0015	(0.0010)	2.76	(0.006)	0.0037	(0.002)	80.9	0.84	0.0013	0.449	(0.004)	(0.0020)	(0.0010)	0.024
1	IARM CuH191-18	14.5	0.0010	(0.0020)	1.60	(0.004)	(0.002)	(0.0013)	(79.6)	0.96	0.0059	3.79	(0.003)	(0.0030)	(0.002)	(0.017)
1	SRM 875	10.42	0.11	.	.	(0.0035)	.	.	87.83	1.45	(0.0010)	<0.0007	0.0020	0.0092	(0.0011)	(0.0008)
1	SRM 874	10.18	(0.002)	.	.	(0.0023)	.	.	88.49	1.22	(0.0002)	0.0020	(0.002)	<0.0005	(0.0011)	(0.0006)
1	IARM 84C	9.8	0.13	(0.002)	.	(0.003)	(0.006)	.	89.4	0.28	.	(0.04)	(0.06)	0.047	(0.006)	(0.004)
2	C36XCN10	9.5	0.10	.	.	1.98	0.015	1.91	.	0.05	.	0.19
2	CURM 62.12	7.94	0.180	.	.	.	0.081	.	89.42	0.45	0.002	1.59	.	0.053	0.034	0.109
2	C34XNS10	7.67	29.0	0.05	.	0.02	0.010	0.05	<0.002	0.03

#	Number	Ni	Zn	Ag	Al	C	Co	Cr	Cu	Fe	Mg	Mn	P	Pb	S	Si
	Number	As	B	Bi	N	Nb	O	Sb	Sn	Ti	Zr					
	C36XCN60	.	(0.0015)	0.0058	.	0.514	.	.	0.0307	0.0066	.					
	IARM 85C	0.0009	0.005	.	.					
	IARM Cu715-20	(0.004)	0.073	.					
	BCS 180/2					
	C36XCN40					
	IARM 236A	.	.	0.003	0.0002	.	0.002	<0.005	0.005	.	.					
	C36XCN100	.	0.0029	0.014	.	0.89	.	.	.	0.03	(0.055)					
	C36XCN90	.	0.005	<0.01	0.12	0.13					
	IARM 298A	(0.004)	<0.005	0.014	<0.001	<0.01	<0.005	(0.04)	4.0	.	<0.01					
	SRM 880					
	C34XNS50	0.194	.	.					
	GBW 02104	0.0098	.	0.0019	.	.	.	0.0020	.	.	.					
	IARM CuH130-18	(0.0060)	(0.0009)	(0.0020)	(0.0006)	.	(0.0006)	(0.0030)	(0.0010)	(0.0010)	(0.0008)	CRM				
	IARM CuH191-18	.	(0.0030)	(0.0020)	(0.0020)	.	.	CRM				
	SRM 875	(0.0010)	.	(0.003)	Cd: 0.0022	(0.14)	<0.001	(0.009)	(0.0002)	Se: (0.0004)						
	SRM 874	(0.0006)	.	<0.0002	Cd: <0.0002	(0.06)	<0.001	0.007	(0.0001)	Se: 0.00015						
	IARM 84C	(0.0012)	0.13	.	.	.					
	C36XCN10					
	CURM 62.12	0.111	.	.					
	C34XNS10					
	Number	As	B	Bi	N	Nb	O	Sb	Sn	Ti	Zr					

GUN METAL CHIPS

= class, where 1 = CRM and 2 = RM

C3X: 50 g units, typical analysis

100 g units

#	Number	Sn	Ni	Pb	Zn	Cu	Ag	Al	As	Bi	Cr	Fe	Mn	P	S	Sb	Si
1	BCS 207/2	9.74	0.28	0.70	1.60	87.35	.	0.013	0.066	0.04	.	0.029	.	(0.018)	.	0.10	0.016
1	C33XGM70	9.23	0.36	0.78	2.06	.	.	0.03	0.12	0.08	.	0.05	0.18	0.067	0.001	0.06	0.09
1	C33XGM60	7.31	1.069	3.11	2.99	84.46	0.0114	0.136	0.175	0.037	0.0019	0.131	0.0912	0.0566	0.07	0.258	0.124
1	BCS 183/4	7.27	1.30	3.15	3.47	84.08	.	(0.002)	0.13	0.005	.	0.056	(0.01)	0.090	0.11	0.23	(0.01)
1	C33XGM290	6.12	0.029	0.052	4.27	89.30	0.0025	(0.0004)	0.0017	0.0020	0.0004	0.011	0.0005	0.136	0.002	0.0015	0.0030
1	CURM 71.33	4.96	0.938	6.84	3.60	83.60	<0.002	<0.001	<0.001	<0.002	<0.0005	0.018	<0.0005	<0.001	<0.001	<0.002	<0.005
1	C33XGM50	4.47	0.697	4.81	5.80	83.38	0.0419	0.084	0.0342	0.0493	Cd: 0.0034	0.254	Co: 0.0453	0.042	0.0697	0.0505	0.0283
2	CURM 71.31	4.06	1.98	6.07	3.98	83.00	0.046	0.023	0.110	0.030	0.039	0.118	0.037	0.060	0.059	0.128	0.020
2	C33XGM80	4.03	0.115	6.78	6.21	82.3	0.105	0.0067	.	0.0138	.	0.298	0.0010	0.0213	0.0055	.	(0.0010)
1	C33XR20	3.19	0.255	3.85	9.14	82.67	0.0029	0.0362	0.0211	0.101	0.0017	0.493	0.0028	0.0208	0.078	0.019	0.0116
1	C33XGM40	2.50	2.05	5.20	7.17	82.6	0.0062	<0.002	0.021	0.041	.	0.051	(0.0019)	<0.005	0.33	0.042	<0.005

BRASS CHIPS

= class, where 1 = CRM and 2 = RM

C31X: 50 g units, typical analysis

GBW: 50-100 g

all others: 100 g

#	Number	Zn	Al	As	Bi	Cu	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn
1	GBW 02101	Rem	0.26	.	0.0024	58.00	0.89	0.73	.	0.0076	0.19	.	0.0091	.	0.54
1	BAM 224	39.40	0.0012	0.0025	0.0006	57.40	0.136	1.70	0.038	0.0112	1.13	0.0004	0.0026	(0.002)	0.066
1	IPT 40	39.1	0.010	.	.	58.10	0.007	.	0.0012	.	2.45	.	0.023	.	0.18
1	IARM 74B	38.9	0.003	<0.01	(<0.005)	60.4	0.011	<0.01	0.006	(0.008)	0.017	(0.003)	0.003	0.003	0.70
1	BAM 223	38.82	(<0.002)	0.0084	0.0018	58.74	0.091	(<0.001)	0.0214	0.0003	2.13	0.0021	0.0040	(<0.003)	0.089
1	BCS 390	38.6	0.83	.	.	57.1	0.83	1.30	0.033	.	1.04	.	.	(0.023)	0.34
1	IARM 75C	38.1	(0.003)	(0.005)	(0.0012)	60.7	(0.06)	(0.0024)	(0.013)	(0.004)	0.42	(0.0015)	(0.007)	(0.005)	0.69
1	IARM 75B	38.0	(0.005)	(0.004)	(0.001)	60.63	0.06	(0.003)	0.02	0.003	0.63	(0.001)	(0.004)	(0.003)	0.59
1	BAM 229	36.63	.	0.00217	.	63.334	0.01061	.	0.01114	(0.00106)	0.0192	.	0.00072	.	0.00485
1	BAM 179/2	35.8	2.22	(0.008)	.	58.5	1.02	0.86	0.56	.	0.35	.	.	0.044	0.70
2	CURM 48.01	32.6	<0.001	0.067	0.038	66.98	0.049	<0.001	0.134	0.016	0.106	.	0.047	0.041	0.002
2	CURM 48.02	32.58	0.013	0.025	0.004	67.16	0.053	0.067	<0.001	0.012	0.084	0.007	0.037	0.010	0.035
2	CURM 48.05	31.0	<0.002	<0.001	<0.0005	68.69	0.066	0.016	0.117	0.007	<0.003	0.013	<0.0005	0.026	0.083
1	C31X B40	28.39	.	0.046	0.0076	71.10	0.026	0.0074	0.0571	(0.023)	0.064	0.0091	0.0076	0.025	0.073
2	CURM 48.04	26.99	<0.001	0.034	0.014	72.68	0.008	0.012	0.096	0.006	0.043	0.011	0.026	0.004	0.018
1	IARM 313A	21.3	(0.001)	0.0010	(0.001)	75.4	0.011	(0.001)	(0.002)	0.09	0.042	0.0016	0.014	3.09	0.006
1	C31X B70	14.51	0.0015	0.0030	0.060	85.17	0.100	0.0010	0.0251	.	0.0338	.	0.0089	0.013	0.0876
1	IARM 151B	12.94	0.002	(0.002)	.	84.0	0.025	0.002	0.011	0.003	0.013	<0.001	(0.001)	3.11	0.009
1	C31XB80	9.52	(0.0013)	0.0081	0.031	90.28	0.0267	0.0012	0.0083	.	0.072	.	0.0108	0.0051	0.035
2	C31XB950	.	(0.001)	(0.01)	(0.01)	95.0	(0.01)	(<0.001)	(<0.001)	(<0.001)	(<0.001)	(<0.001)	(<0.001)	(0.01)	0.5

Number	Ag	B	C	Cd	Co	Cr	Se
GBW 02101
BAM 224
IPT 40	0.002	.	.	0.049	.	.	.
IARM 74B	(0.005)
BAM 223
BCS 390	.	.	.	(0.011)	.	.	.
IARM 75C	(0.004)	<0.1	(0.002)	(0.0015)	(0.0007)	0.0009	(0.005)
IARM 75B	(0.005)	.	(0.004)	.	(0.003)	.	.
BAM 229	0.0034	.
BCS 179/2	.	.	.	(0.003)	.	.	.
CURM 48.01	.	.	.	<0.0003	.	.	.
CURM 48.02	.	.	.	<0.0005	.	0.004	.
CURM 48.05	.	.	.	<0.0003	.	.	.
C31XB40	.	.	.	0.0330	0.033	0.087	.
CURM 48.04	.	.	.	<0.0003	.	.	.
IARM 313A	0.0017	0.0008	(0.002)	(0.0003)	(0.004)	(0.001)	(0.001)
C31X B70	.	0.0029	.	0.0011	0.0124	0.0006	.
IARM 151B	(0.01)	.	0.005	.	.	(0.003)	.
C31XB80	.	0.0021
C31XB950

BRASS CHIPS

= class, where 1 = CRM and 2 = RM

C31X: 50 g units, typical analysis

others: 100 g units

#	Number	Cu	Zn	Al	Fe	Mn	Ni	Pb	Sn	As	Bi	Sb	Si
2	CURM 30.09	89.53	<10.47	<0.001	0.0005	<0.0003	<0.003	<0.001	0.001	<0.001	<0.001	<0.001	<0.001
2	CURM 43.02	76.21	20.82	2.40	0.128	0.035	0.068	0.064	0.060	0.083	<0.001	<0.001	0.038
2	CURM 43.01	74.36	22.44	2.75	0.008	0.064	0.121	<0.002	0.116	0.118	<0.002	<0.001	0.063
1	NM 421	70.48	29.39	.	0.07
1	NM 242	70.19	29.47	.	0.062	.	0.05	0.029	0.07	P:0.005	.	.	.
2	CURM 30.05	69.48	30.53	<0.001	<0.003	<0.0005	<0.0005	<0.002	<0.001	<0.001	<0.003	<0.005	<0.001
1	BCS 344	68.98	30.98
2	CURM 30.18	63.66	32.33	3.28	0.006	<0.001	<0.001	<0.005	0.58	<0.005	<0.001	<0.001	0.131
2	CURM 30.20	61.46	35.71	2.32	<0.005	<0.001	<0.001	<0.002	0.40	<0.001	<0.002	<0.002	0.17
2	CURM 30.15	60.66	<38.88	<0.001	0.50	<0.001	<0.001	<0.005	0.002	<0.005	<0.001	<0.001	<0.005
2	CURM 30.16	60.53	<38.33	<0.001	1.14	<0.001	<0.001	<0.005	0.002	<0.005	<0.001	<0.001	<0.005
1	C31XB20	60.3	.	0.19	0.10	0.31	0.22	0.31	0.18	0.14	0.04	0.10	0.01
2	CURM 30.11	59.86	<38.17	<0.001	0.002	0.23	1.70	0.005	0.002	<0.001	<0.002	<0.001	<0.001
2	CURM 30.24	58.33	<38.32	<0.001	0.001	<0.001	<0.001	3.31	0.002	<0.001	<0.002	<0.001	<0.001
2	CURM 30.21	56.23	40.08	1.44	0.003	<0.001	<0.001	0.004	2.01	<0.001	.	<0.002	0.213
2	DSZU MCX01	Rem	36.3	.	0.01	no uncertainties	.	0.005	0.0002	0.0001	.	0.0005	.

LEADED AND MANGANESE BRASS CHIPS

= class, where 1 = CRM and 2 = RM

C31X: 50 g units, typical analysis

others: 100 g units

#	Number	Pb	Mn	Zn	Al	As	Fe	Ni	P	Sb	Si	Sn	Cu
2	CURM H30.24	3.02	<0.001	37.92	<0.001	<0.001	0.005	<0.001	.	<0.001	<0.001	<0.001	58.87
1	C31X 783510	2.91	.	35.20	0.0146	0.0011	0.134	0.144	0.0197	0.0047	0.053	0.407	60.96
1	IARM Cu360-18	2.73	0.0131	35.1	(0.010)	0.026	0.27	0.0120	(0.003)	0.012	(0.010)	0.29	61.6
1	NM 241	2.64	0.005	38.92	.	.	0.11	0.04	0.004	.	.	0.14	58.1
1	NM 412	2.56	.	38.99	.	.	0.09	0.12	58.18
1	BCS 385	2.24	(<0.005)	38.5	(<0.005)	.	0.15	0.13	.	(<0.01)	.	0.27	58.7
2	C31X 783520	2.08	.	32.88	0.199	0.046	0.077	0.0088	0.0149	0.053	.	0.202	64.34
1	C31X 783550	1.64	.	6.23	0.077	0.104	0.126	0.249	0.018	0.114	.	0.116	91.25
2	C31X MNB10	1.44	0.188	29.37	0.596	.	0.268	0.053	.	.	.	0.105	67.77
1	C31X 783530	1.376	.	37.51	0.163	0.110	0.170	0.251	0.0391	0.084	0.038	0.121	60.07
1	C31X 783540	1.03	.	30.09	0.561	0.206	0.020	0.492	0.125	0.188	.	0.046	67.11
1	C31X MNB20	1.02	2.23	32.19	0.268	.	0.66	0.118	.	.	0.233	0.319	63.02
1	C31X MNB50	0.127	0.243	37.91	3.35	.	0.56	1.31	.	.	0.49	1.75	54.14

Number	Ag	B	Bi	C	Cd	Co	Cr	S	Se
CURM H30.24	.	.	<0.001	O:(0.2)	.
C31X 783510	.	0.0005	0.0141	.	.	0.029	.	(0.001)	(0.0045)
IARM Cu360-18	0.011	.	(0.0023)	(0.003)	0.0034	0.0010	(0.003)	.	.
NM 241
NM 412
BCS 385
C31X 783520
C31X 783550
C31X MNB10
C31X 783530	.	(0.0015)	0.0116	.	0.0039	0.0064	.	.	0.004
C31X 783540
C31X MNB20
C31X MNB50

ADMIRALTY & NAVAL BRASS CHIPS

= class, where 1 = CRM and 2 = RM

C31X: 50 g units, typical analysis

others: 100 g units

#	Number	Sn	Pb	Zn	Cu	Al	As	Bi	Co	Fe	Mn	Ni	P	S	Sb	Si
2	CURM 42.25	2.72	0.0023	39.20	57.78	0.021	0.118	<0.001	.	0.003	0.169	<0.001	0.050	0.005	<0.001	<0.001
2	CURM 42.24	2.25	0.91	33.75	62.45	0.067	0.065	0.054	.	0.066	0.065	0.025	0.226	0.012	0.060	0.093
2	C42.25	2.2	<0.01	rem	58.5	0.02	0.10	<0.002	.	<0.005	0.13	<0.005	0.06	0.001	<0.005	<0.002
2	C31XNB40	2.07	0.09	.	63.8	0.29	0.025	0.09	.	0.11	0.02	0.16	0.20	0.002	0.39	0.22
2	CURM 42.23	1.63	0.575	22.13	74.36	0.008	0.168	0.034	.	0.354	0.019	0.168	0.128	0.045	0.356	0.015
1	IARM Cu485-18	0.759	1.76	36.5	60.8	(0.002)	(0.055)	.	.	0.062	0.0013	0.013	.	.	(0.0018)	(0.003)
1	IARM 76D	0.73	1.69	36.8	60.7	(0.002)	(0.004)	0.0011	0.0010	0.013	0.0006	(0.003)	0.0018	0.0012	0.0040	0.0037
1	IARM Cu486-18	0.692	1.31	36.5	61.2	(0.0030)	(0.025)	(0.0004)	Cd:0.0009	0.036	(0.0003)	0.032	(0.004)	(0.0030)	(0.0050)	(0.0020)
2	CURM 42.21	0.60	0.259	31.61	66.78	0.003	<0.003	0.013	.	0.119	<0.001	0.120	0.087	0.034	0.25	0.15
1	IARM 76C	0.66	1.6	37.2	60.4	(0.004)	(0.003)	.	.	0.013	(0.001)	0.003	0.003	(0.001)	(0.004)	(0.003)
2	C42.21	0.54	0.23	rem	66.1	0.005	<0.005	0.012	.	0.06	<0.005	0.096	0.081	0.007	0.19	0.081
1	C31X NB10	0.535	0.504	29.73	68.35	(0.0004)	0.161	0.0065	(0.0006)	0.0367	0.0508	0.520	0.0223	0.0024	0.0057	0.004

SILICON BRASS CHIPS

= class, where 1 = CRM and 2 = RM

typical analysis listed in mass % except * which is mg/kg

50 g units

#	Number	Si	Zn	Cu	Al	Fe	Mn	Ni	Pb	Sn	As	Co	Cr	Mg	P	S	Sb	Bi*	Cd*
1	C31XWSB50	6.07	0.343	90.06	0.218	0.79	0.496	0.492	0.100	1.050	0.0284	0.057	0.0087	0.0012	0.080	0.0081	0.124	298	47
1	C31XWSB10	5.95	7.55 (82.7)	1.90	0.100	0.099	0.076	0.55	0.23	0.13	0.34	0.017	0.003	0.040	<0.002	0.03	.	.	.
1	C31XWSB40	4.40	5.61	86.09	0.290	0.592	1.45	0.228	0.204	0.802	0.0286	0.096	0.103	0.006	0.042	(0.002)	0.0335	318	12
1	C31XWSB40	4.58	5.05	85.7	0.48	0.77	1.85	0.25	0.168	0.80	0.040	0.109	0.045	(0.0007)	0.060	<0.005	0.067	.	.
2	C31XWSB60A	2.61	1.12	Rem	0.10	0.05	0.29	0.37	0.96	0.39	0.01	0.05	.	0.004	0.06	0.01	0.10	100g	last
1	C31XWSB60D	2.48	0.881	94.74	0.059	0.032	0.248	0.117	0.95	0.056	0.0051	0.247	0.058	(0.001)	(0.020)	(0.002)	0.007	56	71

BRONZE CHIPS

= class, where 1 = CRM and 2 = RM

SRM: 150 g chips

all others: 100 g chips

#	Number	Sn	Al	Bi	Cu	Fe	Mn	Ni	P	Pb	Si	Zn
1	IARM 310A	10.56	0.0009	(0.001)	89.2	0.006	(0.001)	0.043	0.094	0.064	(0.001)	0.10
1	IARM 92C	9.65	0.0013	(0.011)	80.35	(0.008)	(0.0016)	0.170	0.073	9.42	(0.0019)	0.146
1	IARM 89C	9.14	(0.002)	(0.003)	87.5	0.004	(0.001)	0.008	0.004	0.17	(0.003)	3.0
1	IARM Cu903-18	8.3	(0.0010)	.	86.5	(0.012)	(0.0004)	0.41	(0.060)	(0.066)	(0.0040)	4.6
1	IARM Cu932-18	6.82	(0.0007)	0.094	81.2	0.070	.	0.454	0.040	7.95	.	3.44
1	IARM 91E	6.69	0.0015	0.109	81.3	0.110	0.0007	0.300	0.026	7.59	0.0021	3.68
1	BAM 227	6.01	(<0.0001)	0.0088	85.57	0.129	.	0.284	(0.0002)	4.12	(<0.01)	3.46
1	IARM CuMB1-18	5.58	(0.0012)	4.51	88.98	(0.0016)	.	0.58	0.049	0.015	.	0.47
1	IARM 267A	4.95	0.003	(0.005)	87.8	0.019	(0.002)	5.1	0.037	0.026	0.003	2.06
1	IARM 78B	4.73	(0.002)	(0.001)	87.7	0.02	(0.002)	0.077	0.19	3.87	<0.002	3.55
1	IARM 77B	4.66	(0.001)	(0.004)	95.2	0.002	(0.002)	0.002	0.148	0.016	(0.003)	0.007
1	SRM 158A	0.96	0.46	.	90.93	1.23	1.11	0.001	0.026	0.097	3.03	2.08
1	IARM 83B	0.85	0.002	.	58.7	0.97	0.13	0.010	0.004	0.017	(0.003)	39.3
1	IARM 88C	0.147	5.79	0.004	64.5	2.98	2.99	0.276	0.020	0.133	0.091	22.86
1	IARM 80D	0.093	9.67	(0.004)	(81.7)	2.99	0.346	5.01	(0.005)	(0.005)	0.025	(0.007)
1	IARM 72B	0.029	.	.	90.08	0.007	.	0.004	0.005	1.99	(0.002)	7.81
1	IARM 79B	0.017	9.19	(0.003)	88.4	2.13	0.16	0.075	0.005	(0.003)	0.019	0.013
1	IARM 82B	0.017	0.002	.	95.3	0.080	1.04	0.011	0.004	0.011	3.22	0.38
1	IARM 79C	0.010	9.20	.	87.6	2.28	0.20	0.55	0.006	<0.005	0.033	0.014
2	IARM 94A	(<0.01)	10.63	.	.	4.04	0.16	4.37	<0.01	0.009	<0.01	0.09
IARM Cu647-18	(<0.01)	0.0027	CRM	(96.5)	(0.0056)	(0.099)	2.69	(<0.02)	(<0.007)	0.70	(0.005)	
1	IARM 93B	0.009	10.33	.	85.4	3.87	0.024	0.088	(0.002)	0.012	0.024	0.17
1	IARM Cu655-18	0.009	(0.0020)	.	95.5	0.055	0.98	0.0034	(0.0020)	(0.018)	3.15	0.149
1	IARM 204A	0.005	10.55	.	83.3	3.87	0.052	1.95	0.007	0.004	0.034	0.22
1	IARM 94B	(0.003)	10.8	.	80.6	3.99	0.071	4.31	0.011	0.004	0.028	0.14

#	Number	Sn	Al	Bi	Cu	Fe	Mn	Ni	P	Pb	Si	Zn
	Number	Ag	As	C	Co	Cr	S	Sb				
	IARM 310A	0.0020	(0.002)	(0.005)	0.0011	(0.001)	0.0021	(0.002)				
	IARM 92C	(0.05)	(0.005)	(0.002)	(0.0007)	(0.0007)	0.026	0.078				
	IARM 89C	0.005	0.004	(0.002)	(0.001)	(0.002)	0.0011	0.008				
	IARM Cu903-18	0.0059	(0.0010)	(0.0020)	0.0019	Cr:0.0013	(0.0017)	(0.002)				
	IARM Cu932-18	0.019	0.0073	(0.0025)	(0.0024)	Cd:0.0007	0.031	0.31				
	IARM 91E	0.015	0.008	(0.003)	0.0024	(0.0008)	0.028	0.168	Cd: 0.0011	Se: 0.004		
	BAM 227	Se:0.0028	0.081	.	Te:0.0012	.	0.122	0.160				
	IARM CuMB1-18	.	O:(0.003)	.	Se:(0.0025)	.	(0.0020)	(0.003)				
	IARM 267A	(0.002)	(0.004)	(0.003)	(0.002)	(0.001)	0.0014	<0.03				
	IARM 78B	0.008	<0.003	<0.002	<0.0005	.	0.010	0.01				
	IARM 77B	(0.002)	(0.001)	0.003	.	.	0.002	0.005				
	SRM 158A				
	IARM 83B	(0.002)	.	0.003	(0.003)	(0.003)	(0.001)	(0.004)				
	IARM 88C	0.004	(0.007)	0.005	0.0010	0.008	0.0010	(0.003)				
	IARM 80D	(0.04)	(0.009)	(0.004)	0.022	(0.005)	(0.003)	<0.02				
	IARM 72B	(0.002)	(0.003)	0.002	.	.	0.0015	0.006				
	IARM 79B	0.002	.	0.002	(0.002)	(0.003)	(0.001)	.				
	IARM 82B	.	<0.002	(0.003)	.	0.004	0.003	<0.01				
	IARM 79C	<0.005	0.003	0.003	<0.005	(0.002)	<0.001	<0.005				
	IARM 94A	.	(<0.01)	(0.014)	0.01	.	(0.003)	(<0.01)				
	IARM Cu647-18	.	Mg:(0.0086)	.	Zr:0.044	.	.	.				
	IARM 93B	(0.004)	<0.01	0.007	0.006	(0.007)	0.002	(0.012)				
	IARM Cu655-18	(0.0015)	(0.0004)	(0.0100)	.	.	(0.0010)	(0.0008)				
	IARM 204A	0.009	(<0.01)	0.006	0.008	0.008	(0.002)	(<0.01)				
	IARM 94B	0.017	<0.01	(0.006)	0.011	0.017	0.002	(0.011)				
	Number	Ag	As	C	Co	Cr	S	Sb				

CRM LEAD

analysis listed in mg/kg

Number	Type	Ag	As	Au	Bi	Cd	Cu	Ni	Sb	Se	Sn	Te	Tl	Zn	Units
VS 2036-2001	Powder	2322	.	32.6	100 g powder
BCR 288B	Added impurities	30.5	55.7	.	215.8	33.3	19.3	4.57	32.5	<0.2	30.6	32.8	2.3	8.2	160 g chips
BCR 287B	Thermal refined	15.2	<0.003	.	67.3	0.36	0.98	0.024	0.040	<0.005	<0.05	<0.02	0.73	<0.1	160 g chips
BCR 286B	Electro refined	0.015	<0.0002	.	21.5	0.125	1.49	0.041	0.10	<0.05	<0.05	<0.1	2.5	<0.1	160 g chips

LEAD BASE CHIPS AND POWDER

= class, where 1 = CRM and 2 = RM analysis listed in mass % BCS: 100g powder CX: 50g chips SRM: 150-200g powder others: 100g chips

#	Number	Sn	Sb	Ag	As	Bi	Ca	Cd	Cu	Fe	In	Na	Ni	Se	Te	Zn	Other
1	SRM 1129	62.7	0.13	0.075	0.055	0.13	.	.	0.16	.	.	.	0.010
1	SRM 127b	39.3	0.43	0.01	0.01	0.06	.	.	0.011	.	.	.	0.012
1	C93X S30APR30	33.0	0.96	0.021	0.018	0.28	.	0.009	0.008	0.003	.	.	0.010	.	.	0.0053	.
1	C93X S30APR20	30.68	1.80	0.049	0.0178	0.168	.	0.0061	0.062	0.0026	0.0199	.	0.042	.	0.0102	0.028	.
1	C93X S30APR10	28.58	2.54	0.0144	0.010	0.059	.	0.0014	0.192	(0.012)	0.0094	.	0.0010	.	0.0024	(0.004)	.
1	GBW 02401	15.97	16.09	.	0.014	0.024	.	.	1.96	Pb: 65.72
2	C86X PSS40	10.69	16.97	(0.006)	0.278	0.120	.	0.047	0.328	*1	0.013	.	0.0031	.	.	*2	.
2	C86X PSS20	6.33	8.16	0.004	1.42	0.054	.	0.069	0.118	*1	(0.002)	.	0.0080	.	.	*2	.
1	SRM 53e	5.84	10.26	.	0.057	0.052	.	.	0.054	<0.001	.	.	0.003
1	GBW 02402	5.69	15.02	.	0.012	0.0075	.	.	2.88	Pb: 76.22
1	BCS 177/2	5.07	10.1	.	0.05	0.028	.	.	0.12	.	.	.	0.007	.	.	.	Pb: 84.5
2	C85X PSN20	1.87	0.023	0.002	*5	0.0093	.	*1	0.035	.	.	.	*1	0.0058	*1	*1	.
1	C85X ANTH	1.45	6.05	0.0071	0.217	0.0194	.	0.0046	0.0291	0.010	.	.	0.0062	0.0149	0.0071	(0.0007)	.
1	C85X HRH	0.874	1.13	0.247	0.74	0.092	.	(0.0002)	0.080	.	.	.	0.001	0.037	0.002	.	.
1	C84X BA10	0.85	*1	0.0088	*1	0.0084	0.106	0.0016	0.0041	0.006	0.0007	.
2	C84X BA20	0.51	0.002	0.008	*05	0.024	0.061	0.0052	0.003	*2	0.019	.
1	C84X BA80	0.293	0.0009	0.0043	(0.0004)	0.019	0.157	0.0010	0.0007	<0.002	0.0013	0.013	Al: 0.021
2	C85X PSS120	0.21	11.4	0.0015	0.11	0.007	.	*1	0.30	*1	.	.	0.0016	*1	*5	0.087	.
2	C83X PR70	0.189	0.795	0.290	0.051	0.479	.	0.455	0.176	(0.0008)	0.653	.	(0.0015)	0.0052	0.0097	(0.0006)	Pt: 0.0047
2	C85X PSb30	0.13	2.66	*2	0.14	0.010	.	*1	0.032	*1	.	.	0.0013	0.024	*2	(0.0002)	.
2	C84X BA40	0.11	0.061	0.003	(0.0008)	0.074	(0.014)	0.010	0.031	.	.	.	0.0007	.	0.029	(0.0003)	.
2	C85X PSb80	0.085	8.43	0.016	0.02	0.010	.	*1	0.032	*1	.	.	0.0014	0.0007	*5	(0.0002)	.
2	C85X PSb100	0.080	10.2	0.0015	0.11	0.007	.	*1	0.14	*5	.	.	0.0013	*1	*2	0.014	.
2	C85X 0616Pb10	0.070	1.78	0.002	0.070	0.025	.	0.0023	0.048	*1	.	.	0.001	0.018	0.001	0.001	.
2	C85X PSb50	0.057	5.14	0.0017	0.12	0.022	.	*1	0.007	*1	.	.	0.0025	0.0008	*1	*1	.
1	C83X PR40	0.009	0.012	0.014	(0.002)	0.014	0.0026	0.010	0.015	.	0.005	0.001	0.013	0.003	0.025	0.005	Au: 0.002
1	C83X PR10	0.004	0.005	0.088	0.050	0.080	0.004	0.075	0.006	.	0.045	0.01	0.001	<0.002	0.003	0.002	Au: 0.008
2	BM Pb	<0.0005	(5ppm)	<0.0003	<0.0005	<0.004	.	.	<0.0005	.	.	.	<0.0001	.	.	<0.001	Pb: 99.99

* In the above chart, * represents <0.00 so that, for example, *1=<0.001
C83X-86X, C93X: typical analysis

LEAD-SILVER ALLOY CHIPS

typical analysis

Class	Number	Ag	Al	As	Bi	Cd	Cu	Fe	In	Sb	Sn	Zn	Units
RM	C82X Ag6.0	6.0	0.002	0.025	0.54	0.010	0.19	0.001	0.006	0.48	0.50	0.008	50 g
RM	C82X Ag3.5	3.48	<0.001	0.022	0.27	0.004	0.075	0.001	0.045	0.11	0.24	0.001	50 g
CRM	C82X Ag1.5	1.55	.	0.006	0.06	.	0.27	.	.	0.39	0.04	0.004	50 g

RM LEAD BASE BATTERY ALLOY CHIPS

typical analysis

50 g units

Number	Sn	Ag	As	Bi	Ca	Cd	Cu	Sb	Te	Zn
C84X BA60	0.73	0.002	<0.001	0.008	0.095	(0.002)	0.0010	0.001	<0.001	<0.001
C84X BA70	0.61	0.002	<0.001	0.009	0.036	<0.002	0.0009	0.002	<0.001	<0.0005

CRM	MAGNESIUM CHIPS															Units
	typical analysis															
Number	Ag	Al	Be	Ca	Cd	Ce	Cu	Fe	La	Mn	Ni	Pb	Si	Sn	Zn	Units
C61XMgP30	0.013	0.090	<0.0001	0.053	0.015	0.006	0.030	0.014	0.004	0.015	0.005	0.015	0.050	0.016	0.019	50 g
C61XMgP20	0.003	0.065	<0.0001	0.014	0.006	0.002	0.012	0.006	0.002	0.012	0.003	0.006	0.031	0.007	0.012	50 g
C61XMgP10	<0.001	0.013	<0.0005	<0.001	<0.0005	.	(0.0006)	0.027	.	0.0037	<0.002	0.005	0.005	(0.001)	0.002	50 g

MAGNESIUM BASE CHIPS

= class, where 1 = CRM and 2 = RM

BCS: 100 g units

CX: typical analysis 50 g units

#	Number	Al	RE	Ag	Mn	Zn	Be	Ca	Cd	Cu	Fe	Ni	Pb	Si	Sn	Zr	Other
1	BCS 316	8.01	.	.	0.28	0.68	.	.	.	0.040	0.009	0.004	0.024	0.055	0.005	.	.
1	C65XMgA10	5.45	.	0.012	0.060	1.26	0.006	0.029	0.013	0.221	0.021	0.021	0.012	0.20	0.072	(0.0015)	Ce: 0.009 La: 0.007
1	C65XMgB30	3.21	.	(0.002)	0.012	0.60	0.0030	0.029	0.011	0.021	0.007	0.0019	0.004	0.011	0.005	.	.
1	C65XMgB10	2.39	.	0.03	0.68	1.71	0.0007	0.41	0.07	0.20	0.016	0.012	0.01	0.17	0.011	.	Ce: 0.015 La: 0.013
2	C65XMgB20	2.32	.	.	0.44	0.95	.	0.008	.	0.096	0.015	0.005	0.012	0.06	0.012	.	.
2	C63XMgE20	0.056	.	.	1.58	0.04	.	(0.003)	.	0.058	0.009	0.012	0.013	0.035	0.011	.	.
2	C65XMgD30	0.041	0.008	0.005	0.28	1.97	0.0003	.	.	0.058	0.023	0.002	0.009	0.020	0.007	0.029	.
1	C63XMgE30	0.015	.	0.005	2.36	0.022	.	0.13	0.001	0.012	0.004	0.0023	0.005	0.01	0.0057	.	.
2	C67XMgF30	0.01	2.40	.	0.015	3.18	.	0.006	.	0.03	0.009	0.002	0.017	0.005	0.006	0.48	.
1	BCS 307	(0.008)	2.84	.	0.006	2.08	.	.	.	0.005	0.002	0.56	.
2	C66XMgD40	0.006	.	.	0.02	2.80	.	0.004	.	0.01	0.003	0.002	0.017	0.01	0.003	0.44	.
2	C68XMgH40	0.004	2.4	2.05	0.015	0.17	.	.	.	0.03	0.001	0.004	.	0.002	.	0.46	.
2	C68XMgL10	0.002	2.09	1.41	0.016	0.009	.	.	.	0.013	0.009	0.005	.	0.001	.	0.54	Th: 0.24

RE = Total Rare Earths

RM MANGANESE

Number	Mn	As	C	Co	Cu	Fe	Ni	P	Pb	S	Si	V	Units
BM Mn	99.9	<0.0001	<0.0005	<0.0001	<0.0002	<0.0020	<0.0001	<0.0002	<0.0001	0.00040	<0.0010	<0.0001	100 g chips

NICKEL POWDER

certified analysis listed in mg/kg except % which is mass %

Number	Ag	Al	Au	C	Cr	Cu	Fe	Ir	Mn	Mo	Ni%	Os	P	Pb	Pd	Pt	Rh	Ru	S	Si	Units
CRM - nickel ore																					
VS 1702-86	23.4	.	0.84	.	.	(3%)	.	0.11	.	.	5.4	0.06	.	.	30.0	8.6	0.98	0.34	.	.	100 g
RM - nickel powder																					
BS HPN-1	(<0.1)	70	.	268	22	2	202	.	2	3	.	.	5	0.2	4	6	100 g

continued informational values

Number	As	B	Ba	Be	Bi	Ca	Cd	Co	Ga	H	In	Mg	N	Na	O	Sb	Se	Sn	Te	Ti	Tl	V	Zn
VS 1702-86
BS HPN-1	<0.5	<2	<1	<1	<0.2	3	<0.1	<2	<0.5	70	<0.2	1	17	4	1400	<0.1	<0.2	<1	<0.2	<1	<0.1	<1	<1

CRM NICKEL CHIPS

= class, where 1 = CRM and 2 = RM

100 g units

#	Number	Ag	Al	As	B	Be	Bi	C	Ca	Cd	Co	Cr	Cu	Fe
2	IARM 190A	0.00109	0.0050	0.0028	<0.0005	(<0.0001)	0.00111	0.0022	<0.0010	0.0005	0.0008	(0.0001)	0.0017	0.0099
2	IARM 189A	0.00024	0.0044	0.00007	(<0.0005)	(<0.0001)	0.00026	0.0023	<0.0010	0.00008	0.00031	(0.0010)	0.00090	0.0038
2	IARM 188A	0.00011	0.0024	0.00007	(<0.0005)	(<0.0001)	0.00009	0.0022	<0.0010	0.00002	0.00017	(0.0006)	0.00018	0.0019
2	IARM 187A	0.00001	0.0011	0.00001	(<0.0005)	(<0.0001)	<0.00001	0.0013	<0.0010	(<0.00001)	0.00010	(0.0003)	0.00022	0.0019
2	IARM 191A	0.00001	0.00015	0.0013	(<0.0005)	(<0.0001)	<0.00001	0.0014	<0.0010	<0.0001	0.0545	0.00021	0.00042	0.00079
1	BAM RS 4	<0.0001	<0.0001	<0.00005	(<0.0002)	.	(<0.00001)	0.00094	<0.0001	<0.00002	<0.0001	<0.00005	<0.0002	0.00042
1	IARM 50C	.	(0.004)	.	0.0027	.	.	0.015	.	.	(0.011)	(0.005)	0.028	0.084

Number	Ga	Mg	Mn	Mo	N	Ni	O	P	Pb	S	Sb	Se
IARM 190A	<0.00005	(0.0006)	0.00018	(<0.0001)	(0.0001)	.	(0.0019)	0.0034	0.00093	0.00033	0.0011	0.00065
IARM 189A	<0.00005	(0.0008)	0.00019	(<0.0001)	(0.0001)	.	(0.0018)	0.00037	0.00029	0.00018	0.00039	0.00021
IARM 188A	<0.00005	(0.0004)	0.00023	<0.0001	(0.0001)	.	(0.0017)	0.00014	0.00010	0.00018	0.00011	0.00007
IARM 187A	<0.00005	(0.0002)	0.00030	(<0.0001)	(0.0001)	.	(0.0014)	<0.00010	0.000015	0.00019	<0.00005	<0.00001
IARM 191A	<0.00005	(0.0002)	0.00031	(<0.0001)	(0.0002)	.	(0.0030)	<0.00010	0.00003	0.00021	<0.00005	0.00019
BAM RS 4	<0.00002	<0.00008	<0.00005	(<0.00002)	0.00025	99.995	(0.0029)	.	<0.0001	(<0.0002)	<0.00002	<0.0001
IARM 50C	.	0.005	0.22	.	(0.002)	99.4	.	(0.0014)	.	0.0012	.	.

Number	Si	Sn	Te	Ti	Tl	V	W	Zn
IARM 190A	0.0028	0.00062	0.00089	(0.0006)	0.00058	(<0.00005)	.	0.00081
IARM 189A	0.0019	0.00022	0.00017	(0.0003)	0.00023	(<0.00005)	.	0.00028
IARM 188A	0.0018	0.00011	0.00008	(0.0002)	(0.00009)	(<0.00005)	.	0.00023
IARM 187A	(0.0018)	0.00004	<0.00001	(0.0003)	<0.00002	(0.00008)	.	<0.00005
IARM 191A	(0.0005)	0.00004	<0.00001	(<0.0001)	<0.00002	(<0.00005)	.	0.00019
BAM RS 4	(<0.0002)	<0.00003	(<0.00002)	.	<0.00002	(<0.00002)	(<0.00001)	<0.0004
IARM 50C	0.031	.	.	0.026

NICKEL ALLOY CHIPS

= class, where 1 = CRM and 2 = RM

#	Number	Al	C	Co	Cr	Cu	Fe	Mg	Mn	Mo	Nb	Ni	Si	Ti	V	W
1	IARM 283A	6.05	0.114	9.8	8.05	(0.01)	0.044	0.0033	(0.001)	5.94	0.020	64.4	0.019	0.98	0.0058	0.056
1	IARM 52D	2.95	0.125	0.005	(0.004)	29.6	1.38	0.0065	0.59	.	(0.002)	64.5	0.170	0.60	(0.0010)	.
1	SRM 882	2.85	(0.006)	(0.007)	(0.0001)	31.02	(0.009)	(0.001)	0.0007	.	.	65.25	(0.006)	0.57	(0.0001)	.
1	IARM NiB-3	0.41	(0.003)	0.142	1.55	(0.014)	1.57	0.010	0.70	28.2	0.15	67.2	(0.021)	(0.007)	(0.007)	(0.07)
1	IARM 63B	0.31	0.0025	0.019	0.47	0.012	1.68	0.005	0.61	27.3	(0.001)	69.6	0.019	0.003	(0.010)	0.060
1	VS N2/3	0.20	0.018	.	5.59	0.083	Rem	.	0.84	.	.	76.3	1.40	.	.	.
1	IARM 63D	0.13	0.0079	(0.013)	0.153	(0.003)	1.56	(0.0013)	0.76	26.6	(0.04)	70.4	(0.03)	0.14	(0.007)	(0.02)
2	IARM 203A	0.066	0.005	12.88	0.72	0.05	40.6	(<0.002)	0.023	0.090	5.00	38.44	0.41	1.58	(<0.01)	(0.02)
1	IARM 51D	0.036	0.139	0.011	0.064	32.6	1.68	0.016	1.03	0.019	(0.006)	64.1	0.16	0.033	.	.
1	BCS 363/1	0.027	0.140	0.032	(0.05)	31.90	1.86	.	1.26	.	.	64.7	0.028	(0.03)	.	.
1	IARMNi244H-18	0.23	0.052	(0.005)	6.9	0.013	39.9	0.0014	10.9	(0.003)	0.70	41.1	0.16	0.20	(0.004)	.
1	IARM Ni909-18	(0.009)	(0.006)	13.1	(0.010)	(0.007)	42.4	(0.00012)	(0.030)	.	4.6	37.7	0.42	1.62	.	(0.009)
1	BCS 371	.	0.30	0.39	.	.	.	0.060	0.34	.	.	.
1	VS N10/4	.	0.0074	.	.	(0.005)	0.399	.	0.237	27.04	.	.	0.093	0.085	1.57	.
1	VS N3/4	.	0.0064	.	2.16	4.98	Rem	.	0.424	.	.	.	0.264	.	.	.
1	VS N4/3	.	0.0057	.	0.070	5.65	5.80	.	0.762	4.87	.	.	0.81	.	.	.
1	NCS HC20502	.	0.0015	0.043	0.466	0.027	Rem	.	0.983	4.13	.	80.07	0.317	0.004	.	.

Number	B	N	O	P	Pb	S	Sn	Zr	Units
IARM 283A	0.014	0.0003	0.0004	0.003	Ta:4.3	0.0006	(0.0002)	0.053	100 g
IARM 52D	(0.0020)	.	.	(0.002)	.	(0.0012)	0.0013	0.026	100 g
SRM 882	(0.0001)	.	.	.	(0.0006)	0.0014	(0.003)	(0.0005)	100 g
IARM NiB-3	(0.0020)	0.0027	.	(0.005)	.	(0.0004)	.	.	100 g
IARM 63B	(<0.002)	0.0041	0.0010	0.004	.	(0.0004)	.	(0.002)	100 g
VS N2/3	.	.	.	0.0034	.	0.0025	.	.	100 g
IARM 63D	0.0017	.	.	(0.004)	.	(0.0006)	.	(0.002)	100 g
IARM 203A	(0.002)	.	.	0.006	.	0.0009	.	<0.01	100 g
IARM 51D	.	.	.	(0.010)	.	0.0015	.	.	100 g
BCS 363/1	(0.002)	.	.	100 g
IARMNi244H-18	(0.002)	0.0087	(0.0009)	(0.003)	.	0.0038	(0.0003)	(0.0008)	100 g
IARM Ni909-18	0.0013	0.0026	(0.004)	(0.002)	.	0.0018	.	.	100 g
BCS 371	0.013	.	.	100 g
VS N10/4	.	.	.	0.0022	.	0.0028	.	.	100 g
VS N3/4	0.0018	.	.	100 g
VS N4/3	.	.	.	0.0019	100 g
NCS HC20502	.	.	.	0.0007	.	0.0024	.	.	100 g

Ag:(0.0004) As:(0.0001) Se:(0.0002)

As: 0.0009 Sb: 0.00012

Ta: (0.006)

last of stock

NICKEL BASE CHIPS AND POWDER WITH Cr > 10 % CONTINUED FROM THE PREVIOUS PAGE

IARM 718P-18 is powder, all others chips

Number	Ag	B	Mg	N	O	P	S	Sn	Ta	V	Zr	Units	Other
IARM 329A	0.00007	0.0010	0.0124	0.073	0.0027	0.0059	0.0003	(0.0005)	.	0.009	(0.0012)	100 g	
IARM Ni690-18	.	.	0.0030	0.012	.	(0.004)	0.0007	.	.	0.048	.	100 g	
IARM 67C	.	(0.001)	0.0068	0.035	0.0016	0.011	0.0006	0.0014	(0.006)	0.031	(0.002)	100 g	
IARM 372A	.	0.0016	0.016	(0.011)	(0.0008)	(0.003)	0.0016	.	.	(0.008)	0.017	100 g	
VS N11/3	0.0016	0.003	100 g	
IARM 357A	.	(0.0014)	(0.005)	(0.011)	(0.005)	0.013	0.0021	.	.	0.091	.	100 g	
IARM 338A	(0.0001)	0.0049	0.0058	0.0276	0.0010	(0.003)	0.0008	0.00037	(0.002)	0.0026	0.081	100 g	Y:(0.06%)
IARM 358A	.	(0.0011)	0.0019	0.0045	(0.001)	(0.004)	0.0018	.	.	0.009	0.022	100 g	
IARM 282A	(0.0001)	0.005	(0.004)	0.207	0.0023	0.016	0.0003	(0.003)	(0.005)	0.052	(0.002)	100 g	
VS N14/3	0.0020	0.0029	100 g	
SRM 867	(<0.0001)	(0.002)	.	(0.017)	(0.006)	(0.018)	(0.002)	.	(0.001)	(0.047)	.	100 g	
IARM Ni825-18	.	0.0023	.	0.0093	(0.0020)	0.013	.	0.0023	(0.0011)	0.047	(0.002)	100 g	
IARM NiX-18	.	0.0038	0.0030	0.042	(0.0012)	0.0107	(0.0050)	.	.	(0.037)	.	100 g	
IARM 366A	.	.	(0.004)	0.0136	(0.0010)	0.008	(0.0003)	.	.	(0.028)	(0.012)	100 g	
IARM Ni617-18	.	0.0023	(0.0011)	0.0082	(0.0010)	(0.004)	(0.0007)	.	.	(0.006)	(0.06)	100 g	
SRM 865	(0.0002)	(<0.001)	.	(0.066)	(0.004)	(0.012)	(0.001)	.	(<0.01)	(0.019)	.	150 g	
IARM 68F	.	(0.0050)	(0.006)	0.045	0.0007	(0.006)	(0.0005)	.	.	(0.007)	.	100 g	
IARM 68E	.	0.007	(0.006)	0.050	0.0007	(0.005)	(0.0005)	.	.	(0.007)	.	100 g	
IARM 65D	.	(0.001)	0.007	0.019	0.0005	0.008	0.0004	(0.001)	(0.01)	0.012	(0.002)	100 g	
VS N16/2	.	0.0066	.	.	.	0.0028	0.0019	.	.	0.030	.	100 g	Sb: 0.00014
IARM 54G	.	0.0027	0.0040	0.022	.	0.007	(0.0020)	(0.0009)	.	0.025	.	100 g	
IARM 274A	.	0.002	0.0019	0.007	0.0006	0.007	0.0004	0.001	(0.002)	0.019	(0.001)	100 g	
IARM NiN155-18	.	0.0024	.	0.12	.	0.008	(0.0009)	.	.	0.0236	.	100 g	
IARM Ni925-18	.	0.0034	.	0.0033	0.0011	0.012	0.0024	.	.	(0.031)	.	100 g	
NCS HC41501	0.0023	0.0006	.	.	(0.001)	.	.	100 g	
IARM 328A	.	0.0011	(0.0008)	0.0056	0.0006	(0.004)	0.0006	(0.0002)	(0.0004)	0.008	(0.004)	100 g	
IARM 276A	0.00010	0.0038	0.007	0.0388	0.0010	0.006	0.0005	0.0004	0.011	(0.008)	(0.003)	100 g	
IARM Ni725-18	.	0.0023	(0.005)	0.008	.	0.0047	(0.0008)	(0.0011)	(0.006)	0.013	.	100 g	
IARM 328B	.	(0.0010)	.	(0.006)	.	(0.005)	(0.0006)	.	.	(0.014)	.	100 g	
IARM 362B	.	.	0.008	0.0060	(0.0006)	(0.005)	(0.0004)	.	.	(0.010)	.	100 g	
Number	Ag	B	Mg	N	O	P	S	Sn	Ta	V	Zr	Units	Other
IARMNi256Mo-18	.	0.0009	.	0.022	.	(0.004)	0.0011	.	Ca:0.0014	(0.009)	.	100 g	
NCS HC23504	0.0182	0.0107	100 g	
IARM 347A	Pb:0.0003	0.0020	0.0008	0.062	0.0026	0.023	0.0009	0.011	(0.005)	0.078	(0.002)	100 g	
SRM 866	(<0.0001)	(<0.001)	.	(0.018)	(0.004)	(0.017)	(0.001)	.	(<0.001)	(0.040)	.	100 g	
VS N5/3	0.0014	0.0033	100 g	
IARM 25D	.	0.0036	0.0016	0.034	(0.005)	0.019	0.0013	0.008	.	0.089	.	100 g	
VS N6/4	0.002	0.003	100 g	Pb: 0.004
IARM NiWasp-18	.	0.0061	(0.0018)	0.0046	(0.0009)	0.0032	(0.0004)	.	(0.005)	(0.023)	0.058	100 g	
BCS 478	.	.	.	0.007	.	0.0057	0.0010	100 g	
IARM Ni718P-18	.	.	.	(0.010)	0.014	(0.006)	(0.0013)	.	(0.006)	0.017	.	75 g	POWDER
IARM Ni282-18	.	0.0014	0.0054	.	.	(0.003)	(0.0006)	.	.	(0.013)	(0.0014)	100 g	
BCS 310/1	100 g	
SRM 349a	.	(0.005)	.	.	.	(0.003)	0.0024	.	.	(0.12)	(0.053)	150 g	
BCS 351/1	.	0.0035	0.0016	0.0077	.	0.0045	0.00037	0.00033	0.0033	0.0181	0.0017	100 g	Sb: 0.00024
NCS HC41502	.	0.0025	.	.	.	0.0033	0.0005	.	(0.008)	.	.	100 g	
IARM Ni718-20	.	0.0039	0.0025	0.009	.	0.0032	(0.0030)	.	0.006	0.016	.	100 g	
IARM 287A	.	0.009	0.0023	0.0007	0.0005	(0.001)	0.0008	0.0002	0.010	(0.004)	0.008	100 g	
VS N13/4	.	0.0098	.	.	.	0.0018	0.0020	100 g	Ce: 0.0047
C22X 8030	0.018	(<0.001)	0.001	0.018	.	last	0.05	50 g	Pb: 0.023
VS N9/4	.	0.0049	100 g	
IARM NiPE16-18	.	0.0028	.	(0.006)	(0.0006)	(0.006)	(0.0007)	.	.	(0.018)	0.019	100 g	
BAM 326-1	0.0028	.	.	.	0.129	100 g	
IARM NiH214-18	.	0.0033	0.0053	0.0026	.	(0.0017)	(0.0004)	.	Y:(0.008)	(0.003)	0.026	100 g	
IARM 53F	.	0.0026	0.016	.	.	0.0070	(0.0022)	(0.002)	(0.004)	0.024	.	100 g	
IARM NiC276-18	.	0.0020	(0.010)	(0.017)	.	(0.008)	(0.0007)	.	.	(0.018)	.	100 g	
SRM 864 **	(<0.0001)	0.00283	0.01383	(0.01)	(0.004)	(0.011)	(0.0028)	(0.00074)	(<0.001)	0.0327	(0.00037)	100 g	
IARM NiS-18	.	0.0061	0.0021	.	.	0.006	(<0.001)	.	.	(0.0027)	.	100 g	La: 0.031
VS N12/3	0.0021	0.0027	100 g	
IARM 57E	.	0.008	(0.0013)	.	.	(0.005)	(0.0009)	.	.	0.021	0.037	100 g	
VS N7/3	0.002	0.002	100 g	
IARM 277A	.	0.015	0.0021	0.0017	0.0005	0.002	0.0010	<0.003	(0.02)	0.011	0.010	100 g	
NCS HC23505	0.008	100 g	
VS N8/3	.	0.020	0.0015	.	.	0.0023	0.0016	.	.	0.58	.	100 g	
BCS 350	.	0.013	0.072	100 g	
BCS 387	.	0.016	.	.	.	0.007	0.003	.	Clearance Sale Item	.	.	100 g	
BCS 387/1	0.005	0.005	100 g	
VS N15/3	.	0.02	.	.	.	0.002	.	.	.	0.3	.	100 g	
Number	Ag	B	Mg	N	O	P	S	Sn	Ta	V	Zr	Units	Other

* Provisional Analysis

** SRM 864 also contains, in mg/kg, Pb: 2.27 Tl:0.0029

CRM IN 100 TYPE NICKEL ALLOY CHIPS

analysis listed in mass %

Number	Al	Co	Cr	Mo	Ti	V	B	C	Zr	Units
BCS 345	5.58	14.70	9.93	3.01	4.74	1.00	0.019	0.153	0.044	100 g
BCS 346	(5.5)	(15)	(10)	(3)	(5)	(1)	.	(0.15)	.	100 g

continued analysis listed in mg/kg

Number	Ag	As	Bi	Ca	Cd	In	Ga	Mg	Pb	Sb	Se	Sn	Te	Tl	Zn
BCS 345	<0.2	(2)	<0.2	(<5)	<0.1	.	8	5	0.2	<2	<0.5	6	<0.2	<0.2	<0.5
BCS 346	35	50	10	(36)	0.4	(19)	(52)	147	21	47	9	91	12	.	29

CRM TRACE ELEMENTS IN SUPERALLOY CHIPS

analysis listed in mg/kg

HCl1520-4: 150 g chips, others 100 g powder

Number	Ag	As	B	Bi	Ca	Cd	Ce	Cu	Hf	Ga	Ge	In	P	Mg	Pb	Sb	Sc	Se	Sn	Te	Tl	Zn
NCS HCl1529	5.4	25	13	1.8	.	.	0.19	53	12	49	27	10	80	.	11	33	0.6	2.2	43	1.3	1.1	13
NCS HCl1522	5.3	15	(90)	0.4	11	1.8	(110)	.	.	108	.	30	(40)	15	11	59	.	11	72	2.1	51	105
NCS HCl1521	4.6	11	(100)	0.4	21	4.6	(40)	.	.	32	.	2.6	(40)	16	4.1	95	.	16	53	11	22	32
NCS HCl1528	4.4	44	24	2.0	.	.	0.28	94	33	52	75	31	131	.	8.2	49	1.2	2.5	45	2.3	3.9	15
NCS HCl1520	3.5	17	(100)	4.2	42	7.3	(30)	.	.	29	.	11	(40)	82	12	204	.	43	103	3.0	8.5	24
NCS HCl1527	2.5	96	25	1.2	.	.	0.44	172	3.8	38	38	2.6	55	.	4.7	16	1.2	4.1	18	7.5	4.3	14
NCS HCl1526	1.0	14	47	0.19	.	.	1.8	363	7.4	34	24	7.2	36	.	3.7	3.3	2.7	12	8.3	31	0.16	13
NCS HCl1525	0.78	6.7	90	0.14	.	0.31	0.37	571	3.5	31	13	0.88	41	.	3.4	1.4	1.3	9.8	3.2	28	0.13	12
NCS HCl1524	0.7	72	(100)	3.4	5.3	1.6	(10)	.	.	63	.	9.2	(40)	111	91	6.2	.	53	92	83	8.1	6.0
NCS HCl1523	0.3	72	(100)	0.5	32	1.9	(10)	.	.	28	.	0.4	(40)	53	2.2	7.4	.	43	1040	0.5	83	20

CRM TRACE ELEMENTS IN SUPERALLOY CHIPS

analysis listed in mg/kg

analysis listed in mass %

35 g units

Number	Bi	Pb	Se	Te	Tl	Al	B	C	Co	Cr	Hf	Nb	Ni	Ta	Ti	W	Zr
SRM 897	(0.5)	11.7	9.1	1.05	0.51	(2)	(0.01)	(0.12)	(8.5)	(12)	(1.2)	(0.9)	Rem	(1.75)	(2)	(1.75)	(0.1)
SRM 899	(0.3)	3.9	9.5	5.9	0.252	(2)	(0.01)	(0.12)	(8.5)	(12)	(1.2)	(0.9)	Rem	(1.75)	(2)	(1.75)	(0.1)

RM TIN CHIPS

analysis listed in mass %				analysis listed in mg/kg								100 g chips		
Number	C	Sn	Melting Point °C	As	Bi	Cd	Cu	Fe	In	Ni	Pb	S	Sb	Zn
BM Sn	.	99.9999	.	.	<0.5	.	<0.1	<0.1	.	<0.1	<0.3	.	.	<0.4
BCS 192h	0.001	99.998	231.9	<1	<1	<1	<1	<1	<1	<1	6	2	<5	<1
BCS 192j	0.001	99.996	231.9	<1	<1	<1	<1	<1	<1	<1	<10	2	<10	<1

last of stock

CRM TIN POWDER

analysis listed in mass %												
Number	Ag	As	Cu	Fe	Pb	S	Sb	Zn	SiO ₂	Sn	WO ₃	Units
GBW 07231	0.0025	0.574	.	21.33	2.89	0.183	0.024	0.264	.	45.80	.	100 g
GBW 07232	.	0.306	0.043	9.53	1.62	0.090	0.016	0.120	0.93	.	0.182	100 g

TIN CHIPS AND POWDER

# = class, where 1 = CRM and 2 = RM		BCS: 100 g powder				GBW: 100 g chips				SRM: 75 g powder			all others: typical analysis 50 g chips				
#	Number	Sb	Ag	Cd	Cu	Ni	Pb	Sn	Zn	Al	As	Au	Bi	Co	Fe	In	Te
2	C73XSC70	14.01	0.006	0.0018	6.51	0.008	0.356	.	(0.003)	0.001	0.047	.	0.009	0.0160	0.046	0.014	.
1	GBW 02302	11.81	.	.	6.72	.	1.20	80.27	.	.	0.020	.	0.012
2	C73XSC110	11.7	0.06	1.63	10.7	0.48	0.04	.	0.066	<0.005	0.30	.	0.53	.	0.07	.	.
1	BCS 178/2	9.45	(0.002)	0.14	4.58	0.17	3.18	82.2	0.040	.	0.15	.	0.11	.	0.024	.	.
2	C73XSC90	8.18	0.004	0.078	8.47	0.008	0.20	.	(0.003)	<0.001	0.53	.	0.066	0.0030	0.037	0.010	.
1	GBW 02301	7.87	.	.	4.06	.	1.32	86.61	.	.	0.018	.	0.014
1	SRM 54d	7.04	0.0032	.	3.62	0.0027	0.62	88.57	.	.	0.088	.	0.044	.	0.027	.	.
2	C73XSC40	6.02	0.042	0.052	3.05	0.017	0.514	.	0.008	0.005	0.005	.	0.218	0.0035	0.011	0.011	.
1	C74XHB	5.00	0.070	0.011	4.75	1.12	0.058	.	0.018	.	0.026	.	0.008	.	0.12	.	.
2	C72XSA50R	4.93	.	0.05	0.018	.	0.08	.	0.035	.	0.015	.	0.006	.	(0.004)	.	.
1	C71XSR20	0.063	0.029	0.042	0.055	0.005	0.13	.	0.010	0.003	0.057	0.008	0.057	.	<0.001	0.051	0.023
1	C71XSR10 *	0.0156	0.0121	0.0104	0.0111	0.0041	0.0324	.	0.0146	(0.0016)	0.0102	0.0014	0.0107	.	(0.0021)	0.0120	0.0112

* C71XSR10 also contains Ga: 0.0049 and Hg: 0.0142

CRM TIN-LEAD SOLDER CHIPS AND POWDER

BAM, BCS: powder																all others: typical analysis chips	
Number	Sn	Pb	Ag	As	Au	Bi	Cd	Cu	Fe	In	Ni	Sb	Te	Zn	Units		
C91XS63 PR40	66.8	Rem	0.030	<0.002	0.05	0.030	0.021	0.021	<0.005	0.014	<0.005	0.093	0.006	<0.001	50 g		
BAM BNM 010	63.40	36.47	(0.014)	(0.012)	(<0.001)	0.0245	0.0016	0.0417	(0.0020)	(<0.001)	0.0021	0.0488	.	(<0.0001)	100 g		
C91XS63 PR10	63.0	Rem	0.01	0.007	0.046	0.06	0.006	0.009	0.003	.	0.001	0.28	.	<0.001	50 g		
BCS 347	62.6	Rem	0.099	(0.02)	0.037	0.080	0.004	0.169	(0.002)	.	0.0072	0.191	.	0.0015	100 g		
C91XS63 PR20	62.6	Rem	0.057	0.080	0.090	0.162	0.0168	0.052	0.030	0.019	0.0073	0.614	0.009	0.007	50 g		
C91X S63 PR00 *	60.0	Rem	0.01	0.01	0.015	0.007	0.010	0.02	0.002	0.005	0.002	0.02	0.003	<0.001	50 g		
C91XS30 PR30	30.88	Rem	0.024	0.0126	0.0063	0.294	0.0115	0.102	0.0016	0.0085	0.0269	0.269	.	(0.003)	50 g		

* Provisional Analysis

RM	TITANIUM POWDER														powder 50 g	
	typical analysis															
Number	Ti	Al	Co	Cr	Cu	Fe	Mn	Mo	Ni	P	Pb	Si	W	Zn	Zr	
DH SL2701	98.52	0.018	0.00123	0.046	0.001	0.174	0.009	.	0.029	.	.	0.021	0.011	0.00027	0.00010	
DH SL2703	98.42	0.024	0.00190	0.059	0.002	0.238	0.017	0.016	0.031	<0.006	0.00030	.	0.015	0.00067	0.00020	last

CRM	TITANIUM													
	BCR produced by HIP: 090A: 40 mm ø x 20 mm; 090B: 25 g of 0.2 g cubes IARM: 65 g													
Number	Al	B	C	Co	Cr	Cu	Fe	H	Mn	Mo	N	Nb	Ni	
IARM 312B	0.018	(<0.001)	0.0092	(<0.002)	0.010	(0.003)	0.072	0.0004	(0.001)	(0.003)	0.007	(0.001)	0.019	
IARM 303B	(0.015)	.	0.035	.	0.0018	(0.002)	0.120	(0.0008)	(0.001)	(0.002)	0.017	(0.006)	(0.0013)	
IARM 361A	(0.013)	(0.0005)	(0.012)	(<0.002)	0.008	(0.003)	0.095	(0.0027)	(<0.05)	0.288	(0.006)	(0.004)	0.88	

Number	O	Pd	S	Si	Sn	V	W	Y	Zr
IARM 312B	0.128	(<0.005)	(0.0008)	(0.006)	(0.004)	0.009	(<0.005)	(<0.001)	0.0014
IARM 303B	0.176	0.13	<0.002	(0.006)	(0.006)	(0.0023)	<0.002	Ti:(99.6)	(0.0028)
IARM 361A	0.15	(0.002)	(<0.004)	(0.012)	(0.004)	(0.006)	(<0.03)	(0.0004)	(0.0016)

CRM	TITANIUM ALLOY CHIPS AND POWDER, chart 1 of 2														I
	Units														
Number	Al	V	C	Cr	Cu	Fe	Mn	Mo	N	Nb	Si	Sn	Zr		
IARM 269B	7.86	1.03	(0.014)	(0.0014)	(0.0023)	0.071	0.0071	0.98	(0.006)	(0.004)	(0.025)	0.008	(0.002)		
SRM 2433	7.63	0.98	.	.	.	0.063	.	0.99		
C58A BT13008	6.79	2.25	0.006	.	.	0.04	.	1.71		
C58A ZB13002	6.54	3.61	0.014	.	.	0.066	.	.	0.016	.	0.024	.	.		
IARM Ti64-18	6.52	4.08	(0.034)	(0.013)	.	0.19	.	(0.004)	(0.025)	.	(0.011)	(0.003)	.		
IARM Ti64P-18	6.47	4.24	0.051	.	.	0.216	0.011	.	(0.04)	.	.	0.008	.		
C58A CP13005	6.46	5.1	0.01	0.02	0.0099	0.231	0.0064	.	.	.	0.031	0.001	.		
C58A BT13002	6.29	4.1	0.078	.	.	0.044		
C58A CP13001	6.25	4.1		
BCS 356	6.25	4.05	(0.0085)	0.0112	0.0055	0.124	.	0.0020	0.0103	.	(0.0200)	.	.		
SRM 173C	6.245	4.154	0.027	0.0165	0.0040	0.2130	(0.002)	0.0068	(0.028)	.	(0.019)	(0.010)	0.0053		
C58A BT13005	6.2	4.02	0.013	.	.	0.172		
IARM Ti64ELI-18	6.11	4.01	0.033	(0.004)	(0.002)	0.167	(0.0014)	.	(0.006)	.	(0.014)	(0.022)	.		
C58A CP13004	5.88	1.61	0.017	0.028	0.0085	0.074	0.027	3.58	.	.	0.059	0.0085	.		
C58A FG13003	5.85	3.92	.	.	.	0.09	.	.	0.022	.	0.026	.	.		
IARM Ti662-18	5.61	5.35	0.007	0.046	0.46	0.510	(0.005)	0.0031	0.021	.	0.011	2.01	(0.0011)		
BCS 357	5.46	3.53	(0.0072)	0.0521	0.0537	0.202	.	0.053	0.0148	.	(0.0500)	.	.		
C58A CP13003	5.21	4.89	0.014	0.997	.	1.01	.	4.87	.	.	0.038	.	.		
IARM Ti42515-18	3.99	2.53	0.0067	0.015	(0.0022)	1.58	(0.006)	(0.0014)	0.0026	(0.0016)	0.011	(0.004)	(0.0019)		
IARM Ti1023-18	3.31	9.75	(0.032)	(0.016)	(0.006)	1.98	(0.0024)	(0.003)	(0.005)	.	(0.018)	.	.		
SRM 2432	3.15	10.00	0.008	(<0.01)	(<0.005)	1.77	(<0.01)	.	.	.	0.029	.	(<0.01)		
C58A BT13007	3.13	14.99	0.015	2.95	.	0.077	3.15	.		
SRM 649	3.08	15.1	0.011	2.96	(<0.001)	0.133	(<0.01)	.	(0.01)	(<0.01)	.	3.04	.		
IARM 261E	3.05	2.51	0.012	0.016	0.0025	0.18	(0.001)	0.003	0.006	(0.005)	0.007	0.005	(0.003)		
IARM 261C	3.05	2.46	0.011	0.014	0.003	0.180	(0.003)	0.004	0.005	(0.003)	0.007	0.006	0.003		
IARM 344B	3.03	14.7	0.0095	2.91	(0.0024)	0.118	(0.003)	(0.006)	(0.016)	(0.003)	(0.03)	3.01	(0.002)		
IARM 261D	3.02	2.50	0.011	0.016	0.0028	0.185	(0.002)	0.003	0.0051	(0.003)	0.008	0.005	0.003		
IARM 261A	3.00	2.48	0.007	0.013	(0.002)	0.19	0.0011	(0.003)	0.007	.	0.012	0.008	(0.002)		
IARM 261B	2.98	2.23	0.011	0.016	0.003	0.19	(0.003)	0.004	0.004	(0.002)	0.008	0.004	(0.002)		

Number	B	Co	H	Ni	O	P	Pd	Ru	S	Ta	Ti	W	Y	Units
IARM 269B	(<0.001)	(<0.0005)	0.007	(0.001)	0.090	(0.003)	(<0.005)	(0.004)	(0.003)	(<0.005)	(89.9)	(0.001)	(<0.001)	65 g chips
SRM 2433	50 g chips
C58A BT13008	50 g chips
C58A ZB13002	.	<0.001	50 g chips
IARM Ti64-18	.	.	(0.0031)	0.011	0.181	(89.0)	.	.	65 g chips
IARM Ti64P-18	.	.	(0.0018)	.	(0.15)	.	.	.	(0.0014)	75 g powder
C58A CP13005	50 g chips
C58A BT13002	50 g chips
C58A CP13001	50 g chips
BCS 356	.	.	.	0.0070	50 g chips
SRM 173C	(0.000045)	(0.002)	(0.006)	0.0203	0.164	.	.	(0.0006)	.	.	(89.15)	(0.002)	.	50 g chips
C58A BT13005	50 g chips
IARM Ti64ELI-18	.	.	(0.0021)	(0.003)	0.118	(89.7)	.	.	65 g chips
C58A CP13004	50 g chips
C58A FG13003	50 g chips
IARM Ti662-18	.	.	0.0089	0.039	0.19	85.8	.	.	65 g chips
BCS 357	.	.	.	0.0511	50 g chips
C58A CP13003	50 g chips
IARM Ti42515-18	.	(0.0020)	0.0018	0.009	0.25	(91.6)	.	.	65 g chips
IARM Ti1023-18	.	.	(0.002)	0.009	0.109	84.8	.	.	65 g chips
SRM 2432	(<0.001)	.	.	(<0.01)	(<0.001)	(<0.001)	50 g chips
C58A BT13007	50 g chips
SRM 649	(<0.001)	.	.	(<0.01)	50 g chips
IARM 261E	0.0003	(0.0004)	(0.0005)	0.018	0.084	<0.003	(0.002)	(0.001)	(0.001)	(0.001)	(94.1)	(0.001)	(0.001)	65 g chips
IARM 261C	0.0004	(0.0005)	0.001	0.016	0.085	(0.003)	(0.002)	(0.001)	(0.001)	(0.001)	(94.1)	(0.001)	(0.0004)	65 g chips
IARM 344B	<0.001	<0.004	(0.007)	0.021	0.118	<0.003	<0.03	<0.02	<0.003	<0.04	(76.0)	<0.03	<0.006	65 g chips
IARM 261D	0.0003	<0.001	(0.0005)	0.018	0.083	<0.004	(0.002)	(0.0005)	(0.001)	(0.0005)	(94.2)	(0.001)	(0.0005)	65 g chips
IARM 261A	.	.	0.0023	0.006	0.10	.	.	.	(0.001)	.	.	.	(0.001)	65 g chips
IARM 261B	0.0004	<0.004	(0.001)	0.023	0.083	(0.004)	.	(0.001)	(0.0004)	.	(94.4)	(0.003)	(0.0004)	65 g chips

CRM TUNGSTEN POWDER

analysis listed in mg/kg except % which is mass %

Number	Al	Bi%	Ca	Co	Cr	Cu	Fe	K	Mg	Mn	Mo	Na	Ni	P	Si	Sn	WO ₃ %	Units
BAM S002	29.4	.	46	45	47.0	28.4	53	40.0	38.8	16.7	59	41	29	(7.2)	106	42	.	100 g
VS 1710-79	.	0.146	71.96	100 g

ZINC CHIPS

= class, where 1 = CRM and 2 = RM analysis listed in mass % 100 g chips

#	Number	Zn	Al	As	Cd	Cu	Fe	Mg	Pb	Sn	Ti
1	BM Zn	99.99	<0.0003	<0.0005	<0.004	<0.003	<0.004	<0.001	<0.003	<0.001	<0.001
2	IMN 1	.	.	.	0.00066	0.00080	0.0012	.	0.011	0.00021	.

CRM ZINC PELLETS

Number	Cd	Cu	Fe	Pb	Units
GBW 02701	0.0010	0.00010	0.0010	0.0030	50 grams of 3 mm Ø pellets last of stock

CRM ZINC PELLETS

analysis listed in mg/kg

450g of 3mm Ø pellets

Number	Ag	Al	As	Au	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	In	Ir	K	Mg	Mn
SRM 728	1.08	(0.07)	(<0.005)	(<0.02)	(<0.005)	(0.02)	1.14	(1.0)	(<0.03)	5.68	1.84	(<0.05)	(0.05)	(<0.005)	(<0.005)	(<0.01)	(<0.001)	(0.07)

continued

Number	Mo	Na	Nb	Ni	Pb	Pd	Pt	Rh	Ru	Sb	Sc	Si	Sn	Ti	Tl	V	W	Zr
SRM 728	(<0.01)	(0.01)	(<0.01)	(0.45)	11.13	(<0.05)	(<0.01)	(<0.05)	(<0.01)	(0.5)	(<0.001)	(<0.01)	(0.02)	(0.04)	(0.2)	(<0.001)	(0.4)	(<0.01)

CRM ZINC POWDER

listed in mg/kg

certified analysis

informational analysis

powder 200 g

Number	Ag	Cd	Cu	Fe	Ni	Pb	Ti	Al	As	Bi	Co	In	Sb	Sn	V
BAM M603	1.00	1.69	3.69	2.18	0.43	15.8	3.81	0.22	<1	0.102	0.041	<0.5	0.04	<0.1	<0.2

ZINC SPELTER CHIPS

BS: 50 g units

SRM: 100 g units

Number	Al	Cu	Fe	Pb	Sb	Sn
RM BS SP-D	0.25	<0.0005	0.060	0.038	0.006	<0.001
CRM SRM 2139	0.2049	.	.	0.0302	.	.
RM BS SP-B	0.141	<0.002	0.025	0.021	0.061	<0.001
RM BS SP-C	0.185	<0.0005	0.041	0.005	0.031	<0.001
RM BS SP-A	0.051	<0.0005	0.011	0.003	0.099	<0.001

ZINC ALLOY CHIPS, chart 1 of 2

= class, where 1 = CRM and 2 = RM

C41X-43X: 50 g typical analysis

FNE: 100 g

NCS, SRM: 150 g

others: 50 g units

#	Number	Al	Cu	Cd	Fe	Mg	Mn	Ni	Pb	Sb	Sn	Bi	Cr	Si	Ti
2	C43XZ230	29.8	2.73	0.002	0.008	0.01	0.002	0.003	0.002	.	0.003
1	CAN NZA-1	28.70	1.51	0.00098	0.046	0.020	.	.	0.0030	.	0.0069
1	CAN NZA-4	26.65	2.45	0.0029	0.027	0.0106	.	.	0.0101	.	0.0087
1	CAN NZA-3	25.99	2.00	0.0064	0.066	0.049	.	.	0.0045	.	0.0034
2	C43XZ210	24.9	2.05	0.01	0.0114	0.05	0.009	0.002	0.007	.	0.01
1	CAN NZA-2	23.81	3.00	0.0047	0.021	0.029	.	.	0.0076	.	0.0045
1	CAN NZA-7	13.17	0.212	0.00020	(0.016)	0.052	.	.	0.0136	.	0.0116
2	C43XZ110	11.2	0.47	0.014	0.008	0.05	0.01	0.006	0.015	.	0.02
1	CAN NZA-5	10.85	1.04	0.0095	(0.016)	0.021	.	.	0.0012	.	0.0017
1	C43XZ120	10.05	0.796	0.0114	0.047	0.027	0.0059	0.004	0.0133	0.0039	0.0089	(0.002)	0.0023	(0.008)	0.0054
1	C43XZ130	9.58	0.977	0.0102	0.06	0.020	0.007	0.011	0.012	0.009	0.011
1	C43XZ140	8.24	1.23	0.0067	0.015	0.026	0.0033	0.0052	0.0082	0.011	0.0053	0.010	0.0046	0.010	0.0012
1	CAN NZA-6	7.54	3.17	0.0147	(0.105)	0.00037	.	.	0.0109	.	0.0051
1	C43X Z150	7.36	1.53	0.0030	0.009	0.0024	0.0020	0.0019	0.0054	0.005	0.004	0.005	0.0025	(0.011)	0.0020
1	C42XZ80	7.03	0.0215	0.0003	0.013	0.0033	0.0014	0.0019	0.0025	.	(0.0023)	.	(0.0002)	0.013	.
1	NCSHC28974-Zn	4.85	.	.	.	0.083
1	C43XZ40	4.76	3.21	0.0025	(0.064)	0.0434	0.088	0.0286	(0.002)	0.0043	(0.0024)	0.012	0.0063	(0.0065)	0.0017
1	C43XZ70	4.39	0.0249	0.030	0.027	0.0095	0.0045	0.0067	0.0097	.	0.012	.	(0.001)	0.006	.
2	C42XZ10	4.3	0.003	<0.001	0.002	<0.001	<0.001	0.001	0.002	.	0.002
1	C42XZ50	4.22	0.098	0.0021	0.029	0.073	0.0068	0.0185	0.0048	(0.00055)	0.0022	0.006	0.0018	.	.
1	C43XZ60	4.02	2.72	0.0016	0.019	0.0256	0.0006	0.029	0.0016	0.0045	0.0053	0.049	0.0006	0.012	0.0013
1	C42XZ30	3.72	0.159	0.0048	(0.047)	0.0288	0.0252	0.0102	0.0060	0.003	0.0030	.	0.0020	0.015	.
1	C43XZ30	3.64	1.59	0.0132	0.061	0.0143	0.0125	0.0061	0.0132	0.003	0.0125	0.018	0.004	0.005	.
1	C42XZ40	3.55	0.063	0.008	0.01	0.057	0.008	0.017	0.011	0.002	0.006
1	C43XZ50	3.05	6.05	0.0111	0.023	0.041	0.0030	0.0021	0.0045	.	0.0032	.	0.0010	0.003	0.0009
2	C43XZ20	3.2	0.89	0.01	0.02	0.042	0.008	0.003	0.008	0.008	0.01
2	C41X0336Z40	1.39	0.874	0.638	(0.018)	0.179	0.038	0.0074	2.87	0.048	2.38	0.027	.	.	.

#	Number	Ag	As	Ce	In	La	Tl
2	C43XZ230
1	CAN NZA-1
1	CAN NZA-4
1	CAN NZA-3
2	C43XZ210
1	CAN NZA-2
1	CAN NZA-7
2	C43XZ110
1	CAN NZA-5
1	C43XZ120
1	C43XZ130
1	C43XZ140
1	CAN NZA-6
1	C43X Z150
1	C42XZ80	.	.	0.0081	.	0.0079	.
1	NCSHC28974-Zn
1	C43XZ40
1	C42XZ70	.	.	0.053	.	0.047	.
2	C42XZ10
1	C42XZ50	.	.	0.011	0.0048	0.009	0.006
1	C43XZ60
1	C42XZ30	.	.	(0.0003)	.	(0.0003)	.
1	C43XZ30	.	.	.	(0.0019)	.	(0.0035)
1	C42XZ40	.	.	0.020	0.001	0.019	0.003
1	C43XZ50
2	C43XZ20
2	C41X0336Z40	0.0023	0.0005

ZINC ALLOY CHIPS, chart 2 of 2

= class, where 1 = CRM and 2 = RM

typical analysis

50 g units

#	Number	Al	Cu	Cd	Fe	Mg	Mn	Ni	Pb	Sb	Sn	Bi	Cr
1	C41XGLV40	0.514	0.0321	0.0006	0.0028	0.0034	0.0089	0.0441	0.0062	0.0287	0.0024	0.0061	0.0007
1	C41XGLV60	0.474	0.0394	0.0053	0.0047	.	0.0013	0.0008	0.120	0.0112	0.0152	0.0249	0.0029
1	C41X0336Z30	0.43	0.361	0.341	0.270	0.134	0.0058	.	0.019	.	0.111	.	.
1	C41XGLV70	0.399	0.023	0.00056	0.0031	.	0.0025	0.0060	0.082	0.0031	(0.006)	0.0108	0.0010
1	C41XGLV30	0.334	0.0260	0.0188	0.0031	0.00145	0.0111	0.0300	0.0091	0.058	0.0060	0.0016	0.00084
2	C41X4380Z80	0.225	0.020	0.0079	0.003	0.007	0.0015	0.024	0.73	0.016	0.011	0.011	0.0019
1	C41X4380Z40	0.144	0.0022	0.094	0.056	0.126	0.0007	0.0040	0.325	0.017	0.038	0.011	(0.0003)
1	C41X4380Z70	0.137	0.012	0.015	(0.0044)	0.0028	.	0.012	1.25	0.090	0.0047	.	0.0045
1	C41XZ50	0.13	0.023	0.024	(0.02)	0.012	0.004	0.0116	0.0235	0.006	0.0213	.	.
2	C41XGLV10	0.115	0.0028	0.0093	0.059	.	.	0.0141	0.056	<0.001	0.010	0.0025	.
1	C41X0336Z60	0.105	0.0203	0.014	0.08	0.0008	0.0010	0.0018	1.82	0.234	0.0023	0.123	.
1	C41X2951Z30	0.078	1.89	0.0062	0.029	0.0164	0.0018	0.0010	0.0065	.	(0.006)	.	0.184
2	C41XGLV20	0.070	0.0053	0.0026	0.048	.	.	0.0071	0.214	0.007	0.003	0.017	.
1	C41X4380Z10	0.055	0.175	0.376	0.01	0.0012	0.0015	0.0029	0.068	0.002	0.049	0.0017	0.002
1	C41X0336Z50	0.035	0.023	0.058	0.016	<0.0005	(0.0001)	(0.0005)	0.91	0.008	0.21	(0.001)	.
1	C41X2951Z10	0.029	0.79	0.0005	0.011	0.0029	0.0013	0.0038	0.0042	.	(0.0007)	.	0.083
1	C41X0336Z10	0.014	0.007	0.0056	0.0124	0.0049	0.0035	(0.0006)	0.95	.	0.005	.	.
2	C41XGLV50	0.014	0.0116	0.014	0.077	.	.	0.0029	0.019	0.163	0.020	0.0105	.
1	C41XZ40	0.0096	0.0047	0.0066	0.003	0.0019	0.0012	0.0069	0.0092	0.005	0.0070	.	.
1	C41XZ30	0.0083	0.0019	0.0044	0.002	0.0009	0.0007	0.0031	0.0052	0.0037	0.0039	.	.
1	C41X Z20	0.00082	0.00168	0.00179	0.0077	0.00014	0.00053	0.00131	0.00264	0.00057	0.00159	0.00052	.

#	Number	Ag	As	Co	In	Si	Ti	Tl
1	C41XGLV40	.	(0.0003)	0.0037
1	C41XGLV60	.	0.0014	0.0047
1	C41X0336Z30
1	C41XGLV70	.	0.0016	(0.0001)
1	C41XGLV30	.	(0.0007)	0.00150
2	C41X4380Z80	.	.	.	(0.005)	0.012	.	.
1	C41X4380Z40	.	.	.	(0.002)	0.005	.	.
1	C41X4380Z70	0.009	.	.
1	C41XZ50	.	.	.	0.004	.	.	0.003
2	C41XGLV10	<0.001
1	C41X0336Z60	0.0055	0.0020	.	0.0123	.	0.0132	.
1	C41X2951Z30	0.133
2	C41XGLV20	.	<0.001
1	C41X4380Z10	.	.	.	0.006	.	.	.
1	C41X0336Z50
1	C41X2951Z10	0.278
1	C41X0336Z10
2	C41XGLV50	.	0.004
1	C41XZ40	.	.	.	0.0015	.	<0.005	0.003
1	C41XZ30	.	.	.	0.0007	.	0.0012	0.002
1	C41X Z20	.	.	.	0.00057	.	.	0.00117 Hg: 0.00029

CRM ZIRCALOY-4 CHIPS

certified values listed in mass %

Number	B	Cr	Cu	Fe	Hf	Ni	Sn
SRM 360b	0.191	0.1043	0.00125	0.2138	0.00785	0.00225	1.555
BCR 098	.	0.0906	.	0.2143	.	.	1.4600

informational values listed in mg/kg

Number	Al	C	Co	H	Mn	N	O	P	S	Si	Ti	Units
SRM 360b	57	109	0.97	11	9.2	45	1430	8.7	30	80	15.5	100 g
BCR 098	10 g

CRM ZIRCONIUM ALLOYS

analysis listed in mass %

powder 100 g

Number	Al	C	Cr	Cu	Fe	H	Hf	N	Nb	O	Sn	Ti
IARM Zr702-18	0.014	0.017	(0.009)	.	(0.09)	(0.0011)	0.84	(0.003)	.	0.141	(0.04)	(0.004)
IARM Zr705-18	.	0.009	0.007	(0.007)	{0.08}	{0.0012}	0.38	{0.005}	2.53	0.133	.	.