

INDEX

ALLOY LISTING 24
ALLOY SPECIFICATIONS 25
ALUMINUM BRASS 11
ALUMINUM BRONZE 16, 17, 18

BERYLLIUM ALLOY 4
BISMUTH BRASS 11
BISMUTH BRONZE 18
BRASS 9, 10, 11, 13, 14, 15
BRONZE 15, 16, 17, 18

CARTRIDGE BRASS 11, 12
CHROMIUM COPPER 4
CONVERTER COPPER 5
COPPER 2, 3, 4
COPPER ALLOYS 23
COPPER IN VARIOUS FORMS 2
COPPER WIRE 2

ENVIROBRASS 7

FEDERALLOY 7
FREE CUTTING BRASS 12

GILDING METAL 5
GLOBULE ARC 2
GUN METAL 5

HIGH TENSILE BRASS 15

LEADED BRASS 12, 13
LEADED BRONZE 20, 21, 22
LEADED TIN BRONZE 20, 21, 22

MAGNESIUM ALLOY 5
MANGANESE ALLOY 5
MANGANESE BRASS 13
MANGANESE BRONZE 18

NAVAL BRASS 13
NICKEL ALLOY 6, 7
NICKEL BRASS 14
NICKEL BRONZE 18

PHOSPHOR BRASS 14
PHOSPHOR BRONZE 19
PHOSPHORUS DEOXIDIZED 2

ROD 2, 4, 5, 13, 22

SEBILOY 7
SILICON BRASS 14
SILICON BRONZE 19
SILVER ALLOY 8

TIN BRONZE 20, 21, 22
TIN COPPER 8

WIRE 2

XRF 23

CRM PURITY COPPER DISCS AND RODS

listed in mg/kg IMN in SETS only, as grouped IMN CP: 40mm Ø x 23mm IMN CS: 40mm Ø x 25mm or 6mm Ø x 100mm VS: ~40-45mm Ø x ~25mm

Number	Ag	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	P	Pb	S	Sb	Se	Si	Sn	Te	Zn	Other	
AVAILABLE INDIVIDUALLY																				
VS MO4-K3	299	310	124	285	98	115	419	296	551	261	495	70	332	287	93	489	289	293		
VS MO4-K2.2	51.5	54.4	33.0	29.2	31.8	23.7	48.3	35.2	59.8	41.1	54.8	34	42.6	37.7	29.7	43	40	50.4		
VS MO4-K2.1	50.9	51.9	32.8	29.2	28.2	30.5	56.8	55.1	72.2	41.9	50.3	41	45.9	62.6	.	55	34.9	49.1		
VS MO4-7	50.7	50.5	27.6	26.5	30.6	41.3	84.8	53.0	75.6	39.0	26.8	36.6	60.8	.	13.3	45.4	27.0	68.1		
VS MO4-5	30.1	11.0	5.2	1.0	1.0	0.8	5.1	6.4	4.4	0.93	1.9	2.9	8.3	6.1	3.1	2.0	2.9	16.9		
VS MO4-6	21.0	19.8	10.7	10.0	9.2	11.1	40.4	20.0	32.4	14.0	60	19	22.4	10.6	21	14.6	8	32.4		
VS MO4-K1	15.3	16.0	17.4	15.3	15.2	11.7	25.6	17.5	13.7	12.1	22.4	14.5	17.0	10.3	24.9	10.0	9.6	18.0		
VS MO4-1	11.2	0.96	.	0.19	.	.	2.0	0.97	0.34	.	1.1	2.9	2.8	3.2	0.7	.	.	.		
VS MO4-4	10.4	4.0	2.6	3.1	4.9	3.2	15.4	4.7	16.0	1.1	0.82	3.0	3.5	2.4	2.2	4.8	4.3	7.8		
VS MO4-8	5.0	2.4	1.1	0.49	3.0	.	29.1	3.5	1.8	1.3	9.6	8.7	5.8	0.73	4.6	0.96	0.8	3.2		
VS MO4-3 *	2.9	.	0.11	.	0.30	.	3.9	0.49	0.73	.	4.2	4.4	0.55	.	.	0.48	.	0.97	* SET ONLY	
VS MO4-2 *	0.88	0.6	0.63	0.14	0.26	1.0	40.5	1.1	1.1	2.1	13.2	12.8	0.8	0.7	7.1	1.1	.	2.4	* SET ONLY	
VS MO3-4 *	0.41	0.14	0.73	0.93	1.37	0.38	40.2	7.7	0.80	34.6	9.4	.	0.45	0.42	.	0.64	.	9.8	* SET ONLY	
SET ONLY, AS GROUPED																				
IMN CS1	53.1	2.0	1.1	1.0	0.6	(0.3)	18.4	29.0	46.8	57.7	60.5	65.9	3.0	61.5	(3.0)	52.9	2.1	24.1	B:(1.1)	
IMN CS2	45.6	7.4	6.2	7.4	3.6	35.8	30.5	35.3	26.7	33.8	38.6	44.9	7.5	39.0	(9.4)	33.7	5.6	8.9	B:(2.8)	
IMN CS3	38.9	13.8	12.2	13.4	7.4	10.9	28.3	12.6	11.1	12.1	13.3	18.8	13.0	15.4	(22.2)	13.3	10.6	31.3	B:(4.2)	
IMN CS4	237	42.2	39.6	35.5	24.3	7.0	82.0	8.3	7.2	6.3	7.6	41.3	36.8	6.7	(46.5)	6.2	32.9	44.0	B:(21.7)	
IMN CS5	320	70.5	59.7	66.1	37.5	1.0	90.9	4.3	4.4	2.0	5.0	12.0	63.9	0.9	(54.8)	0.9	49.8	101	B:(35.2)	

Number	Ag	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	P	Pb	S	Sb	Se	Si	Sn	Te	Zn	Other
--------	----	----	----	----	----	----	----	----	----	---	----	---	----	----	----	----	----	----	-------

CRM ELECTROLYTIC COPPER ROD SET

available in SET/6 ONLY listed in mg/kg 3 or 6 mm Ø x 100 mm

Number	Ag	As	Bi	Fe	Ni	Pb	Sb	Sn	Zn	Cu
IMN CF1	45.0	6.7	12.5	42.0	29.0	33.0	24.0	21.0	57.0	Rem
IMN CF2	9.0	1.1	.	2.8	0.7	0.6	1.4	.	2.2	Rem
IMN CF3	3.2	1.8	.	20.0	6.4	8.9	2.2	3.2	3.4	Rem
IMN CF4	18.0	43.0	1.2	3.7	7.8	1.1	11.0	1.0	31.0	Rem
IMN CF5	12.0	2.3	0.25	98.0	3.0	3.2	1.9	1.3	4.7	Rem
IMN CF6	12.0	0.32	(0.012)	1.0	(0.4)	1.8	0.2	(0.06)	.	Rem

CRM COPPER

analysis listed in mg/kg 40 mm Ø x 30 mm

Number	Fe	P	Sn
BAM 391	0.90	3.3	(<0.1)
BAM 390	0.79	1.3	(<0.1)
BAM 392	0.80	7.0	(<0.1)

COPPER WIRE FOR GLOBULE ARC WORK

analysis listed in mg/kg wire form, intended for globule arc work ClC: CRM all others: RM 5 rods 3 mm Ø x 80 mm

Number	Ag	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	Pb	Sb	Se	Sn	Te	Zn	O	P	S	Si
38X ClB	13	0.8	0.1	<0.01	0.03	0.06	1.2	1.2	1.0	0.8	0.6	.	<0.3	0.3	0.45	.	.	.	last
38X ClC	11	0.19	0.10	<0.01	.	<0.005	1.7	(0.005)	0.27	(0.05)	0.10	(0.25)	(0.01)	(0.21)	<0.1	266	<0.05	2.0	<0.1

CHILL CAST PHOSPHORUS DEOXIDIZED COPPER

= Class, where 1 = CRM and 2 = RM, typical analysis

#	Number	P	Cu	Ag	Fe	Al	As	Co	Mn	Ni	Pb	Sb	Sn	Zn
2	CURM 09.01	0.151	99.82	0.011	0.0019	<0.0005	<0.001	<0.0003	<0.0003	<0.0003	<0.0005	<0.0005	<0.0005	<0.0008
2	CURM 09.02	0.078	99.90	0.0055	0.0042	<0.0005	<0.001	<0.0005	<0.0005	<0.0005	<0.0005	<0.0005	<0.0005	<0.001
1	SRM C1253a	0.0561	99.46	0.0494	0.0290	0.0176	0.0436	0.0454	0.0357	0.0491	0.0243	0.0139	0.0499	0.0329
1	SRM C1251a	0.0420	99.89	0.0080	0.0285	(<0.0020)	0.0016	0.00132	0.00046	0.00236	0.00235	0.00149	0.0016	0.0024
1	SRM C1252a	0.0125	99.87	0.0158	0.0072	(<0.0020)	0.0118	0.0087	0.0043	0.0128	0.0060	0.0042	0.0120	0.00694

Number	Au	Bi	Cd	Cr	Mg	S	Se	Si	Te	Units
CURM 09.01	.	<0.0003	<0.001	.	50 mm Ø x 10-12 mm
CURM 09.02	.	<0.0005	<0.002	.	50 mm Ø x 10-12 mm
SRM C1253a	0.0072	(0.0056)	0.0070	0.0260	(0.0150)	(0.0050)	0.0136	(0.0580)	0.0168	32 mm x 32 mm x 19 mm
SRM C1251a	0.00155	0.00037	(<0.0003)	(0.0003)	(<0.0020)	(0.0035)	0.0011	(<0.0050)	0.0016	32 mm x 32 mm x 19 mm
SRM C1252a	0.00339	(0.0019)	0.00169	0.0019	(<0.0020)	(0.0070)	0.0056	(<0.0100)	0.00546	32 mm x 32 mm x 19 mm

CRM COPPER IN VARIOUS FORMS

analysis listed in mg/g each of the blow available in 3 forms A: disc 39 mm Ø x 30 mm B: Rod 8 mm Ø x 100 mm C: Chips 50 g

Number	Ag	Al	As	Au	Be	Bi	Cd	Co	Cr	Fe	Ind	Mg	Mn	Ni	P	Pb	S	Sb	Se	Si	Sn	Te	Ti	Zn	Zr	
ERM-EB075	10.8	2.3																								
ERM-EB074	1.03	.	1.23	0.52	0.31	0.51	0.4	0.83	0.37	5.8	0.49	2.03	0.93	0.61	1.53	2.7	(3.3)	0.57	0.55	.	(1.5)	0.5	0.97	2.2	(8.8)	

CRM COPPER RODS analysis listed in mg/kg IMN: 6 mm Ø x 100 mm SRM: ~6.5 mm Ø x 103 mm

Number	Ag	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	O	P	Pb	S	Sb	Se	Sn	Te	Zn	Cu
SRM 494	50	2.6	0.35	.	0.5	2.0	.	3.7	11.7	.	.	26.5	15	4.5	2.00	70	0.58	400	99.91
IMN CS7R	13.7	0.9	<0.5	(0.02)	0.09	19.7	4.9	2.2	4.4	.	(2.4)	(0.9)	7.0	1.0	<1.0	0.5	<0.05	1.2	.
SRM 495	12.2	1.6	0.50	.	.	6.0	.	5.3	5.4	.	.	3.2	13	8.0	0.63	1.5	0.32	12	99.94
SRM 457	8.086	<2	0.22 (<1)	.	0.227 (<2)	2.4 (<0.1)	.	0.67	367	.	.	0.512	4	0.214	4.05 (<0.1)	0.296 (<3)	.	.	99.97

SRM 457 also contains Au:(<0.05), Cd Si and Ti:(<1) IMN CS7R also contains B:<0.5 and Si:<1.0

BERYLLIUM ALLOY

= class, where 1 = CRM and 2 = RM

* Provisional Analysis

#	Number	Be	Co	Ag	Al	Cr	Cu	Fe	Ni	Pb	Si	Sn	Zn	Alloy	Notes
2	CTIF 4584	2.53	0.04	.	0.033	.	97.05	0.120	0.015	(0.002)	0.166	0.022	0.022		Typical Analysis
2	CTIF 4872	1.93	0.400	.	0.059	(0.04)	97.00	0.107	0.103	0.019	0.16	0.044	0.119	172	Typical Analysis
2	BS 172Be-1	1.89	0.206	.	(0.02)	0.0032	97.68	0.052	0.039	(0.002)	0.055	0.033	0.0070	172	last of stock
1	36X CBC4E	1.869	0.215	.	0.0258	.	97.47	0.0274	0.0080	0.329	0.048	0.002	0.003	173	
1	36X CBC3D	1.840	0.209	.	0.019	.	97.77	0.046	0.007	0.0025	0.039	0.0021	0.004		
1	BS 172Be-2	1.83	(0.06)	.	0.032	0.015	97.7	0.127	0.0165	0.041	(0.029)	0.015	0.0057	172	17025
2	CTIF 4766	1.58	0.64	.	0.027	(0.2)	96.83	0.165	0.203	0.053	0.11	0.100	0.070		Typical Analysis
2	CTIF CuBeCo6	1.54	(1.9)	1.37	0.135	0.0576	93.09	0.109	(1.4)	0.0397	0.26	0.0135	0.0330		Typical Analysis
2	CTIF 4583	0.84	(0.002)	.	0.029	.	96.35	(0.15)	2.02	0.084	0.08	0.25	0.094		Typical Analysis
1	36X CBC6A	0.507	1.045	0.0015	0.0490	.	97.11	0.0243	1.132	0.0014	0.0263	0.0041	0.0010		
1	36X CBC2F	0.439	2.22	0.0013	0.0097	.	97.15	0.0076	0.121	(0.0008)	0.0257	(0.0007)	0.0018		
1	BS 17500	0.43	2.31	(0.0012)	0.0210	0.0015	(97.1)	0.0262	0.095	0.0005	0.0641	(0.0002)	0.065	175	17025 , last
1	36X CBC5B	0.404	0.0084	0.0011	0.0104	.	97.61	0.0108	1.905	0.0015	0.004	0.0013	0.0010	175.1	
1	BS 17510 *	0.37	0.02	<0.05	0.04	0.017	[97.7]	0.04	1.64	0.001	0.14	<0.05	0.004	175.1	
2	CTIF 4873	0.10	0.86	.	0.069	0.080	98.60	0.135	0.050	(0.003)	0.071	(0.007)	(0.003)		Typical Analysis

w = wrought and c = cast; D = disc and M = mushroom

Number	As	C	Ca	Mg	Mn	O	P	S	Sb	Te	Zr	Form	Units
CTIF 4584	(0.002)	c	M 60 mm Ø x 5 mm
CTIF 4872	0.008	c	M 60 mm Ø x 5 mm
BS 172Be-1	(0.001)	(0.001)	.	.	0.0010	.	0.003	(<0.0002)	.	.	.	w	D 38 mm Ø x ~7 mm
36X CBC4E	.	.	.	0.0035	.	.	0.0027	w	D ~38 mm Ø x ~15 mm
36X CBC3D	.	.	.	0.0040	w	D 41 mm Ø x 15 mm
BS 172Be-1	(0.00014)	(0.002)	(0.0008)	(0.01)	0.0070	(0.0008)	0.0014	(0.0003)	.	last	(0.0003)	w	D 38 mm Ø x ~7 or ~10 mm
CTIF 4766	0.007	c	M 60 mm Ø x 5 mm
CTIF CuBeCo6	0.0173	c	M 60 mm Ø x 5 mm
CTIF 4583	0.064	c	M 60 mm Ø x 5 mm
36X CBC6A	.	.	.	0.0070	.	.	0.0016	.	.	.	0.0553	w	D ~40 mm Ø x ~15 mm
36X CBC2F	.	.	.	0.0036	.	.	0.0067	.	.	.	(0.0006)	w	D ~40 mm Ø x ~15 mm
BS 17500	(0.0002)	0.0020	0.0054	0.0076	0.081	(0.0005)	0.0031	(0.0001)	0.0001	(0.0004)	.	w	D 38 mm Ø x ~10 mm last
36X CBC5B	.	.	.	0.0009	w	D ~40 mm Ø x ~15 mm
BS 17510 *	<0.05	0.001	<0.005	0.006	0.002	.	<0.05	<0.05	<0.5	.	0.001	c	D 38 mm Ø x ~7 or 19+ mm
CTIF 4873	(0.002)	c	M 60 mm Ø x 5 mm

CHROMIUM COPPER

= class, where 1 = CRM and 2 = RM

#	Number	Cr	Ag	Al	Fe	Mn	Ni	Pb	Si	Sn	Zn	Zr	Cu
1	IARM 158C	1.04	(0.01)	0.002	0.090	0.019	0.32	0.01	0.02	0.01	0.014	.	98.5
1	IARM 158B	0.85	(0.01)	0.002	0.090	0.019	0.32	0.01	0.02	0.01	0.014	.	98.5
1	BS 18150A	0.79	.	0.0023	0.007	0.0010	0.0019	0.0011	0.027	0.0144	0.0006	0.203	[98.9]
1	BS 18150	0.74	.	0.0009	0.0047	0.0010	0.0010	0.0005	0.019	0.0097	0.0006	0.113	[99.1]
2	HRT CU2019	0.73	.	.	(0.005)	.	.	.	0.030	0.011	.	0.17	98.97
1	36X CCR1E	0.652	0.0042	0.0013	0.0170	.	0.0111	0.0008	.	0.0018	(0.0011)	0.079	99.24
1	36X 274B	0.333	0.0016	0.0011	0.0165	0.0004	2.59	0.0011	0.645	(0.0008)	(0.0009)	.	96.44

Number	As	C	Co	Mg	N	O	P	S	Sb	Units
IARM 158C	(0.001)	0.002	0.002	.	<0.0005	0.002	0.005	0.003	0.002	31 mm Ø x 2 mm
IARM 158B	(0.001)	0.002	0.002	.	<0.0005	0.002	0.005	0.003	0.002	31 mm Ø x 2 or 18 mm
BS 18150A	(0.0003)	0.0010	(0.0003)	.	.	(0.0008)	0.0045	0.0007	(0.0002)	38 mm Ø x ~7 or 19+ mm
BS 18150	(0.0004)	0.0009	(0.0002)	.	.	(0.0006)	0.0037	0.0007	(0.0001)	38 mm Ø x ~7 or 19+ mm
HRT CU2019	(0.005)	.	(0.006)	40 mm Ø x 20 mm
36X CCR1E	0.0007	.	.	(0.0003)	.	.	0.0223	0.0016	.	~50 mm Ø x ~17 mm
36X 274B	.	.	0.0042	.	.	.	0.0015	.	.	~40 mm Ø x ~15 mm

17025
17025

Need a larger size?
Most BS items are
available in any height.

CRM CONVERTER COPPER DISC AND ROD SETS

analysis listed in mass %

AVAILABLE IN SETS ONLY, AS GROUPED

IMN CT: 40 mm Ø x 30 mm

IMN CG, CH: 10 mm Ø x 100 mm

Number	Ag	As	B	Bi	Co	Cu	Fe	Ni	P	Pb	S	Sb	Se	Sn	Te	Zn
IMN CT1	0.057	0.32	0.024	0.018	0.051	.	0.17	0.48	0.082	0.013	0.054	0.33	0.062	0.24	0.053	0.28
IMN CT2	0.042	0.22	0.033	0.013	0.033	.	0.10	0.29	0.059	0.086	0.036	0.24	0.041	0.14	0.036	0.19
IMN CT3	0.026	0.11	0.00093	0.0067	0.013	.	0.083	0.12	0.038	0.31	0.012	0.11	0.018	0.070	0.022	0.11
IMN CT4	0.016	0.050	0.0042	0.0043	0.011	.	0.045	0.049	0.020	0.88	0.0060	0.049	0.011	0.025	0.011	0.045
IMN CT5	0.0062	0.0056	(0.011)	0.0011	0.0061	.	0.016	0.0095	0.0059	(1.48)	0.0024	0.010	0.0069	0.0070	0.0064	0.0098
IMN CH6	0.18	.	.	.	0.18	Rem	0.028	0.40	.	0.50	0.19
IMN CH7	0.40	.	.	.	0.11	Rem	0.11	0.18	.	1.01	0.047
IMN CH8	0.039	.	.	.	0.020	Rem	0.0012	0.036	.	1.49	0.077
IMN CH9	0.010	.	.	.	0.0060	Rem	0.0060	0.010	.	1.97	0.015
IMN CG1	0.011	.	.	.	0.17	Rem	0.013	0.036	.	0.60	0.016
IMN CG2	0.25	.	.	.	0.098	Rem	0.015	0.011	.	0.30	0.026
IMN CG3	0.040	.	.	.	0.045	Rem	0.030	0.39	.	0.22	0.14
IMN CG4	0.10	.	.	.	0.057	Rem	0.25	0.23	.	0.11	0.12
IMN CG5	0.41	.	.	.	0.0079	Rem	0.069	0.10	.	0.053	0.18

CRM GILDING METAL

Number	Cu	Fe	Ni	P	Pb	Sn	Zn	method	Units
SRM 1114	96.4	0.01	0.021	0.009	0.012	0.02	3.4	wrought	31 mm Ø x 19 mm
SRM 1113	95.0	0.04	0.057	0.008	0.026	0.06	4.8	wrought	31 mm Ø x 19 mm
SRM 1112	93.3	0.07	0.10	0.009	0.057	0.12	6.3	wrought	31 mm Ø x 19 mm

CRM GILDING METAL SET

available in SET/5 only

wrought 40 mm Ø x 25 mm

Number	Ag	Al	As	Be	Bi	Cd	Cu	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Te	Zn
IMN MI1	0.0038	0.0400	0.0720	0.000091	0.00063	0.0230	95.69	0.2500	0.0030	0.0059	0.0280	0.0060	0.0430	0.000044	0.0032	0.1500	0.0065	3.57
IMN MI2	0.0090	0.0550	0.0540	0.00085	0.00056	0.0160	93.35	0.1600	0.0081	0.0180	0.0220	0.0160	0.0490	0.0019	0.0120	0.1000	0.0110	6.19
IMN MI3	0.0200	0.0150	0.0340	0.0019	0.0026	0.0110	91.46	0.0860	0.0350	0.0730	0.0150	0.0420	0.0230	.	0.0310	0.0670	0.0031	8.01
IMN MI4	0.0260	0.0079	0.0031	0.0065	0.0026	0.0054	88.35	0.0410	0.0500	0.1400	0.0073	0.0700	0.0120	0.0006	0.0600	0.0130	0.0021	11.13
IMN MI5	0.0330	0.0021	0.0150	0.0072	0.0043	0.0012	94.71	0.0150	0.0690	0.2500	0.0026	0.0960	0.0019	0.0096	0.0820	0.0040	.	4.44

GUN METAL

C, CURM: 50 mm Ø x 10 - 12 mm 33X GM29: wrought 33 mm Ø x 19 mm

other 33X: chill cast ~40 mm Ø x ~15 mm

Number	Zn	Sn	Pb	Ni	Fe	Cu	Ag	Al	As	Bi	Co	Cr	Mn	P	S	Sb	Si
CRM																	
33X GM9A	13.81	2.93	6.91	0.710	0.090	75.1	0.0321	0.0052	0.0251	0.076	0.079	Cd:0.0072	.	0.0547	0.0153	0.184	(0.003)
33X GM4AD	5.90	3.02	5.27	1.482	0.0932	84.02	0.0206	0.0015	0.0228	0.0442	0.0077	.	0.00060	0.0034	0.034	0.0568	0.0010
33X GM8H	5.80	3.89	5.76	0.493	0.142	83.63	0.095	0.0052	0.0110	0.016	0.0151	0.0150	.	0.035	0.028	0.061	(0.003)
33X GM5P	5.66	4.48	5.18	0.728	0.127	83.39	0.0497	0.055	0.0498	0.018	0.0298	Cd:0.0048	Te:0.0075	0.0507	0.0411	0.072	0.0310
33X GM21B	4.96	4.50	7.53	0.197	0.693	78.86	0.701	0.173	0.333	0.459	Se:0.173	Cd:0.249	.	0.0697	0.0628	1.033	0.0213
33X GM20B	1.80	4.49	0.294	0.211	0.44	89.49	0.200	0.133	0.300	0.044	0.0211	Cd:0.020	0.040	0.060	.	2.41	.
33X GM7K	1.363	10.07	1.79	0.531	0.0178	85.69	0.0682	.	0.095	0.098	0.100	.	.	0.0050	0.0613	0.111	Te:0.0112
RM																	
CURM 71.32	6.52	6.46	4.43	0.70	0.35	80.48	0.34	0.12	0.25	0.051	last	0.05	0.046	0.016	0.08	0.26	0.022
CURM 71.31	4.27	4.38	6.44	2.07	0.098	82.30	0.052	0.045	0.11	0.027	last	<0.01	0.010	0.060	0.050	0.11	0.006
33X GM29A	4.23	6.12	0.050	0.0289	0.0102	89.36	0.0026	(0.0004)	0.0017	0.0019	.	(0.0004)	(0.0005)	0.138	0.0024	0.0015	0.0027
33X GM24A	3.67	3.85	3.35	0.0087	0.0083	88.88	0.0046	(0.0001)	0.0010	0.0009	.	(0.0013)	<0.0005	0.190	0.003	0.0012	0.0028
CURM 71.33	3.60	4.96	6.84	0.938	0.018	83.60	<0.002	<0.001	<0.001	<0.002	.	<0.0005	<0.0005	<0.001	<0.001	<0.002	<0.005
C71.34	1.55	8.20	2.47	<0.01	0.29	rem	0.025	0.007	0.18	0.029	last	0.03	0.05	0.020	0.16	0.071	0.04
CURM 71.34	1.54	8.19	2.48	<0.005	0.29	86.74	0.023	0.008	0.18	0.031	.	0.04	0.05	0.019	0.18	0.072	0.03

Number	Zn	Sn	Pb	Ni	Fe	Cu	Ag	Al	As	Bi	Co	Cr	Mn	P	S	Sb	Si
--------	----	----	----	----	----	----	----	----	----	----	----	----	----	---	---	----	----

CRM MANGANESE ALLOY SET

AVAILABLE IN SET/6 ONLY

40 mm Ø x 13 mm

Number	Ag	As	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Zn
IMN CK1	0.012	0.013	0.029	1.06	0.44	0.0011	0.0021	0.0049	0.049	0.13	0.24
IMN CK2	0.0094	0.010	0.11	1.51	0.38	0.0022	0.0062	0.0015	0.091	.	0.14
IMN CK3	0.0066	0.0095	0.17	1.78	0.27	0.0043	0.0098	0.0026	0.033	0.075	0.095
IMN CK4	0.0041	0.0055	0.26	1.91	0.13	0.0056	0.017	0.0041	0.0025	0.042	0.065
IMN CK5	.	0.0015	0.29	2.30	0.011	.	.	0.0051	0.011	0.0048	0.033
IMN CK6	0.0012	0.0039	0.40	2.64	0.073	0.013	.	0.0052	0.21	0.025	0.034

CRM MAGNESIUM ALLOY SET

available in set only 40 mm Ø x 25 mm

Number	Mg
IMN CCB-1	0.00405
IMN CCB-2	0.0339
IMN CCB-3	0.241
IMN CCB-4	0.509
IMN CCB-5	0.748

NICKEL ALLOY, chart 2 of 2

#	Number	Ni	Ag	Al	Bi	Co	Cr	Cu	Fe	Mn	Nb	P	Pb	S	Si	Sn	Zn
1	IARM 84C	9.8	(0.002)	.	.	(0.006)	.	89.4	0.28	(0.04)	.	(0.06)	0.047	(0.006)	(0.004)	0.13	0.13
1	34X 79830A	9.76	0.0028	0.0012	.	(0.0012)	.	45.88	0.079	0.311	.	0.0047	2.033	(0.0005)	.	0.1158	41.80
1	BS 706C	9.7	.	(0.001)	.	(0.003)	(0.0006)	87.9	1.68	0.60	.	(0.007)	0.0033	0.0014	0.0018	(0.0070)	0.084
1	36X SP1A	8.33	0.005	0.0020	0.0039	0.057	.	84.90	0.45	0.084	(0.031)	(0.003)	0.0115	0.005	0.004	5.75	0.344
2	CURM 62.12	7.94	.	.	.	0.081	.	89.42	0.45	1.59	.	.	0.053	0.034	0.109	0.111	0.180
2	CTIF CN2	7.80	.	(0.012)	.	.	.	88.40	1.68	1.19	(0.007)	.	0.055	0.028	0.26	(0.0065)	0.515
1	36X CN21A	5.50	0.0064	1.95	.	0.0079	0.0050	92.17	0.0316	0.0391	.	0.053	0.051	.	.	0.038	0.0203
2	HRT CU2012	2.30	97.0	0.013	0.002	0.63	0.035	.
1	37X 218B	1.892	.	0.0018	.	.	0.176	97.29	0.0209	0.0022	.	.	0.0014	.	0.564	0.0032	0.0054
1	36X CN22A	1.806	0.0196	6.09	.	0.0231	0.0144	91.80	0.088	(0.016)	.	0.0178	0.0260	.	.	0.0371	0.0175

Number	As	B	Be	C	Cd	Mg	Sb	Ti	Zr	Units
IARM 84C	.	.	.	(0.003)	.	.	(0.0012)	.	.	31 mm Ø x 2 or 18 mm
34X 79830A	0.0070	.	.	(0.0052)	.	.	0.0041	.	.	~38 mm Ø x ~15 mm
BS 706C	(0.001)	0.00016	N:(0.005)	(0.004)	.	(0.000003)	(0.0006)	.	(0.0000002)	38 mm Ø x ~7 or 19+ mm 17025
36X SP1A	.	0.0007	0.0177	(0.0004)	.	40 mm Ø x 15 mm
CURM 62.12	0.002	.	.	.	60 mm Ø x 10 mm
CTIF CN2	.	.	.	(0.008)	60 mm Ø x 5 mm
36X CN21A	0.0067	.	.	.	0.0021	40 mm Ø x ~17 mm
HRT CU2012	40 mm Ø x 20 mm
37X 218B	~38 mm Ø x ~15 mm
36X CN22A	0.0208	.	.	.	0.0083	40 mm Ø x ~17 mm

CRM NICKEL ALLOY SETS

available in SETS only, as grouped

analysis listed in mass %

NA: 28 mm Ø x 25 mm

MN5: 35 mm Ø x 30 mm
NB: 40 mm Ø x 25 mmN: 35 mm Ø x 30 mm
NC: 40 mm Ø x 12 mm

Number	Ni	Al	As	Bi	C	Cd	Co	Cu	Fe	Mg	Mn	P	Pb	S	Sb	Si	Sn	Zn
IMN NC1	23.17	.	0.0056	0.0011	0.0320	0.0142	0.0062	.	0.0501	0.0016	0.552	0.0147	0.0025	0.0709	0.0024	0.0854	0.0374	0.776
IMN NC2	24.21	0.0219	0.0104	0.0046	(0.0026)	0.0189	0.0115	.	0.290	0.0024	0.413	.	0.0021	0.0837	0.0049	0.196	0.0457	0.508
IMN NC3	24.68	0.229	0.0167	0.0077	(0.0036)	0.0120	0.0282	.	0.106	0.0561	0.148	0.0312	0.0027	(0.0202)	0.0084	0.0609	0.0171	0.244
IMN NC4	25.39	0.332	0.0251	0.0117	0.0500	0.0049	0.101	.	0.426	0.0170	0.0172	0.0113	0.0120	0.0022	0.0113	0.0197	0.0087	0.0099
IMN NC5	25.82	0.0749	0.0427	0.0213	0.0050	0.0018	0.151	.	0.369	0.0861	0.0623	0.0222	0.0409	.	0.0161	0.0198	0.0044	0.0152
IMN N1	25.38	0.0050	Rem	0.0056	.	0.0018	.	0.0019	.	.	.	0.0070	0.0089	0.019
IMN N2	24.28	0.023	Rem	0.35	.	0.21	.	0.011	.	.	.	0.025	0.012	0.16
IMN N3	22.57	0.055	Rem	0.77	.	0.50	.	0.020	.	.	.	0.062	0.023	0.33
IMN N4	21.39	0.080	Rem	1.07	.	0.71	.	0.039	.	.	.	0.13	0.038	0.47
IMN NA1	7.19	.	.	.	(0.020)	.	Rem	2.52	.	1.51	.	0.081	(0.081)	0.80
IMN NA2	9.05	.	.	.	(0.023)	.	Rem	2.03	.	1.03	.	0.056	(0.065)	0.55
IMN NA3	10.35	.	.	.	(0.019)	.	Rem	1.15	.	0.60	.	0.035	(0.036)	0.30
IMN NA4	12.15	.	.	.	(0.012)	.	Rem	0.50	.	0.21	.	0.0066	(0.0069)	0.019
IMN MN5-1	3.21	.	0.0007	0.00011	.	.	.	Rem	0.0041	.	.	(0.00027)	0.0062	.	0.00019	.	.	.
IMN MN5-2	4.50	.	0.0011	0.00071	.	.	.	Rem	0.033	.	.	0.010	0.012	.	0.00078	.	.	.
IMN MN5-3	5.29	.	0.0017	0.0012	.	.	.	Rem	0.062	.	.	0.016	0.016	.	0.0013	.	.	.
IMN MN5-4	5.90	.	0.0038	0.0018	.	.	.	Rem	0.083	.	.	0.026	0.024	.	0.0019	.	.	.

CRM SEBILOY / ENVIROBRASS / FEDERALLOY

Number	Sn	Zn	Bi	Se	As	Co	Fe	Ni	P	Pb	Sb	Cu
32X SEB4E	10.05	7.02	2.48	0.119	0.0065	0.308	0.093	0.0199	0.0043	0.0357	0.0343	79.82
32X SEB4F	10.05	7.02	2.50	0.119	0.0065	0.32	0.093	0.0199	0.0043	0.0357	0.0343	79.82
32X SEB2D	6.96	1.40	4.57	0.044	0.0160	0.0133	0.074	0.0449	0.036	0.104	0.0222	86.56
IARM 266A	6.9	3.48	2.37	0.001	0.004	(0.001)	0.035	0.46	0.032	0.010	0.010	(87)
32X SEB5C	5.18	5.30	1.056	0.471	.	0.0156	0.0430	0.317	0.072	0.268	0.0334	87.21
IARM 226A	5.1	4.8	1.7	0.93	0.003	0.001	0.054	0.54	0.005	0.040	0.004	86.7
IARM 227A	5.1	4.70	2.3	1.21	0.003	0.001	0.060	0.53	0.003	0.042	<0.01	85.9
IARM 265A	4.4	2.45	2.4	(0.002)	(0.005)	(0.001)	0.013	0.69	0.024	0.011	0.015	(90)
32X SEB1D	4.26	7.81	4.25	0.812	0.0402	0.0478	0.071	0.102	0.0021	0.197	0.305	81.88
IARM 228A	4.1	4.1	1.53	0.67	0.003	0.001	0.052	0.45	0.032	0.026	0.010	89.0
IARM 263A	3.5	15.8	2.55	(0.002)	0.003	0.001	0.047	0.66	0.040	0.022	0.06	(78)
IARM 264A	3.03	5.33	3.6	(0.001)	(0.004)	(0.001)	0.048	0.54	0.027	0.057	0.074	(87.3)
32X SEB3E	2.96	0.887	6.47	1.30	0.0325	0.0491	0.0113	1.214	0.0139	0.296	0.108	86.47

Number	Ag	Al	B	C	Cd	Cr	Mn	N	O	S	Si	Units
32X SEB4E	.	0.0007	.	.	0.0017	~40 mm Ø x ~15 mm
32X SEB4F	.	0.0007	.	.	0.0017	~40 mm Ø x ~15 mm
32X SEB2D	0.0443	.	.	.	0.0255	In: 0.074	.	.	.	0.030	.	~40 mm Ø x ~15 mm
IARM 266A	(0.001)	0.002	.	(0.002)	.	(0.002)	(0.002)	.	.	(0.002)	0.002	31 mm Ø x 2 mm
32X SEB5C	.	(0.001)	.	.	0.0051	0.050	.	~40 mm Ø x ~15 mm
IARM 226A	0.004	0.002	.	0.003	.	(0.001)	0.002	<0.0005	(0.001)	0.005	0.002	31 mm Ø x 2 or 18 mm
IARM 227A	0.004	0.002	.	0.003	.	(0.001)	0.001	(0.00002)	0.0013	0.005	0.002	31 mm Ø x 2 or 18 mm
IARM 265A	(0.002)	0.003	.	.	.	(0.001)	(0.002)	.	.	(0.002)	0.003	31 mm Ø x 2 or 18 mm
32X SEB1D	0.0033	0.0052	.	~40 mm Ø x ~15 mm
IARM 228A	0.003	0.002	.	0.003	.	0.001	0.001	<0.0005	(0.002)	0.004	0.002	31 mm Ø x 2 or 18 mm
IARM 263A	(0.006)	(0.002)	.	<0.005	.	(0.002)	(0.002)	.	.	(0.002)	0.003	31 mm Ø x 2 or 18 mm
IARM 264A	(0.005)	0.003	.	(0.004)	.	(0.002)	(0.002)	.	.	0.0013	0.003	31 mm Ø x 2 or 18 mm
32X SEB3E	0.0095	0.0180	.	~40 mm Ø x ~15 mm

RM SILVER ALLOY

31 mm Ø x 2 or 18 mm

Number	Ag	C	P	S	Zr
IARM 159A	3.48	(0.002)	(<0.01)	(<0.01)	.
IARM 160A	3.03	0.003	(0.004)	(<0.003)	0.40
Al, Co, Cr, Fe, Mn, Ni, Pb, Si, Sn, and Zn: (<0.01)					

CRM SILVER ALLOY SET

available in set only 40 mm Ø x 25 mm

Number	Ag
IMN CCA-1	0.00720
IMN CCA-2	0.0539
IMN CCA-3	0.757
IMN CCA-4	1.524
IMN CCA-5	1.964

RM TIN COPPER

cast typical analysis 32X: 40 mm Ø x 15 mm C: 50 mm Ø x 10-12 mm

Number	Sn	Al	As	Bi	Cu	Fe	Mg	Mn	Ni	P	Pb	S	Sb	Si	Zn
C11.04	9.6	<0.005	<0.005	<0.0005	rem	<0.005	<0.001	<0.005	<0.005	0.05	0.01	<0.001	<0.005	<0.005	<0.005
C11.03	7.4	<0.005	<0.005	<0.0005	rem	<0.005	<0.001	<0.005	<0.005	0.04	0.01	<0.001	<0.005	<0.005	<0.005
C11.02	5.5	<0.005	<0.005	<0.0005	rem	<0.005	<0.001	<0.005	0.006	0.02	0.02	<0.001	<0.005	<0.005	<0.005
C11.01	3.4	<0.005	<0.005	<0.0005	rem	<0.005	<0.001	<0.005	0.006	0.009	0.01	<0.001	<0.005	<0.005	<0.005

CRM TIN COPPER SET

available in SET/5 only 40 mm Ø x 30 mm

Number	Ag	As	Bi	Cu	Fe	Ni	P	Pb	Sb	Sn	Zn
IMN CM1	0.010	0.0098	0.010	Rem	0.019	0.0086	0.0088	0.012	0.012	0.61	0.021
IMN CM2	0.0061	0.0068	0.0072	Rem	0.0064	0.0055	0.0058	0.0067	0.0068	0.84	0.0061
IMN CM3	0.0029	0.0036	0.0033	Rem	0.012	0.0031	0.0041	0.0038	0.0040	1.06	0.0060
IMN CM4	0.0011	0.0011	0.00093	Rem	0.0042	0.0011	0.0009	0.0023	0.0019	1.30	0.0020
IMN CM5	.	(0.015)	0.014	Rem	0.0094	0.014	0.015	0.019	0.018	1.14	0.013

CRM BRASS SETS

wrought available in SETS only, as grouped

MB: 40 mm Ø x 18 mm

ME, MG, WR: 35-40 mm Ø x 25-30 mm

WC: 40 mm Ø x 12 mm

Number	Cu	Zn	Al	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	P	Pb	Sb	Si	Sn
IMN MG1	91.14	Rem	0.040	.	0.00058	.	.	.	0.0081	0.0013	0.048	(0.0019)	0.049	0.00077	.	0.0062
IMN MG2	90.08	Rem	(0.0026)	.	0.00039	.	.	.	0.0067	0.0007	0.0022	0.0012	0.0048	(0.00084)	.	0.018
IMN MG3	93.19	Rem	0.020	.	0.0014	.	.	.	0.062	0.0096	0.013	0.018	0.015	0.0026	.	0.033
IMN MG4	94.00	Rem	.	.	0.0017	.	.	.	0.091	0.024	0.0042	0.012	0.008	0.0045	.	0.023
IMN MG5	95.09	Rem	0.0011	.	0.0026	.	.	.	0.149	0.0036	0.0021	0.0069	0.0054	0.0061	.	0.013
IMN MG6	92.27	Rem	0.0067	.	0.00088	.	.	.	0.028	0.045	0.030	0.0026	0.031	0.0015	.	0.053
IMN WC1	75.10	Rem	0.0034	0.0043	0.0028	.	.	.	0.031	.	.	0.015	0.046	0.0034	0.26	0.0032
IMN WC2	75.05	Rem	0.0016	0.0024	0.0020	.	.	.	0.015	.	.	0.011	0.031	0.0023	0.41	0.0025
IMN WC3	75.28	Rem	0.0018	0.0011	0.00093	.	.	.	0.021	.	.	0.0058	0.0085	0.0010	0.89	0.0011
IMN WC4	75.32	Rem	0.00096	.	0.00047	.	.	.	0.0067	.	.	0.0048	0.0051	0.00080	0.76	0.0010
IMN WC5	75.03	Rem	0.00084	0.0022	0.0019	.	.	.	0.18	.	.	.	0.0055	0.0011	0.48	0.0044
IMN WC6	75.32	Rem	0.0019	0.00097	0.0012	.	.	.	0.051	.	.	0.0037	0.0036	0.00057	0.58	0.0028
IMN ME2	71.29	Rem	this item also available individually				0.87
IMN ME3	70.70	Rem	this item also available individually				1.11
IMN ME4	69.40	Rem	this item also available individually				1.21
IMN ME5	68.53	Rem	this item also available individually				1.42
IMN MB1	60.66	39.39	this item also available individually			
IMN MB2	67.17	32.80	this item also available individually			
IMN MB3	73.26	26.67	this item also available individually			
IMN MB4	78.77	21.20	this item also available individually			
IMN MB5	84.25	15.63	this item also available individually			
IMN MB6	90.07	9.95	this item also available individually			
IMN MB7	95.00	4.99	this item also available individually			
IMN WR1	55.72	Rem	0.496	0.203	0.00109	0.00045	0.00196	0.00049	0.0577	1.051	3.534	0.00122	0.0496	0.00046	1.097	0.605
IMN WR2	56.99	Rem	1.092	0.0129	0.00642	0.00548	0.00210	0.00705	0.802	1.631	2.683	0.0311	0.291	0.00566	0.817	0.453
IMN WR3	58.95	Rem	1.683	0.0492	0.0118	0.00807	0.0106	0.0149	0.184	1.674	1.799	0.0126	0.514	0.0150	0.566	0.254
IMN WR4	60.07	Rem	2.297	0.00528	0.0211	0.0154	0.0154	0.0190	0.600	2.254	0.989	0.0213	0.683	0.0247	0.279	0.100
IMN WR5	61.20	Rem	3.024	0.00129	0.0278	0.0200	0.0196	0.0253	0.141	3.070	0.251	0.0282	0.885	0.0334	0.0485	0.0116

Number	Cu	Zn	Al	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	P	Pb	Sb	Si	Sn
--------	----	----	----	----	----	----	----	----	----	----	----	---	----	----	----	----

RM TRACE ELEMENTS IN BRASS

cast 50 mm Ø x 10 - 12 mm

Number	Cu	Zn	Al	As	Bi	Fe	Mn	Ni	Pb	Sb	Si	Sn
C30.10	93.8	6.1	<0.002	<0.005	<0.002	<0.005	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01
C30.07	82.0	rem	<0.002	<0.005	<0.002	<0.005	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01
C30.06	74.8	rem	<0.005	<0.005	<0.002	<0.005	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01
CURM 30.05	69.48	30.53	<0.001	<0.001	<0.003	<0.003	<0.0005	<0.0005	<0.002	<0.005	<0.001	<0.001
C38.06	(62)	rem	<0.001	<0.005	<0.001	<0.002	<0.002	<0.005	<0.005	<0.002	<0.002	<0.002
C38.06-1	(62)	rem	<0.001	<0.001	<0.0005	<0.005	<0.001	<0.005	0.002	<0.002	<0.002	<0.002
C30.17	61.6	rem	<0.005	<0.005	<0.005	1.4	<0.005	0.01	0.01	<0.005	<0.005	<0.01
C30.16	61.2	rem	<0.002	<0.005	<0.002	0.90	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01
C38.01	(61)	rem	0.003	0.03	<0.0005	0.01	0.009	0.01	0.20	0.02	<0.0005	0.20
C38.02	(61)	rem	0.004	0.06	0.0005	0.09	0.14	0.03	0.10	0.06	0.01	0.09
C38.03	(61)	rem	0.06	0.08	0.008	0.05	0.07	0.13	0.06	0.08	0.07	0.05
C38.04	(61)	rem	0.02	0.04	0.008	0.04	0.22	0.06	0.03	0.12	0.12	0.02
C38.05	(61)	rem	0.12	0.01	0.01	0.008	0.02	0.19	0.02	0.01	0.14	0.01
C30.12	60.85	rem	<0.005	<0.005	<0.002	<0.005	0.90	0.52	<0.01	<0.005	<0.005	<0.01
C30.03	60.6	39.3	<0.002	<0.005	<0.005	<0.005	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01
C30.13	60.6	rem	<0.002	<0.005	<0.002	<0.005	1.9	<0.01	<0.01	<0.005	<0.005	<0.01
C30.15	60.6	rem	<0.002	<0.005	<0.002	0.55	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01
C30.14	60.5	rem	<0.005	<0.005	<0.005	<0.01	2.4	1.0	<0.01	<0.005	<0.005	<0.005
C30.22	58.28	rem	<0.003	0.011	<0.005	0.006	<0.005	<0.01	1.05	<0.012	<0.005	0.009
C30.02	55.6	rem	<0.002	<0.005	<0.005	<0.005	<0.005	<0.005	<0.01	<0.005	<0.005	<0.01
C30.01	51.48	rem	<0.002	<0.005	0.005	<0.005	<0.005	<0.005	<0.01	<0.005	<0.005	<0.01

RM BRASS MUSHROOMS

chill cast

typical analysis

60 mm Ø x 5 mm

Number	Zn	Cu	Al	As	Be	Fe	Ni	Mg	Mn	P	Pb	Sb	Si	Sn
CTIF L 7	42.45	55.6	0.308	.	.	0.031	0.020	.	0.62	.	0.71	.	0.13	0.038
CTIF L 1-1	39.7	59.60	0.015	.	.	0.017	0.106	.	.	0.080	0.062	.	0.36	0.046
CTIF L 2	35.55	61.55	0.485	.	.	0.216	0.71	.	0.350	.	0.408	.	0.202	0.48
CTIF L 3-1	35.50	(58.60)	1.22	0.073	.	0.357	0.993	.	0.214	0.030	1.32	(0.032)	0.025	1.62
CTIF L 4-1	34.55	61.75	0.100	.	.	0.466	0.227	.	0.109	.	2.017	.	0.12	0.693
CTIF L 6	30.26	66.55	0.139	.	.	0.085	1.21	.	0.055	.	0.205	.	1.25	0.250
CTIF L 23	17.90	81.20	.	0.051	.	0.246	0.033	.	.	0.05	0.058	.	0.280	0.20
CTIF UZ 52	16.90	81.18	.	.	0.014	0.32	0.084	0.04	0.002	0.068	0.11	0.08	0.12	1.06
CTIF UZ 53	16.67	82.60	.	0.01	.	0.255	0.025	.	<0.001	0.055	0.025	.	0.145	0.205
CTIF L 21	15.40	82.50	.	0.103	.	0.086	0.156	.	0.004	0.05	0.209	0.10	0.036	1.5
CTIF L 22	15.0	84.3	<0.02	<0.006	.	0.20	0.10	.	<0.01	.	0.10	.	<0.05	1.0
CTIF L 20	13.10	85.55	0.008	0.122	.	0.115	0.205	.	0.043	.	0.27	.	0.035	0.56

BRASS

= class, where 1 = CRM and 2 = RM

CURM: cast 50 mm Ø x 10-12 mm
SRM: wrought 31 mm Ø x 19 mmPB: 45 mm Ø x 25 mm
others: chill cast ~40-43 mm Ø x ~15-18 mm

#	Number	Zn	Cu	Al	As	Bi	Fe	Mn	Ni	Pb	Sb	Si	Sn
1	31X B1Q	44.82	54.99	(0.001)	0.0070	0.0183	0.0223	0.0079	0.0200	0.0155	0.0075	(0.007)	0.0279
1	31X B2N	39.1	60.2	0.161	0.0154	0.0150	0.122	0.0361	0.102	0.053	0.0121	.	0.0129
2	CURM 30.15	38.88	60.66	<0.001	.	.	0.50	<0.001	<0.001	<0.005	.	<0.005	<0.002
2	CURM 30.16	38.33	60.53	<0.001	.	.	1.14	<0.001	<0.001	<0.005	.	<0.005	<0.002
2	CURM 30.11	38.17	59.86	<0.001	.	.	0.002	0.23	1.70	0.005	.	<0.001	<0.002
1	IARM 75C	38.1	60.7	(0.003)	(0.005)	(0.0012)	(0.06)	(0.0024)	(0.013)	0.42	(0.007)	(0.005)	0.69
2	SRM 1107	37.3	61.2	.	.	.	0.037	.	0.098	0.18	.	.	1.04
1	31X TB3L	37.0	62.42	0.044	0.047	0.0085	0.040	0.034	0.031	0.118	0.053	0.020	0.133
1	31X B11H	36.65	60.72	0.0262	0.0061	0.0054	0.802	0.653	1.033	0.0134	0.0057	0.0063	0.0117
1	31X TB5B	35.6	61.49	0.071	0.396	0.292	0.094	0.283	0.106	0.575	0.229	0.111	0.129
1	31X B3N	35.05	64.56	.	0.0104	0.0152	0.0408	0.0290	0.0171	0.085	0.0148	.	0.0394
1	31X B3M	35.01	64.58	0.074	0.0196	0.0149	0.0264	0.0296	0.0259	0.0299	0.0205	.	0.0202
1	31X TB4G	33.64	66.07	0.0041	0.0106	0.0058	0.0340	0.0013	0.0133	0.0246	0.0095	0.0203	0.0197
1	31X B21E	29.55	69.32	0.0244	0.0908	0.104	0.126	0.0603	0.117	0.113	0.105	0.059	0.101
1	31X B5L	23.98	75.38	0.0138	0.0357	0.0088	0.038	(0.002)	0.0275	0.084	0.016	(0.005)	0.266
1	31X B6K	19.93	79.90	0.0010	0.0009	0.0010	0.0097	0.0039	0.0066	0.0122	0.0011	0.015	0.0029
1	31X B7L	15.34	84.22	0.0435	0.0054	0.0607	0.099	0.0088	0.0351	0.0416	0.0196	0.018	0.089
1	SRM 1110	15.2	84.5	.	.	.	0.033	.	0.053	0.033	.	.	0.051
1	SRM 1111	12.8	87.1	.	.	.	0.010	.	0.022	0.013	.	.	0.019
1	31X B8J	10.23	89.37	(0.001)	0.0074	0.030	0.132	0.0006	0.0421	0.082	0.0254	(0.002)	0.0311
1	31X B23D	9.97	89.57	0.0048	0.0482	0.0463	0.060	0.0053	0.047	0.046	0.0448	0.0046	0.060
1	31X B9L	3.83	96.05	(0.0005)	0.0053	0.0068	0.0168	0.0017	0.0129	0.0549	0.0075	0.0036	0.0245
1	31X B24D	1.99	95.65	(0.0024)	0.0116	0.0126	0.0342	0.0030	0.134	0.050	0.118	.	1.93
2	PB MS10	.	84.26	.	0.014	0.37	0.28	0.016	0.025	0.020	(0.009)	0.12	0.052
1	BAM M396	.	65.49	0.223	0.0590	0.00032	0.0235	0.00445	0.0143	.	0.00061	.	.

#	Number	Zn	Cu	Al	As	Bi	Fe	Mn	Ni	Pb	Sb	Si	Sn
	Number	B	C	Cd	Co	Cr	Hg	P	S	Se			
	31X B1Q	0.0007	.	0.0018	0.0015	0.0091	.	0.0385
	31X B2N	0.0029	Ag:0.0118	0.0032	0.042	.	.	0.0191	.	Te:0.0015	.	.	.
	CURM 30.15
	CURM 30.16
	CURM 30.11
	IARM 75C	<0.1	(0.002)	(0.0015)	(0.0007)	0.0009	.	(0.004)	(0.0015)	(0.005)	.	.	.
	SRM 1107
	31X TB3L	0.0014	.	0.0078	0.0043	.	.	Ag:0.011	Te:0.0025
	31X B11H	last	.	.	.
	31X TB5B	Ag:0.216	.	0.49	0.0202	0.0031	.	0.0255
	31X B3N	0.0008	.	0.0027	0.0066	Te: 0.0056	.	0.0366	Ag:0.0152
	31X B3M	0.0022	Ag:0.0247	0.0040	0.0109	.	.	0.0421	Te:0.0098
	31X TB4G	(0.0004)	.	0.0032	0.0067	.	.	.	Te:0.0035
	31X B21E	0.1269	(0.002)	Te:0.0353	.	.	.
	31X B5L	(0.0009)	.	0.0040	0.0250
	31X B6K	0.0023	.	0.0037	0.0063	<0.0005
	31X B7L	0.0013	.	0.0064	0.0044	.	Te:(0.002)
	SRM 1110
	SRM 1111
	31X B8J	.	.	0.0155	0.0072	(0.0005)	.	0.0026	0.045
	31X B23D	.	.	0.0010	0.0472	.	.	0.030	0.053
	31X B9L	(0.0003)	0.0029	.	.	.
	31X B24D	.	.	0.0008	.	.	.	0.0065	0.050
	PB MS10
	BAM M396	.	.	0.00022	0.00012	0.00079	.	0.00089	.	<0.001	38 mm Ø x 30 mm	.	.

Number	B	C	Cd	Co	Cr	Hg	P	S	Se
--------	---	---	----	----	----	----	---	---	----

ALUMINUM BRASS

= class, where 1 = CRM and 2 = RM

#	Number	Al	Zn	Cu	As	Bi	Fe	Mn	Ni	Pb	Sb	Si	Sn	Other	Units
2	CTIF LH1-1	7.99	16.90	64.90	.	.	4.48	5.18	0.0944	0.022	0.081	0.205	(0.007)	P: 0.079	60 mm Ø x 5 mm
2	CTIF LH 2	6.20	21.95	61.98	.	.	2.98	3.65	3.00	0.080	.	0.086	0.055		60 mm Ø x 5 mm
2	CTIF LH 6-1	6.09	18.98	63.18	.	.	(3.1)	4.54	3.19	0.25	.	0.20	0.257		60 mm Ø x 5 mm
1	BAM 388	4.972	4.81	89.27	.	.	0.0303	0.0512	0.00736	0.000969	.	.	0.857		40 mm Ø x 30 mm
2	C30.19	4.65	rem	69.9	<0.005	<0.002	<0.005	<0.005	<0.01	<0.01	<0.01	<0.005	1.07		50 mm Ø x 10-12 mm
1	31X B14G	4.02	36.52	58.85	0.0091	0.0103	0.0183	0.0117	0.0190	0.0104	0.0139	0.051	0.486	Ag:0.0130 Co:0.0109	~40mmØ x ~15mm
2	CTIF LH 5-1	3.65	25.72	66.0	.	.	1.26	1.37	1.57	0.110	.	0.114	0.141		60 mm Ø x 5 mm
2	CURM 30.18	3.28	32.33	63.66	.	.	0.006	<0.001	<0.001	<0.005	.	0.131	0.58		50 mm Ø x 10-12 mm
2	CTIF LH 7	3.16	(26.85)	63.40	.	.	(2.35)	2.96	0.70	0.327	.	0.055	0.227		60 mm Ø x 5 mm
1	31X B15H	2.98	36.80	59.07	0.0048	0.0074	0.0176	0.0122	0.0102	0.0073	0.0111	0.109	0.944	Ag:0.0071 Co:0.0046	~40mmØ x ~15mm
2	C30.18	2.91	rem	64.36	<0.005	<0.003	<0.005	<0.005	<0.005	<0.01	<0.005	0.10	0.65		50 mm Ø x 10-12 mm
2	CURM 43.01	2.75	22.44	74.36	0.118	<0.002	0.008	0.064	0.121	<0.002	<0.001	0.063	0.116		50 mm Ø x 10-12 mm
2	CTIF LH 10	2.66	28.90	59.05	.	.	(1.0)	3.57	1.49	1.76	.	1.30	0.203		60 mm Ø x 5 mm
2	CURM 43.02	2.40	20.82	76.21	0.083	<0.001	0.128	0.035	0.068	0.064	<0.001	0.038	0.060		50 mm Ø x 10-12 mm
2	CURM 30.20	2.32	35.71	61.46	.	.	<0.005	<0.001	<0.001	<0.002	.	0.17	0.40		50 mm Ø x 10-12 mm
2	CTIF LH 13	2.00	31.8	55.75	.	.	(2.00)	3.14	3.22	0.67	.	0.21	1.19		60 mm Ø x 5 mm
1	31X B16H	1.98	37.18	58.37	0.0056	0.0042	0.0162	0.0029	0.0076	0.0295	0.0126	0.197	2.13	Ag:0.0052 Co:0.0023	~40mmØ x ~15mm
2	C43.03	1.6	rem	79.7	<0.005	<0.005	0.07	<0.002	<0.005	0.10	<0.01	<0.005	<0.005		50 mm Ø x 10-12 mm
1	BAM 368 *	1.972	rem	77.049	0.0246	.	0.0193	0.0203	0.0258	0.01313	(0.002)	.	0.0147	P: 0.00899	40 mm Ø x 30 mm
2	C30.21	1.44	rem	56.0	<0.005	.	<0.005	<0.005	<0.005	<0.005	<0.01	1.96	1.96		50 mm Ø x 10-12 mm
2	CURM 30.21	1.44	40.08	56.23	.	.	0.003	<0.001	<0.001	0.004	.	0.213	2.01		50 mm Ø x 10-12 mm
2	CTIF LH 12	1.13	33.15	62.75	.	.	(1.2)	0.125	0.505	0.21	.	(0.06)	0.83		60 mm Ø x 5 mm
2	CTIF LH 11	0.46	26.20	66.80	.	.	0.36	0.71	2.91	1.26	.	0.88	0.44		60 mm Ø x 5 mm

* BAM 368 also contains 62.1 ppm Mg

CRM ALUMINUM BRASS SET

available in SET/4 only

40 mm Ø x 35 mm

Number	Al	As	Bi	Cd	Cr	Cu	Fe	Mg	Mn	Ni	P	Pb	Sb	Si	Sn	Zn
IMN WO1	1.33	0.056	0.0003	0.013	0.013	78.85	0.13	0.00060	0.014	0.0043	0.0023	0.15	0.0083	0.044	0.011	Rem
IMN WO2	1.76	0.041	0.0014	0.032	0.0098	77.80	0.050	0.0066	0.16	0.031	0.0090	0.098	0.00098	0.013	0.056	Rem
IMN WO3	2.15	0.015	0.0047	0.039	0.0027	77.58	0.029	0.0055	0.051	0.11	0.0062	0.054	0.0035	0.007	0.0071	Rem
IMN WO4	2.50	0.030	0.0098	0.0063	0.00034	76.20	0.022	0.013	0.074	0.077	0.015	0.020	0.0058	0.001	0.13	Rem

CRM BISMUTH BRASS

chill cast analysis listed in mass % except * which is mg/kg

~40 mm Ø x ~15 mm

Number	Bi	Zn	Cu	Al	As	B*	Cd*	Co	Fe	Mn	Ni	P	Pb	S*	Sb	Se*	Si	Sn
31X BIB3C	4.04	31.83	63.18	0.154	0.0476	.	14	0.0032	0.0510	.	0.127	0.0626	0.181	18	0.0321	47	0.0516	0.198
31X BIB2E	1.031	35.01	61.12	0.504	0.0224	.	55	0.0437	0.143	.	0.550	0.0232	0.118	<10	0.087	27	0.151	1.267

RM CARTRIDGE BRASS

cast typical analysis listed in mass %

31X: ~40 mm Ø x ~15 mm

others: 50 mm Ø x 10 - 12 mm

Number	Zn	Cu	Al	As	Bi	Cd	Cr	Fe	Mg	Mn	Ni	P	Pb	S	Sb	Si	Sn
CURM 48.01	32.6	66.98	<0.001	0.067	0.038	<0.0003	*	0.049	0.0008	<0.001	0.134	0.016	0.106	<0.001	0.047	0.041	<0.002
CURM 48.02	32.58	67.16	0.013	0.025	0.004	*	0.004	0.053	*	0.067	<0.001	0.012	0.084	0.007	0.037	0.010	0.035
CURM 48.05	31.0	68.69	<0.002	<0.001	*	<0.0003	*	0.066	*	0.016	0.117	0.007	<0.003	0.013	*	0.026	0.083
31X B4N	30.22	69.3	Cr:0.0013	0.059	0.0139	0.032	0.0083	0.043	.	0.032	0.019	0.0083	0.080	(0.002)	0.006	0.030	0.046
C48.03	rem	70.45	0.007	0.079	0.029	0.013	0.0005	<0.001	0.001	0.040	0.030	<0.001	0.054	0.004	0.097	<0.002	0.047
C48.06	rem	71.6	0.002	0.008	0.004	0.008	0.0006	0.02	0.001	0.006	0.11	0.002	0.02	0.006	0.006	0.006	0.03
CURM 48.04	26.99	72.68	<0.001	0.034	0.014	<0.0003	<0.002	0.008	0.0005	0.012	0.096	0.006	0.043	0.011	0.026	0.004	0.018

* For the above chart, * indicates a value of <0.0005

CRM CARTRIDGE BRASS

available in SET/5 or individually remainder is Zinc

wrought 40 mm Ø x 25 mm

Number	Ag	Al	As	Be	Bi	Cd	Cu	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Te
IMN MH1	0.0029	0.0010	0.0670	0.0088	0.0037	0.0260	65.93	0.0170	0.0350	0.2600	0.0160	0.0065	0.0034	0.0004	0.0740	0.1400	0.0004
IMN MH2	0.0110	0.0190	0.0410	0.0015	0.0022	0.0180	68.25	0.0270	0.0110	0.2200	0.0055	0.0210	0.0055	0.0240	0.0540	0.0970	0.0015
IMN MH3	0.0065	0.0081	0.0160	0.0003	0.0011	0.0089	71.28	0.0810	0.0850	0.1000	0.0035	0.0780	0.0090	0.0130	0.0310	0.0240	0.0046
IMN MH4	.	0.0027	0.0011	0.0045	0.0006	0.0029	69.94	0.1300	0.0017	0.0520	0.0022	0.3300	0.0043	0.0170	0.0160	0.0110	0.0035
IMN MH5	0.0250	0.0140	0.0038	0.00004	.	0.0012	72.87	0.1900	0.0720	0.0072	0.0011	0.2000	0.0180	0.0035	0.0039	0.0021	0.0047

CRM CARTRIDGE BRASS SETS 40 mm Ø x ~28 mm

Table with 7 columns: Number, Cd, Cr, Cu, Se, Zn, Zr. Rows include IMN MJ1-MJ5, IMN MJJ1-MJJ4 with various chemical compositions.

available in SETs only, as grouped

CRM FREE CUTTING BRASS SET 40 mm Ø x 25 mm

Table with 14 columns: Number, Al, As, Bi, Cu, Fe, Mn, Ni, P, Pb, Sb, Si, Sn, Zn. Rows include IMN WN1-WN5 with various chemical compositions.

LEADED BRASS

= class, where 1 = CRM and 2 = RM

* Provisional Analysis

Large table with 17 columns: #, Number, Pb, Sn, Zn, Cu, Al, As, Bi, Co, Fe, Mn, Ni, P, Sb, Si. Contains multiple rows of brass alloy compositions.

Table with 13 columns: Number, Ag, B, Be, C, Cd, Cr, Mg, O, S, Se, Te, Units. Rows include IMN BR1, SRM 1124, 31X 7835-8B, CURM H30.24, 31X CZ121A, 33X RB2B, BAM 375, BS 360C, BS 360B, BS 360D, IARM Cu360-18, 31X 7835-7A, 31X 7835-2L, 31X CZ132A, HRT CU2015, 31X CZ122A, BAM M394, BAM M394a, 31X 7835-3K, 31X 7835-5A, 31X 7835-6D, 31X CZ114A, BS 857B-1, BS 857B-2, BS 857B-3, BS 857B-4, 31X CZ115A, 31X 7835-9B, 31X 7835-4K, 31X CZ112A.

CRM NICKEL AND PHOSPHOR BRASS

analysis listed in mass %

Number	Ni	P	Cu	Zn	Al	Cd	Cr	Fe	Mn	Pb	Sn	Units
31X B29A	4.11	3.33	67.08	24.75	0.219	0.0144	0.062	0.144	0.0625	0.146	0.0328	40 mm Ø x ~15 mm
BAM 387	5.020	.	75.18	19.57	.	.	.	0.0617	0.0796	0.00108	0.00301	40 mm Ø x 30 mm

CRM NICKEL BRASS SETS

available in SETS ONLY, as grouped analysis listed in mass % except * which is mg/kg IMN WH, WM: 40 mm Ø x 25 mm IMN WP: 40 mm Ø x 30 mm

Number	Ni	Zn	Cu	Al	As	Bi	C*	Cd	Co	Fe	Mg	Mn	P	Pb	S	Sb	Si	Sn
IMN WP1	5.45	Rem	67.15	0.020	0.0012	0.00080	.	0.0019	.	0.020	.	0.0069	0.020	0.52	.	0.0010	(0.01)	0.0042
IMN WP2	7.79	Rem	65.08	0.0090	0.0049	0.0052	.	0.0052	.	0.12	.	0.040	0.0067	0.82	.	0.0052	(0.009)	0.11
IMN WP3	10.24	Rem	63.05	0.0020	0.011	0.012	.	0.011	.	0.20	.	0.15	0.0079	1.52	.	0.012	(0.03)	0.18
IMN WP4	12.38	Rem	60.91	0.039	0.015	0.016	.	0.016	.	0.31	.	0.35	0.011	(2)	.	0.015	(0.04)	0.26
IMN WP5	15.63	Rem	58.70	0.049	0.021	0.021	.	0.026	.	0.026	.	0.49	0.0027	(1.8)	.	0.028	(0.03)	0.33
IMN WP6	4.27	Rem	69.37	2.41
IMN WM1	5.03	25.35	69.06	0.083	0.00026	0.011	44	0.0046	0.021	0.011	0.0054	0.38	0.0018	0.018	0.017	0.00098	0.0026	0.0036
IMN WM2	6.66	24.18	68.41	0.050	0.0030	0.014	52	0.022	0.017	0.022	0.019	0.53	0.023	0.011	0.0058	0.013	0.0067	0.011
IMN WM3	6.09	23.57	69.85	0.033	0.0053	0.0055	58	0.0024	0.011	0.077	0.0042	0.19	0.0052	0.0073	0.0073	0.0043	0.037	0.098
IMN WM4	5.36	23.19	71.10	0.0080	0.0072	0.0029	72	0.0021	0.0099	0.13	0.0027	0.011	0.0057	0.0044	0.0058	0.0059	0.071	0.075
IMN WM5	4.68	25.90	68.99	0.0012	0.0089	0.0007	90	0.00077	0.0021	0.22	0.00056	0.0024	0.016	0.0020	0.0030	0.0068	0.094	0.035
IMN WH1	5.70	Rem	68.16	.	.	.	(46)	.	0.0061	0.0052	.	0.56	0.0029	.	(0.0055)	.	0.010	.
IMN WH2	6.34	Rem	69.14	.	.	.	(58)	.	0.017	0.038	.	0.36	0.0072	.	(0.0071)	.	0.038	.
IMN WH3	3.44	Rem	70.18	.	.	.	(70)	.	0.031	0.11	.	0.25	0.013	.	(0.011)	.	0.072	.
IMN WH4	4.14	Rem	71.15	.	.	.	(75)	.	0.048	0.13	.	0.11	0.015	.	(0.017)	.	0.12	.
IMN WH5	4.89	Rem	72.28	.	.	.	(87)	.	0.028	0.22	.	0.011	0.017	.	(0.021)	.	0.17	.

SILICON BRASS

= class, where 1 = CRM and 2 = RM

Number	Si	Zn	Cu	Al	Fe	Mn	Ni	P	Pb	Sb	Sn
2 CTIF LS2	4.91	11.60	79.60	0.156	1.022	0.220	1.110	0.064	0.886	0.0103	0.338
1 ERM-EB393a	3.35	(20.8)	75.8	0.00021	0.0143	0.00185	0.00297	0.0454	0.0104	(0.000093)	0.00390
2 CTIF LS3	3.3	19	76	0.43	0.10	0.15	0.11	0.011	0.58	0.107	0.15
1 31X WSB6F	3.13	0.0506	95.40	(0.0013)	0.158	0.924	0.0509	0.0179	0.0310	0.0406	0.0142
1 IARM 313A	3.09	21.3	75.4	(0.001)	0.011	(0.001)	(0.002)	0.09	0.042	0.014	0.006

Number	Ag	As	B	C	Cd	Co	Cr	S	Zr	Units
CTIF LS2	60 mm Ø x 5 mm
ERM-EB393a	.	0.000134	Bi: (0.000019)	.	0.000061	.	0.000156	.	Se: (0.00047)	40 mm Ø x 30 mm
CTIF LS3	60 mm Ø x 5 mm
31X WSB6F	0.0131	0.0110	0.0054	.	0.0039	0.0095	.	.	.	-40 mm Ø x ~15 mm
IARM 313A	0.0017	0.0010	0.0008	(0.002)	(0.0003)	(0.004)	(0.001)	0.0016	(0.0004)	31 mm Ø x 2 mm

CRM HIGH TENSILE BRASS

Number	Cu	Zn	Al	Fe	Mn	Si	As	C	Ni	P	Pb	S	Sb	Sn	Units
31X HT31B	67.00	17.06	6.82	3.01	5.69	0.0443	0.0005	0.0057	0.226	0.0030	0.0139	0.0007	B:0.0014	0.079	~40 mm Ø x ~15 mm
31X HT37A	60.33	34.69	0.0004	0.0344	2.88	1.38	0.0011	0.003	0.0105	0.003	0.623	<0.0005	0.0007	0.0116	40 mm Ø x 18 mm

RM BRONZE MUSHROOMS

chill cast typical analysis 60 mm Ø x 5 mm

Number	Sn	Zn	Cu	Al	As	Fe	Mn	Ni	P	Pb	S	Sb	Si
CTIF B 1	15.15	0.92	82.90	0.072	.	0.088	.	0.063	0.037	0.202	0.030	0.444	0.055
CTIF B 2	13.55	0.11	85.90	(0.002)	.	0.041	.	(0.003)	0.17	0.0206	0.048	(<0.002)	0.17
CTIF B 3	12.8	2.2	80.2	0.1	.	0.2	0.20	1.5	0.45	1.6	0.04	0.2	0.07
CTIF B 4	11.10	1.34	83.75	.	.	0.021	.	0.57	0.52	2.53	0.019	0.10	0.015
CTIF B 14	10.75	0.15	87.00	<0.01	0.04	0.11	0.02	0.30	0.64	0.50	0.02	0.08	0.075
CTIF B 13	10.05	1.09	86.35	0.016	0.065	0.250	0.046	0.50	0.210	0.99	0.070	0.243	0.085
CTIF B 5	9.90	0.42	85.95	0.039	.	0.18	0.082	2.28	0.041	0.48	0.067	0.47	0.049
CTIF B 30	9.80	1.05	77.45	0.063	.	0.115	0.150	0.97	0.063	10.0	0.048	0.22	0.066
CTIF B 12	9.57	0.61	85.65	0.120	0.111	0.162	0.235	2.63	0.525	0.201	0.013	0.117	0.050
CTIF B 11	8.04	2.10	84.75	.	.	0.170	.	2.0	0.057	1.93	0.09	0.70	0.14
CTIF B 31	7.65	0.79	78.65	(0.031)	.	(0.015)	.	0.489	.	11.79	0.028	0.475	(0.047)
CTIF B 23	7.18	1.46	83.45	0.020	.	(0.040)	.	0.086	0.070	7.20	0.019	0.384	0.025
CTIF B 10	6.95	2.75	83.65	0.205	0.0075	0.165	(0.0045)	1.01	0.014	4.07	0.050	1.14	.
CTIF B 20	6.35	3.77	83.35	0.040	.	0.165	.	0.51	0.072	5.10	0.115	0.520	0.055
CTIF B 32	5.92	1.17	74.80	0.075	0.0056	0.11	.	1.49	0.039	16.10	0.027	0.13	0.070
CTIF B 21	5.13	6.17	83.05	0.13	.	0.285	.	1.21	(0.004)	3.79	0.047	0.18	.
CTIF B 22	3.5	4.0	83.0	.	.	<0.10	.	2.5	.	6.0	0.03	0.05	<0.1
CTIF UN 3S	0.215	1.62	92.65	0.11	.	0.30	0.073	3.45	.	0.20	.	.	1.24

Number	Sn	Zn	Cu	Al	As	Fe	Mn	Ni	P	Pb	S	Sb	Si
--------	----	----	----	----	----	----	----	----	---	----	---	----	----

BRONZE

Number	Cu	Fe	Ni	P	Pb	Sn	Zn	method	Units
32X CSN1A	.	0.0020	(0.0001)	0.0007	.	0.306	0.0039	wrought	~20 mm Ø x ~22 mm
SRM 1115	87.9	0.13	0.074	0.005	0.013	0.10	11.7	wrought	31 mm Ø x 19 mm
SRM C1115	87.9	0.13	0.074	0.005	0.013	0.10	11.7	cast	31 mm x 31 mm x 19 mm
SRM 1116	90.3	0.046	0.048	0.008	0.042	0.04	9.4	wrought	31 mm Ø x 19 mm
SRM 1117	93.0	0.014	0.020	0.002	0.069	0.02	6.8	wrought	31 mm Ø x 19 mm
SRM C1117	93.0	0.014	0.020	0.002	0.069	0.02	6.8	cast	31 mm x 31 mm x 19 mm

CRM ALUMINUM BRONZE SETS

available in SETS only, as grouped

analysis listed in mass % except * which is mg/kg

40 mm Ø x ~25-30 mm

Table with 18 columns: Number, Al, As, Bi, Cd, Co, Cr*, Fe, Mg*, Mn, Ni, P, Pb, S, Sb, Si, Sn, Zn. Rows include IMN BF1-BF5, IMN BP1-BP5, IMN BO1-BO5, IMN BJ1-BJ5.

ALUMINUM BRONZE - LOW NICKEL

= class, where 1 = CRM and 2 = RM

Table with 16 columns: #, Number, Al, Cu, As, Cr, Fe, Mg, Mn, Ni, P, Pb, Si, Sn, Zn. Rows include 1 32X ALB9C, 1 IARM Cu955-18, 1 IARM Cu954-18, 1 BS 624, 2 BS 954A, 2 HRT CU2018, 1 VS BR1, 1 VS BR4, 1 32X CA 7A, 2 BS 623, 1 IARM 79C, 1 IARM 79B, 2 BS 623A, 1 VS BR2, 2 CURM 51.14, 2 CURM 51.13, 1 BS 642B, 1 BS 642C, 2 C51.13, 1 32X 61400A, 1 BS 642D, 1 IARMCu642-18, 2 CURM 51.12, 1 32X CA12A, 2 C51.12, 2 CURM 51.11.

Table with 13 columns: Number, Ag, Be, C, Co, N, O, S, Sb, Zr, Units. Rows include 32X ALB9C, IARM Cu955-18, IARM Cu954-18, BS 624, BS 954A, HRT CU2018, VS BR1, VS BR4, 32X CA 7A, BS 623, IARM 79C, IARM 79B, BS 623A, VS BR2, CURM 51.14, CURM 51.13, BS 642B, BS 642C, C51.13, 32X 61400A, BS 642D, IARMCu642-18, CURM 51.12, 32X CA12A, C51.12, CURM 51.11.

Need a larger size? Most BS items are available in any height.

ALUMINUM BRONZE - HIGH NICKEL

= class, where 1 = CRM and 2 = RM

#	Number	Al	Cu	As	Cr	Fe	Mg	Mn	Ni	P	Pb	Si	Sn	Zn
1	32X ALB 10B	12.11	73.64	0.0194	0.0152	3.63	0.0122	1.626	7.21	0.069	0.152	0.158	0.201	0.961
1	IARM 94B	10.8	80.6	<0.01	0.017	3.99	.	0.071	4.31	0.011	0.004	0.028	(0.003)	0.14
2	BS 955C	10.68	80.6	<0.002	.	4.04	.	0.06	4.31	0.012	0.003	0.025	0.003	0.15
1	IARM 204A	10.55	83.3	<0.01	0.008	3.87	.	0.052	1.95	0.007	0.004	0.034	0.005	0.22
1	32X ALB 3S	10.43	80.01	0.0213	0.0392	3.720	0.0659	0.243	3.51	0.0345	0.117	0.155	0.1209	1.313
2	BS 955B	10.30	81.5	(0.002)	.	3.79	.	0.12	4.11	0.017	0.051	0.05	0.024	0.052
2	BS 954C	10.21	83.9	(0.006)	.	3.9	.	0.29	1.38	0.011	0.050	0.07	0.08	0.09
2	BS 954B	10.20	83.9	(0.005)	.	3.90	.	0.27	1.38	0.012	0.047	0.07	0.07	0.10
2	BS 630A	10.05	81.0	(0.002)	.	3.73	.	0.11	4.81	<0.01	0.0069	0.037	0.019	0.17
2	HRT CU2001	10.05	79.09	.	.	4.79	.	0.36	4.94	0.011	0.015	0.08	0.018	0.17
2	C52.51	10.0	Rem	.	<0.01	4.3	<0.01	<0.01	5.1	.	<0.01	<0.01	<0.01	0.02
2	HRT CU2009	9.93	78.88	.	.	3.73	.	0.29	6.22	0.010	0.037	0.19	0.020	0.54
1	IARM 334B	9.91	80.8	(0.003)	(0.004)	3.7	(0.001)	0.60	4.70	0.005	0.006	0.075	0.019	0.122
1	BS 630C	9.90	80.7	0.0007	0.0030	3.82	0.0011	0.325	4.82	0.0043	0.0093	0.064	0.0152	0.234
1	BS 630B	9.78	80.8	0.0007	0.0017	3.90	0.0009	0.281	4.88	0.0028	0.0056	0.0166	0.0289	0.254
1	IARM 334A	9.76	80.7	(0.004)	(0.01)	3.82	(0.001)	0.69	4.77	(0.005)	0.010	0.073	0.025	0.110
1	IARM 80D	9.67	(81.7)	(0.009)	(0.005)	2.99	(0.003)	0.346	5.01	(0.005)	(0.005)	0.025	0.093	(0.007)
1	32X ALB 6K	9.69	80.77	0.0116	(0.1)	2.71	0.0104	0.787	5.42	(0.006)	0.0749	0.073	0.120	0.126
1	VS BR3	9.6	.	.	.	4.00	.	0.227	3.85	(0.003)	0.007	0.071	0.005	0.009
2	BS CC954	9.28	84.0	0.003	.	3.61	.	0.353	1.12	0.013	0.13	0.092	0.061	1.30
2	C52.56	8.9	Rem	.	0.14	4.6	0.09	0.74	5.6	.	0.17	0.15	0.11	0.28
1	32X ALB 12A	8.29	82.90	.	.	1.094	0.0013	0.958	6.33	0.0101	0.0018	0.0202	0.310	0.0625
2	CURM 52.54	7.85	81.59	.	<0.005	3.31	<0.005	1.20	5.40	.	0.086	0.022	0.135	0.39
1	32X ALB 5K	7.21	83.72	.	0.192	2.04	0.179	1.416	3.92	(0.051)	0.0512	0.107	0.0293	0.80
1	32X ALB 13A	7.09	84.96	.	.	1.171	.	5.39	1.381	0.009	(0.0009)	0.086	0.0072	0.0194
1	32X ALB 8E	6.38	77.17	0.145	0.36	5.54	0.015	1.562	6.68	0.171	0.071	0.603	0.312	0.352
1	32X ALB 8F	6.21	77.04	0.189	0.088	5.37	0.194	1.57	6.11	0.261	0.049	0.513	0.435	1.395

#	Number	Al	Cu	As	Cr	Fe	Mg	Mn	Ni	P	Pb	Si	Sn	Zn
---	--------	----	----	----	----	----	----	----	----	---	----	----	----	----

Number	Ag	Be	Bi	C	Co	S	Sb	Se	Units
32X ALB 10B	0.0144	.	.	.	0.0984	.	.	Te:0.0108	~40 mm Ø x ~15 mm
IARM 94B	0.017	.	.	(0.006)	0.011	0.002	(0.011)	.	31 mm Ø x 2 mm
BS 955C	0.014	<0.002	.	38 mm Ø x ~7 or 19+ mm
IARM 204A	0.009	.	.	0.006	0.008	(0.002)	<0.01	.	31 mm Ø x 2 mm
32X ALB 3S	0.0272	.	.	.	0.0760	.	.	Nb:0.018	~40 mm Ø x ~15 mm
BS 955B	(0.009)	0.002	(0.002)	.	38 mm Ø x 12 mm
BS 954C	.	.	.	(0.004)	.	<0.0005	<0.003	.	38 mm Ø x ~7 or 19+ mm
BS 954B	.	.	.	(0.005)	.	<0.0005	(0.001)	.	38 mm Ø x ~7 or 19+ mm
BS 630A	.	.	.	0.005	.	(0.001)	<0.001	.	38 mm Ø x ~7 mm
HRT CU2001	0.003	.	.	40 mm Ø x 20 mm
C52.51	50 mm Ø x 10 - 12 mm
HRT CU2009	40 mm Ø x 20 mm
IARM 334B	0.0013	(0.001)	(0.001)	0.005	(0.003)	0.0008	(0.004)	(0.004)	31 mm Ø x 2 or 18 mm
BS 630C	.	<0.0005	.	0.0060	0.0019	<0.0005	0.0003	.	38 mm Ø x ~7 or 19 mm+
BS 630B	.	<0.0005	.	0.0067	0.0017	0.0013	<0.0005	.	38 mm Ø x ~7 or 19 mm+
IARM 334A	(0.001)	(0.001)	(0.001)	0.0058	(0.003)	0.0007	0.004	.	31 mm Ø x 2 or 18 mm
IARM 80D	(0.04)	<0.002	(0.004)	(0.004)	0.022	(0.003)	<0.02	<0.03	31 mm Ø x 2 or 18 mm
32X ALB 6K	0.0082	.	.	.	0.139	.	.	.	~40 mm Ø x ~15 mm
VS BR3	38 mm Ø x 18 mm
BS CC954	.	.	.	(0.007)	.	(0.002)	0.004	.	32 mm Ø x 17 mm
C52.56	50 mm Ø x 10 - 12 mm
32X ALB 12A	0.044	.	.	.	0.0056	.	.	(0.0007)	~41 mm Ø x ~15 mm
CURM 52.54	50 mm Ø x 10 - 12 mm
32X ALB 5K	0.0061	.	.	0.0606	.	Nb:0.181	.	Te:0.047	~40 mm Ø x ~15 mm
32X ALB 13A	0.0011	.	.	(0.0007)	~35 mm Ø x ~15 mm
32X ALB 8E	0.0099	.	.	.	0.554	.	0.024	.	~40 mm Ø x ~15 mm
32X ALB 8F	0.0100	.	.	0.0204	0.425	.	0.0250	.	~40 mm Ø x ~15 mm Nb:(0.002) Te:(0.003)

Number	Ag	Be	Bi	C	Co	S	Sb	Se	Units
--------	----	----	----	---	----	---	----	----	-------

Need a larger size?
Most BS items are available in any height.

RM ALUMINUM BRONZE MUSHROOMS

chill cast		typical analysis											60 mm Ø x 5 mm	
Number	Al	Cu	Fe	Mn	Ni	Pb	Si	Sn	Zn	Bi	Cd	Cr	Mg	
CTIF CA 36	12.60	77.25	2.93	0.131	6.33	0.0154	0.113	0.201	0.244	0.058	.	0.041	0.130	
CTIF 2158-W	11.95	85.00	2.53	0.26	0.10	<0.005	0.015	<0.01	<0.01	
CTIF 4065-P	11.85	81.20	3.40	0.075	3.18	0.03	0.034	0.18	0.03	
CTIF CA 35	11.4	75.6	6.1	1.6	3.80	0.10	0.25	0.30	0.55	
CTIF 2154-V	11.25	85.00	3.05	0.12	0.41	<0.005	0.015	<0.01	<0.01	
CTIF CA 13	11.20	82.45	3.82	1.22	0.50	0.0230	0.11	(0.01)	0.65	
CTIF CA 3	10.9	86.5	0.80	0.06	0.80	0.15	0.08	0.20	0.30	
CTIF CA 21	10.82	81.9	3.45	0.30	3.09	0.05	0.07	0.07	0.100	.	0.0095	.	.	
CTIF CA11	10.54	84.45	1.27	0.779	1.95	0.109	0.254	0.258	0.211	.	.	.	0.125	
CTIF CA 22	10.45	80.50	2.51	0.745	4.54	0.0243	0.32	0.30	0.605	
CTIF 3011-G	10.35	84.80	1.98	0.165	2.00	0.10	0.16	0.125	0.25	
CTIF CA 27	10.25	81.1	2.81	1.195	3.88	0.11	0.127	0.054	0.428	.	0.012	.	.	
CTIF CA 10	10.15	80.65	4.55	0.333	3.39	0.16	0.46	0.16	0.067	
CTIF 3299-J	10.10	87.60	0.38	1.12	0.21	0.110	0.136	0.106	0.19	
CTIF 3297-Y	10.00	87.45	1.88	0.03	.	0.11	0.15	0.10	0.27	
CTIF CA37	9.84	76.79	6.85	0.752	4.98	0.0503	0.040	0.147	0.364	0.0118	.	0.085	0.077	
CTIF 4149-G	9.84	84.95	2.00	0.21	1.96	0.15	0.18	0.34	0.37	
CTIF 2152-S	9.78	85.05	3.99	0.42	0.68	<0.005	0.015	.	<0.01	
CTIF 2151-R	9.43	84.75	4.48	0.73	0.56	<0.005	0.015	<0.01	<0.01	
CTIF 3296-L	9.40	88.55	0.07	0.37	0.41	0.30	0.20	0.06	0.62	
CTIF CA 31	9.15	76.5	3.18	3.27	7.51	0.020	0.064	0.063	0.145	.	.	.	0.02	
CTIF CA 26	9.10	81.25	4.36	0.188	4.87	0.058	0.035	0.005	0.038	.	0.034	.	.	
CTIF 3300-M	8.73	89.5	0.45	0.165	0.205	0.205	0.415	0.205	0.085	
CTIF 3301-Z	8.10	87.30	4.00	0.26	0.125	0.032	0.057	0.028	0.06	
CTIF 2794-H	8.0	90.3	0.82	<0.01	0.69	<0.01	0.048	0.105	<0.01	
CTIF CA 20	8.00	87.15	0.79	1.85	1.18	0.18	0.17	0.19	0.41	.	0.05	.	.	
CTIF CA 12	8.0	84.1	2.77	3.09	1.385	0.047	0.058	0.036	0.45	
CTIF CA 25	7.97	79.12	6.10	0.51	5.74	0.03	0.084	0.177	0.252	
CTIF CA 30	7.55	81.6	5.2	2.05	3.10	0.142	0.15	0.099	0.066	
CTIF 3018-F	7.25	81.90	4.45	1.57	4.50	0.02	0.085	0.06	0.06	
CTIF 3610-Q	7.10	82.32	3.98	0.045	5.40	0.23	0.065	0.25	0.51	.	0.090	.	.	
Number	Al	Cu	Fe	Mn	Ni	Pb	Si	Sn	Zn	Bi	Cd	Cr	Mg	

CRM BISMUTH BRONZE

Number	Bi	Cu	Ni	P	Pb	Sn	Zn	Al	Fe	O	S	Sb	Se	Units
IARM CuMB1-18	4.51	88.98	0.58	0.049	0.015	5.58	0.47	(0.0012)	(0.0016)	(0.003)	(0.0020)	(0.003)	(0.0025)	31 mm Ø x 2 mm or 18 mm

MANGANESE BRONZE

# = class, 1=CRM and 2=RM		BS 675B, 863B, 675A: 38 Ø x ~7 to 19+ mm										BS 675: 38 Ø x 12 mm		IARM: 31 Ø x 2 or 18 mm			
#	Number	Mn	Al	Fe	Sn	Zn	Cu	As	C	Co	Cr	Ni	P	Pb	S	Sb	Si
1	BS 863B	2.97	5.25	2.84	0.033	26.1	[62.4]	0.0004	0.0028	0.0009	0.0042	0.081	0.0010	0.0205	0.0007	0.0012	0.0103
1	IARM 88C	2.99	5.79	2.98	0.147	22.86	64.5	(0.007)	0.005	0.0010	0.008	0.276	0.020	0.133	0.0010	(0.003)	0.091
2	BS 675A	0.32	<0.002	1.12	0.8	39.1	58.5	0.003	(0.0007)	.	.	0.019	0.010	0.074	(0.0005)	0.0011	(0.005)
1	BS 675B	0.175	(<0.005)	1.10	0.92	39.3	58.7	0.0009	(<0.001)	(0.0002)	(0.0002)	0.0071	0.0020	0.071	0.0002	0.0011	(<0.005)
1	IARM 83B	0.13	0.002	0.97	0.85	39.3	58.7	.	0.003	.	.	0.010	0.004	0.017	(0.001)	(0.004)	(0.003)
2	BS 675	0.11	<0.01	0.73	0.92	39.7	Rem.	<0.005	(0.0004)	.	last	<0.01	<0.01	<0.01	(0.0013)	<0.01	<0.02

BS 675B and 863B are 17025

CRM NICKEL BRONZE SET

available in SET/5 only		analysis listed in mass %											40 mm Ø x ~30 mm	
Number	Al	Bi	Cu	Fe	Ni	P	Pb	S	Sb	Se	Si	Sn	Zn	
IMN BN5	0.0245	0.0298	rem	0.00731	2.69	0.0634	0.00612	0.0018	0.0314	0.00636	(0.00211)	11.82	0.0560	
IMN BN1	0.00286	0.118	rem	0.495	0.226	0.123	0.0239	0.113	0.117	0.00335	(0.00839)	6.47	0.135	
IMN BN2	0.00371	0.0707	rem	0.589	1.64	0.0769	0.00514	0.213	0.0656	0.0104	.	6.21	0.369	
IMN BN3	0.00126	0.00098	rem	0.153	1.04	0.00038	0.0054	(0.0017)	0.0088	.	.	9.29	0.0625	
IMN BN4	0.00055	0.00595	rem	0.0216	0.635	0.0066	0.0145	0.112	0.0055	0.0134	(0.00064)	9.81	0.00771	

PHOSPHOR BRONZE

= class, where 1 = CRM and 2 = RM

* Provisional Analysis

#	Number	P	Sn	Zn	Cu	Mn	Ni	Pb	Al	As	Fe	Mg	S	Sb	Si
1	32X PB11H	0.89	3.07	1.53	91.3	0.0404	0.70	1.07	0.070	0.187	0.377	0.015	0.011	0.446	0.084
1	BS 510C	0.335	5.43	0.13	94.1	<0.001	0.015	0.0051	(0.0009)	<0.005	0.0042	.	0.0019	<0.01	0.0028
1	32X 51000A	0.300	4.85	0.0105	94.87	.	0.0084	0.0032	0.0007	.	0.0024	.	0.0021	.	.
1	33X 54400A	0.243	3.97	3.87	86.79	.	0.244	4.69	0.0009	0.0156	0.072	.	0.0251	0.0362	.
1	32X PB20A	0.196	4.55	0.007	95.22	<0.005	0.0090	0.0045	<0.005	0.0011	0.0013	.	0.0030	0.0012	0.0046
1	IARM 78B	0.19	4.73	3.55	87.7	(0.002)	0.077	3.87	(0.002)	<0.003	0.02	.	0.010	0.01	<0.002
1	IARM Cu510-18 (0.16)	4.54	0.0034	95.2	(0.0010)	(0.017)	(0.0027)	(0.0004)	(0.0007)	(0.0008)	.	.	(0.0020)	(0.0008)	(0.0050)
1	IARM 77B	0.148	4.66	0.007	95.2	(0.002)	0.002	0.016	(0.001)	(0.001)	0.002	.	0.002	0.005	(0.003)
1	32X 52100A	0.146	7.73	0.0026	92.10	.	0.0111	0.0031	0.0009	0.0009	0.0008	.	0.0008	.	.
1	32X PB14E	0.128	9.65	0.103	89.70	0.0141	0.103	0.0354	0.0201	0.0235	0.0211	.	0.070	0.0433	(0.003)
1	32X PB13F	0.128	6.34	0.374	92.64	0.0216	0.099	0.075	0.0034	0.0309	0.057	.	.	0.1091	0.0107
2	BS 510A	0.11	4.6	0.21	95.10	<0.002	0.020	0.016	<0.002	0.0008	0.005	.	0.008	(0.003)	<0.003
2	CURM 54.02	0.107	5.53	0.410	92.87	0.101	0.109	0.663	0.020	0.023	0.102	0.0020	0.030	0.026	0.012
1	32X PB13E	0.089	6.55	0.301	92.48	0.0440	0.0953	0.109	0.0251	0.0391	0.0549	.	.	0.092	0.053
1	32X PB15A	0.0873	2.21	0.76	96.07	0.125	0.212	0.174	0.045	0.123	0.116	0.0275	.	0.026	0.043
1	BS 510B	0.074	4.6	0.251	[95.0]	0.0004	0.0211	0.0112	(0.006)	0.0010	0.009	.	0.007	(0.002)	(0.003)
1	IARM Cu544-18	0.069	4.14	3.80	88.0	.	0.019	3.92	.	.	(0.010)
2	CURM 54.01	0.053	3.17	0.346	95.42	0.158	0.348	0.307	0.040	0.044	0.028	0.008	0.023	0.070	0.039
2	HRT CU2016	0.050	7.23	0.006	92.67	.	0.007	0.006	.	.	0.004	.	0.003	0.006	.
2	C54.01	0.05	3.2	0.31	Rem	0.13	0.26	0.29	0.009	0.04	0.01	<0.001	0.03	0.08	0.006
1	BS 544B	0.0258	4.06	3.51	88.2	(0.0009)	0.068	3.9	(0.0009)	0.0043	0.087	.	0.0249	0.0244	0.0042
1	BS 544C	0.0092	4.10	3.78	88.4	<0.005	0.153	3.31	<0.05	(0.008)	0.055	.	0.058	0.0045	0.0029
1	32X PB16A	0.0073	17.60	0.0082	82.02	.	0.127	0.088	(0.0006)	0.0035	(0.001)	.	0.0049	0.013	0.005

Number	Ag	Bi	C	Co	Cr	N	O	Se	Units
32X PB11H	B: 0.0021	0.023	.	0.034	~40 mm Ø x ~15 mm
BS 510C	(0.004)	.	(0.0010)	0.0008	<0.005	.	0.0006	.	38 mm Ø x ~7 or 19+ mm 17025
32X 51000A	0.0022	38 mm Ø x ~15 mm
33X 54400A	0.0124	.	.	0.0013	~38 mm Ø x ~15 mm
32X PB20A	38 mm Ø x 17 mm
IARM 78B	31 mm Ø x 2 or 18 mm
IARM Cu510-18	0.0019	.	(0.0018)	.	.	.	0.0011	.	31 mm Ø x 2 or 18 mm
IARM 77B	.	.	0.003	31 mm Ø x 2 or 18 mm
32X 52100A	0.0011	0.0019	38 mm Ø x ~15 mm
32X PB14E	0.0152	0.146	.	0.0047	~40 mm Ø x ~15 mm
32X PB13F	0.0196	0.0309	.	0.0091	.	.	Te: 0.0298	.	~40 mm Ø x ~15 mm
BS 510A	.	.	(0.0006)	38 mm Ø x 12 mm last
CURM 54.02	50 mm Ø x 10-12 mm
32X PB13E	0.0205	0.0224	.	0.0088	~40 mm Ø x ~15 mm
32X PB15A	.	.	.	0.0509	40 mm Ø x ~15 mm
BS 510B	Zr: (0.0004)	0.0010	(0.0006)	(0.0008)	(0.0001)	0.0009	.	.	38 mm Ø x ~7 or 19+ mm 17025
IARM Cu544-18	38 mm Ø x ~3 or 19 mm
CURM 54.01	50 mm Ø x 10-12 mm
HRT CU2016	40 mm Ø x 20 mm
C54.01	50 mm Ø x 10-12 mm
BS 544B	0.0173	.	0.0031	(0.0012)	(0.0007)	(0.0007)	0.0005	.	38 mm Ø x ~7 or 19+ mm 17025
BS 544C	<0.005	.	0.0018	(0.0020)	<0.005	.	0.0006	.	38 mm Ø x ~7 or 19+ mm 17025
32X PB16A	0.0166	0.0530	.	(0.0004)	.	.	.	Te: (0.002)	~40 mm Ø x ~15 mm

**Need a larger size?
Most BS items are
available in any height.**

SILICON BRONZE

= class, where 1 = CRM and 2 = RM

#	Number	Si	Cu	Mn	Al	As	C	Cr	Fe	Ni	P	Pb	Sn	Zn
1	BS 655B	3.25	95.7	0.928	<(0.005)	0.0004	0.0012	0.0006	0.042	0.0043	0.0047	0.0205	0.0053	0.0248
1	BS 655C	3.22	95.6	0.958	<(0.005)	0.0006	<(0.005)	0.0021	0.052	0.0030	0.0035	0.0047	0.0049	0.0152
1	IARM 82B	3.22	95.3	1.04	0.002	<0.002	(0.003)	0.004	0.080	0.011	0.004	0.011	0.017	0.38
1	37X 65500A	3.13	95.75	0.960	0.0028	.	(0.0044)	0.0029	0.035	0.0059	0.0046	0.0034	0.0426	0.0353
1	IARM Cu655-18	3.15	95.5	0.98	(0.0020)	(0.0004)	(0.0100)	.	0.055	0.0034	(0.0020)	(0.018)	0.009	0.149
2	BS 655A	3.14	95.74	0.91	(0.002)	<0.002	(0.0006)	.	0.075	0.008	(0.004)	0.008	0.07	0.02
1	IARM Cu647-18	0.70	(96.5)	(0.099)	0.0027	.	.	.	(0.0056)	2.69	(0.02)	(0.007)	(0.01)	(0.005)

Number	Be	Co	Mg	N	O	S	Sb	Zr	Units
BS 655B	<(0.0005)	<(0.005)	<(0.0005)	<(0.0005)	<(0.0005)	0.0010	0.0002	<(0.0005)	38 mm Ø x ~7 or 19 mm 17025
BS 655C	<(0.0005)	<(0.005)	<(0.0005)	<(0.0005)	<(0.001)	0.0007	<(0.0005)	.	38 mm Ø x ~7, ~12 or 19 mm 17025
IARM 82B	.	.	.	<0.0005	(0.001)	0.003	<0.01	.	31 mm Ø x 2 or 18 mm
37X 65500A	0.0014	0.0010	.	.	~38 mm Ø x ~15 mm
IARM Cu655-18	.	Ag: (0.0015)	.	.	.	(0.0010)	(0.0008)	.	31 mm Ø x 2 or 18 mm
BS 655A	(0.0006)	<0.002	.	38 mm Ø x 12 mm
IARM Cu647-18	.	.	(0.0086)	0.044	31 mm Ø x 2 or 18 mm

CRM SILICON BRONZE SET BH1 BH3 and BH6 set only, others ok individual 40 mm Ø x 25 mm

Number	Al	As	Bi	Cu	Fe	Mg	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn
IMN BH1	0.027	0.0047	0.018	Rem	1.67	0.0065	0.25	0.96	0.0047	0.74	0.012	0.066	4.77	0.044	2.03
IMN BH2	0.079	0.015	0.014	Rem	1.28	0.0066	0.54	0.74	0.023	0.57	0.0092	0.042	4.14	0.21	2.99
IMN BH3	0.14	0.022	0.0091	Rem	0.96	0.0075	1.00	0.53	0.039	0.40	0.0062	0.026	3.07	0.37	3.84
IMN BH4	0.22	0.054	0.006	Rem	0.55	0.0057	1.46	0.28	0.059	0.24	0.0064	0.016	2.29	0.55	4.91
IMN BH5	0.29	0.071	0.0019	Rem	0.093	0.0024	1.80	0.047	0.073	0.015	0.0055	0.0054	1.45	0.69	5.58
IMN BH6	0.32	0.078	0.018	Rem	0.35	0.01	0.80	0.39	0.078	0.017	0.016	0.056	1.51	0.32	6.27

LEADED, TIN, AND LEADED TIN BRONZE CHART 1 of 2

= class, where 1 = CRM and 2 = RM

#	Number	Sn	Pb	Zn	Cu	Al	Fe	Mn	Ni	P	S	Sb	Si
2	CTIF B1	15.15	0.202	0.92	82.90	0.072	0.088	.	0.063	0.037	0.030	0.444	0.055
1	32X SN7B	12.4	2.31	1.14	81.21	0.0254	0.036	.	0.276	0.0051	0.027	0.235	.
2	CURM 50.04	11.30	9.94	0.66	76.11	0.014	0.10	0.028	1.10	0.032	0.14	0.50	0.011
2	HRT CU2000	11.03	0.78	0.42	86.4	(0.001)	0.04	(0.01)	1.28	0.009	0.014	.	(0.01)
1	IARM 310A	10.56	0.064	0.10	89.2	0.0009	0.006	(0.001)	0.043	0.094	0.0021	(0.002)	(0.001)
2	CURM 50.02	10.34	10.67	0.006	78.84	0.046	.	.	.
1	32X 52480A	10.33	0.329	0.397	88.54	.	0.020	.	0.369	0.0103	0.0071	0.0182	(0.002)
2	BS 905A-2	10.3	0.032	2.3	[87.3]	(<0.005)	0.014	(<0.005)	0.018	0.056	(0.004)	0.004	(<0.005)
2	BS 905A-3	10.3	0.033	2.3	[87.3]	(<0.005)	0.013	(<0.005)	0.018	0.052	(0.004)	0.004	(<0.005)
2	BS 905A-4	10.3	0.033	2.2	[87.3]	(<0.005)	0.012	(<0.005)	0.018	0.049	(0.004)	0.004	(<0.005)
2	BS 905A-1	10.25	0.030	2.27	87.3	(<0.003)	0.015	(<0.003)	0.018	0.055	.	0.004	(<0.004)
1	32X LB11E	10.19	10.21	0.039	78.7	(0.0004)	0.0034	.	0.498	0.0050	0.029	0.068	0.0093
1	BS 937C	9.99	9.15	0.196	80.0	(0.0008)	0.0033	(0.0007)	0.26	0.0009	0.025	0.55	(0.002)
1	32X 93700A	9.95	8.38	0.78	80.43	.	0.0011	.	0.307	(0.0015)	0.0017	0.0051	.
1	IARM 92C	9.65	9.42	0.146	80.35	0.0013	(0.008)	(0.0016)	0.170	0.073	0.026	0.078	(0.0019)
1	32X LB12E	9.63	8.64	0.459	79.76	0.0337	0.029	.	0.354	0.240	0.053	0.484	0.0099
2	HRT CU2017	9.24	8.91	0.37	80.11	.	0.011	.	1.25	0.007	0.026	0.14	.
1	IARM 89C	9.14	0.17	3.0	87.5	(0.002)	0.004	(0.001)	0.008	0.004	0.0011	0.008	(0.003)
1	BS 929	9.07	1.98	0.0055	85.3	(<0.00005)	0.0030	(<0.00005)	3.37	0.119	0.0026	0.0146	(<0.001)
2	CURM 50.01	9.01	11.13	0.91	75.38	<0.0005	0.074	<0.001	1.93	0.069	0.188	0.50	<0.001

#	Number	Sn	Pb	Zn	Cu	Al	Fe	Mn	Ni	P	S	Sb	Si
	Number	Ag	As	Bi	C	Cd	Co	Cr	Mg	Se	Te	Units	
	CTIF B1	60 mm Ø x 5 mm	
	32X SN7B	0.328	1.13	0.198	.	0.020	0.339	.	.	0.066	0.0204	~40 mm Ø x ~15 mm	
	CURM 50.04	.	0.06	0.10	50 mm Ø x 10-12 mm	
	HRT CU2000	40 mm Ø x 20 mm	
	IARM 310A	0.0020	(0.002)	(0.001)	(0.005)	(0.001)	0.0011	(0.001)	.	(0.001)	.	31 mm Ø x 2 or 18 mm	
	CURM 50.02	50 mm Ø x 10-12 mm	
	32X 52480A	0.0131	.	0.0013	~40 mm Ø x ~15 mm	
	BS 905A-2	0.002	0.002	.	(0.002)	38 mm Ø x 12 mm	
	BS 905A-3	(0.002)	0.002	.	(0.001)	38 mm Ø x 12 mm	
	BS 905A-4	(0.002)	0.002	.	(0.002)	38 mm Ø x 12 mm	
	BS 905A-1	(0.002)	(0.001)	38 mm Ø x 12 mm	
	32X LB11E	0.061	0.0408	0.051	.	.	0.009	.	.	.	0.0147	~40 mm Ø x ~15 mm	
	BS 937C	(0.015)	0.0112	(0.018)	(0.0015)	(0.0002)	0.0006	(0.00004)	0:0.0060	(0.0008)	(0.0005)	38 mm Ø x 19+ mm 17025	
	32X 93700A	0.0004	~42 mm Ø x ~15 mm	
	IARM 92C	(0.05)	(0.005)	(0.011)	(0.002)	.	(0.0007)	(0.0007)	.	(0.001)	.	31 mm Ø x 2 or 18 mm	
	32X LB12E	0.0450	0.112	0.0338	.	.	0.061	.	.	.	0.0215	~40 mm Ø x ~15 mm	
	HRT CU2017	40 mm Ø x 20 mm	
	IARM 89C	0.005	0.004	(0.003)	(0.002)	(0.001)	(0.001)	(0.002)	0:0.006	(0.001)	(0.0004)	31 mm Ø x 2 or 18 mm	
	BS 929	(<0.005)	0.0017	(<0.005)	(<0.005)	.	0.0031	(<0.005)	.	0:0.0031	.	51 mm Ø x ~7 or 19+ mm 17025	
	CURM 50.01	0.19	.	0.024	50 mm Ø x 10 - 12 mm	

Number	Ag	As	Bi	C	Cd	Co	Cr	Mg	Se	Te	Units
--------	----	----	----	---	----	----	----	----	----	----	-------

LEADED, TIN, AND LEADED TIN BRONZE CHART 2 of 2

= class, where 1 = CRM and 2 = RM

#	Number	Sn	Pb	Zn	Cu	Al	Fe	Mn	Ni	P	S	Sb	Si
1	BS 903E	8.63	0.100	4.11	87.0	(0.001)	0.0072	.	0.293	0.056	0.0092	0.010	(0.0018)
1	BS 903D	8.55	0.101	4.14	86.7	(0.0001)	0.0058	.	0.284	0.059	0.0090	0.0121	(0.0003)
2	CURM 50.03	8.41	8.86	1.72	77.42	0.005	0.018	0.037	2.89	0.159	0.064	0.24	0.005
1	IARM Cu903-18	8.3	(0.066)	4.6	86.5	(0.0010)	(0.012)	(0.0004)	0.41	(0.060)	(0.0017)	(0.002)	(0.0040)
1	32X LB10G	8.29	12.60	0.110	77.10	(0.0005)	0.0011	.	0.690	0.0034	0.0100	0.599	.
2	BS 903B	7.9	0.10	4.39	86.7	(0.001)	0.049	0.0004	0.50	0.073	0.006	0.003	0.002
1	BAM 374	7.60	0.00083	0.00404	92.22	.	0.0040	0.00043	0.00327	0.1697	(0.0013)	(0.00063)	(<0.0010)
2	BS 938-1	7.16	14.8	0.26	77.1	(<0.002)	(0.015)	(0.001)	0.49	(0.059)	0.009	0.033	(<0.004)
1	BS 936	6.99	10.7	0.244	81.5	0.0007	0.0026	(0.0006)	0.36	(0.053)	0.009	0.102	0.0040
1	IARM Cu932-18	6.82	7.95	3.44	82.2	(0.0007)	0.070	.	0.454	0.040	0.031	0.31	.
1	32X SN6B	6.78	1.644	2.00	85.73	0.059	0.376	0.090	0.295	.	.	0.304	.
1	IARM 91E	6.69	7.59	3.68	81.3	0.0015	0.110	0.0007	0.300	0.026	0.028	0.168	0.0021
1	BS 932G	6.35	7.78	2.92	82.0	(0.002)	0.028	(0.0005)	0.39	0.11	0.035	0.173	0.0014
1	BS 932F	6.30	7.32	3.39	[82.1]	(0.0008)	0.057	(0.0002)	0.388	0.0105	0.0368	0.199	0.0011
1	BS 932H	6.28	7.62	2.79	82.4	(0.0020)	0.019	(0.0005)	0.41	(0.11)	0.038	0.185	(0.002)
1	IARM 184A	6.0	19.0	0.37	(74)	0.0016	(0.003)	(0.002)	0.30	0.008	0.021	0.27	(0.002)
1	32X LB13D	5.98	7.04	0.77	85.1	0.0014	0.0159	.	0.629	0.033	0.074	0.092	0.008
1	BAM 377	5.92	0.000449	0.01006	94.04	0.00451	0.01042	0.000921	0.01074	(<0.0010)	(0.00068)	0.00130	(0.0134)
2	BS 922B-1	5.8	1.33	3.95	88.4	(0.001)	0.010	(0.002)	0.61	0.037	.	0.002	(0.001)
2	BS 922B-2	5.8	1.33	3.91	88.4	(0.001)	0.008	(0.002)	0.61	0.031	.	0.002	(0.001)
2	BS 922B-4	5.8	1.33	3.82	88.4	(0.001)	0.007	(0.002)	0.61	0.021	.	0.002	(0.001)
2	BS 922B-5	5.8	1.33	3.78	88.4	(0.001)	0.006	(0.002)	0.61	0.017	.	0.002	(0.001)
1	BAM 378	5.738	(0.00042)	(0.00073)	94.13	(<0.0001)	0.0182	(0.000074)	0.00183	0.0602	(0.00091)	0.00861	(<0.0010)
1	32X LB16A	5.55	18.78	0.450	74.42	(0.0012)	0.0040	.	0.793	(0.0018)	0.0011	(0.0012)	.
1	32X LB14H	5.16	15.04	0.254	78.4	0.0008	0.041	.	0.300	0.039	0.036	0.103	0.0012
1	IARM 267A	4.95	0.026	2.06	87.8	0.003	0.019	(0.002)	5.1	0.037	0.0014	<0.03	0.003
1	BS 836D	4.82	4.9	4.84	84.8	0.0011	0.026	(0.0002)	0.370	0.086	0.039	0.108	0.0027
1	BS 836B	4.71	4.6	4.85	85.2	0.0015	0.022	(0.0007)	0.377	0.096	0.036	0.102	(0.0032)
1	BS 836C	4.7	4.72	4.91	85.0	(0.0015)	0.017	(0.0007)	0.370	0.066	0.038	0.104	0.0032
1	32X LB15F	4.53	20.15	0.147	74.5	0.0009	0.0039	.	0.104	0.063	0.021	0.198	0.0018
1	BAM M397	3.99	0.229	1.96	0.336	.	0.45	0.097	.
1	BAM M397a	3.9	0.227	1.87	0.337	.	0.45	0.097	.
1	IARM 72B	0.029	1.99	7.81	90.08	.	0.007	.	0.004	0.005	0.0015	0.006	(0.002)

#	Number	Sn	Pb	Zn	Cu	Al	Fe	Mn	Ni	P	S	Sb	Si
---	--------	----	----	----	----	----	----	----	----	---	---	----	----

Number	Ag	As	Bi	C	Cd	Co	Cr	Mg	Se	Te	Units	
BS 903E	.	(0.002)	.	(0.002)	.	(0.002)	(0.0007)	N:(0.0004)	O:(0.007)	.	38 mm Ø x ~7 or 19+ mm	17025
BS 903D	(0.006)	0.0014	(0.004)	(<0.005)	.	(0.0009)	.	O:0.0011	(0.0006)	(0.001)	38 mm Ø x 19 mm	17025
C50.03	.	0.094	0.027	50 mm Ø x 10-12 mm	last
IARM Cu903-18	0.0059	(0.0010)	.	(0.0020)	.	0.0019	.	O:0.0013	.	.	31 mm Ø x 2 or 18 mm	
32X LB10G	0.0686	0.169	0.093	.	.	0.084	~40 mm Ø x ~15 mm	
BS 903B	.	0.003	.	(0.0004)	38 mm Ø x ~7 mm	last
BAM 374	0.00121	(0.00043)	(0.00022)	(<0.0002)	.	40 mm Ø x 30 mm	
BS 938-1	0.0048	(0.004)	38 mm Ø x 12 mm	
BS 936	O:0.0026	0.0045	N:(0.0001)	(0.0025)	.	(0.003)	(0.00004)	.	.	Ti:(0.00006)	50 mm Ø x 19+ mm	17025
IARM Cu932-18	0.019	0.0073	0.094	(0.0025)	0.0007	(0.0024)	.	.	(0.009)	.	38 mm Ø x ~3 or 19 mm	
32X SN6B	1.007	0.804	0.127	Au:0.0027	0.0242	0.750	0.015	.	.	.	~40 mm Ø x ~15 mm	
IARM 91E	0.015	0.008	0.109	(0.003)	0.0011	0.0024	(0.0008)	.	0.004	.	31 mm Ø x 2 or 18 mm	
BS 932G	.	0.0096	.	(0.011)	.	0.0025	(0.001)	.	O:0.0014	.	38 mm Ø x ~7 or 19+ mm	17025
BS 932F	.	0.0091	.	(0.0053)	.	O:0.0025	.	.	.	last	38 mm Ø x ~11 or 19 mm	17025
BS 932H	.	0.010	.	(0.007)	.	0.0028	.	O: 0.0016	.	.	38 mm Ø x ~7 or 19+ mm	17025
IARM 184A	(0.01)	0.010	(0.03)	(0.004)	.	(0.001)	(0.001)	.	.	.	31 mm Ø x 2 or 18 mm	
32X LB13D	0.0249	0.118	0.058	.	0.0006	0.0044	~40 mm Ø x ~15 mm	
BAM 377	0.00644	(<0.0010)	0.00422	.	.	.	0.00669	.	0.0055	.	40 mm Ø x 30 mm	
BS 922B-1	(0.001)	0.001	41 mm Ø x 12 mm	
BS 922B-2	(0.001)	0.001	41 mm Ø x 12 mm	
BS 922B-4	(0.001)	0.001	41 mm Ø x 12 mm	
BS 922B-5	(0.001)	0.001	41 mm Ø x 12 mm	
BAM 378	0.00266	0.000995	(<0.0001)	.	0.01007	0.0089	0.0311	0.00287	(<0.0002)	0.00850	40 mm Ø x 30 mm	
32X LB16A	0.0016	.	0.0120	32 mm Ø x 17 mm	
32X LB14H	0.046	0.055	0.496	.	0.0005	0.0018	~40 mm Ø x ~15 mm	
IARM 267A	(0.002)	(0.004)	(0.005)	(0.003)	.	(0.002)	(0.001)	.	(0.002)	.	31 mm Ø x 2 or 18 mm	
BS 836D	0.023	0.0081	0.093	(0.003)	.	0.0027	O:0.0012	(0.0004)	Be:(0.00009)	.	44 mm Ø x ~7 or 19+ mm	17025
BS 836B	0.025	0.0081	0.10	(0.0032)	.	0.0027	O:0.0010	(0.0005)	Be:(0.00009)	.	44 mm Ø x ~7 or 19+ mm	17025
BS 836C	0.024	0.0082	0.10	(0.003)	.	0.0027	O:0.0014	(0.0007)	Be:(0.000005)	.	44 mm Ø x ~7 or 19+ mm	17025
32X LB15F	0.023	0.0163	0.129	.	0.0006	0.0004	~40 mm Ø x ~15 mm	
BAM M397	.	(0.00029)	<0.0001	<0.0001	40 mm Ø x 30 mm	
BAM M397a	.	(0.00029)	<0.0001	<0.0001	40 mm Ø x 30 mm	
IARM 72B	.	(0.003)	.	0.002	31 mm Ø x 2 or 18 mm	

Number	Ag	As	Bi	C	Cd	Co	Cr	Mg	Se	Te	Units
--------	----	----	----	---	----	----	----	----	----	----	-------

CRM LEADED, TIN, AND LEADED TIN BRONZE DISC AND ROD SETS

available in SETS ONLY, as grouped

IMN BB: 10 mm Ø x 100 mm

IMN BL: 40 mm Ø x 27 mm

IMN BI, WL: 40 mm Ø x 25 mm

Number	Al	As	Bi	C	Cd	Co	Cu	Fe	Mg	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn
IMN BL1	0.11	0.058	0.024	.	0.060	.	Rem	0.38	0.051	0.062	0.25	0.49	0.25	(0.0081)	0.053	0.059	2.58	0.68
IMN BL2	0.15	0.039	0.014	.	0.040	.	Rem	0.21	0.11	0.055	0.37	0.29	0.14	(0.0063)	0.039	0.031	4.04	0.40
IMN BL3	0.019	0.025	0.0099	.	0.022	.	Rem	0.10	.	0.026	0.13	0.084	0.065	.	0.021	0.015	6.12	0.15
IMN BL4	.	0.0089	0.0058	.	0.0092	.	Rem	0.014	.	0.0092	0.015	0.010	0.013	(0.022)	0.0095	0.011	8.38	0.017
IMN BL5	0.00052	0.00057	0.0015	.	0.0015	.	Rem	0.0061	0.0030	0.0011	0.0074	0.0042	0.0069	0.031	0.0039	(0.0038)	11.05	0.0078
IMN BB1	0.019	0.086	0.032	.	.	.	84.82	0.33	.	0.081	0.061	0.055	1.55	.	0.60	0.037	8.10	3.90
IMN BB2	0.032	0.12	0.024	.	.	.	84.09	0.28	.	0.12	0.097	0.085	2.64	.	0.49	0.055	7.11	4.70
IMN BB3	0.0021	0.0079	0.0021	.	.	.	80.88	0.037	.	0.0012	2.42	(0.014)	6.73	.	0.052	0.0044	3.36	6.23
IMN BB4	0.0062	0.029	0.011	.	.	.	81.32	0.086	.	0.020	1.20	0.030	6.14	.	0.21	0.018	2.58	8.11
IMN BB5	0.015	0.051	0.018	.	.	.	82.25	0.14	.	0.054	0.49	0.037	5.18	.	0.31	0.028	4.11	7.21
IMN BB6	0.040	0.16	0.041	.	.	.	83.54	0.31	.	0.15	0.23	0.12	3.52	.	0.62	0.083	5.47	5.40
IMN BI1	0.15	0.14	0.12	.	.	.	Rem	0.42	.	0.26	2.41	0.70	6.97	(0.011)	0.58	0.23	3.19	3.55
IMN BI2	0.077	0.11	0.070	.	.	.	Rem	0.31	.	0.15	1.46	0.59	5.39	(0.0055)	0.43	0.13	4.18	5.73
IMN BI3	0.034	0.052	0.028	.	.	.	Rem	0.17	.	0.082	0.29	0.32	4.52	(0.003)	0.24	0.075	5.01	7.16
IMN BI4	0.0020	0.010	0.0030	.	.	.	Rem	0.083	.	0.025	0.088	0.029	3.82	(0.002)	0.075	0.014	7.69	10.22
IMN WL1	0.082	0.0010	0.0093	0.0050	0.0017	0.0010	95.54	0.072	0.00036	0.0041	0.44	0.012	0.013	0.020	.	0.057	0.22	3.52
IMN WL2	0.057	0.0078	0.0073	0.0082	0.0023	0.0065	97.49	0.13	0.00097	0.0038	0.32	0.016	0.011	0.0070	0.0050	0.046	0.32	1.56
IMN WL3	0.0034	0.020	0.0050	0.010	0.010	0.0096	96.51	0.20	0.0016	0.38	0.22	0.021	0.0083	0.0088	0.0085	0.0037	0.37	2.21
IMN WL4	.	0.0034	0.0026	0.0032	0.0068	0.013	96.41	0.012	.	.	0.019	.	0.0066	0.0050	.	0.0019	0.55	2.97
IMN WL5	0.0014	0.0011	0.0011	.	0.0038	0.019	97.62	0.0025	.	0.00073	0.0014	.	0.0030	0.0019	0.0006	0.0009	0.73	1.61
IMN WL6	0.10	0.024	0.012	0.016	0.025	0.019	95.76	0.31	0.015	0.14	0.091	0.032	0.016	0.017	0.011	0.13	0.80	2.48

COPPER ALLOY XRF SET

Part Number: BS CU-22 AVAILABLE INDIVIDUALLY ~7 mm thick discs (BS 938-1 ~12mm) **17025**

CDA	Number	Cu	Al	Fe	Mn	Ni	Pb	Si	Sn	Zn	As	C	P	S	Sb	Be	Co	Te	Cr
110	BS 110B	99.94	<0.0002	0.0005	<0.0001	<0.0002	0.00052	<0.0004	<0.0002	<0.0003	<0.0001	0.0007	<0.0006	0.00030	<0.0005	<1ppm	<1ppm	0: 0.0363	
145	BS 14500	99.4	(<0.0006)	0.0041	0.00004		0.0008	(<0.002)	0.0002	0.004	(<0.0005)	0.0005	0.0075	0.0033	(<0.001)	(<1ppm)	(<1ppm)	0: 0.0007	Te: 0.53
172	BS 172Be-1	97.68	(0.02)	0.052	0.0010	0.039	(0.002)	0.055	0.033	0.0070	(0.001)	(0.001)	0.003	(<0.0002)		1.89	0.206	0: 0.0007	Cr: 0.0032
360	BS 360A	61.42	<0.001	0.151	0.0007	0.058	2.51	<0.005	0.13	35.63	0.002	(0.0032)	0.001	(0.0003)	0.008				
464	BS 464A	60.6	(0.001)	0.013	0.0002	0.004	0.056	<0.01	0.62	38.73	<0.002	(0.0006)	0.012	0.001	(0.001)				
482	BS 482A	60.0	(0.003)	0.020	<0.002	(0.007)	0.50	(0.002)	0.65	38.8	<0.002	(0.0015)	<0.003	<0.002	0.0012				
510	BS 510A	96.10	<0.002	0.005	<0.002	0.020	0.016	<0.003	4.6	0.21	0.0008	(0.0006)	0.11	0.008	(0.003)				
544	BS 544A	88.4	(0.0005)	0.092	<0.002	0.16	4.16	<0.002	4.42	3.42	(0.006)	(0.002)	<0.002	0.038	0.040				
623	BS 623A	88.13	9.12	2.19	0.273	0.146	0.001	0.014	0.002	0.008	(0.002)	(0.002)	<0.002	<0.0005	<0.002				
630	BS 630A	81.0	10.05	3.73	0.11	4.81	0.0069	0.037	0.019	0.17	(0.002)	0.005	<0.01	(0.001)	<0.001				
642	BS 642A	91.0	6.70	0.17	0.005	0.025	0.001	1.80	0.018	0.011	<0.002	0.001	0.001	<0.001	<0.002				
655	BS 655A	95.74	(0.002)	0.075	0.91	0.008	0.008	3.14	0.07	0.02	<0.002	(0.0006)	(0.004)	(0.0003)	<0.002				
675	BS 675A	58.5	<0.002	1.12	0.32	0.019	0.074	(0.005)	0.80	39.1	<0.002	(0.0007)	0.010	(0.0005)	0.0011				
706	BS 706A	87.60	(0.002)	1.30	0.66	10.18	0.008	<0.005	0.011	0.13	<0.0005	0.004	0.006	0.012	0.0006				
715	BS 715A	69.0	(0.01)	0.61	0.82	30.22	(0.007)	0.10	0.008	0.10	(0.0014)	0.03	0.006	0.001	(0.003)				
863	BS 863A	64.1	5.21	2.41	3.00	0.29	0.022	0.034	0.013	24.8	0.010	0.003	(0.007)	<0.0005	0.003				
903	BS 903B	86.7	(0.001)	0.049	0.0004	0.50	0.10	0.002	7.9	4.39	0.003	(0.0004)	0.073	0.006	0.003				
922	BS 922B-1	88.4	(0.001)	0.010	(0.002)	0.61	1.33	(0.001)	5.8		0.001		0.037		0.002			Ag: (0.001)	
929	BS 929	85.3	(<0.00005)	0.0030		3.37	1.98	(<0.001)	9.07	0.0055	0.0017	(<0.005)	0.119	0.0026	0.0146		0.0031	0: 0.0031	
938	BS 938-1	77.1	(<0.002)	0.015	(0.001)	0.49	14.8	(<0.004)	7.16	0.26	(0.004)		0.059	0.009	0.033			Ag: 0.0048	
954	BS 954A	85.64	10.17	3.50	0.10	0.20	0.016	0.029	0.033	0.30	(0.006)	0.004	0.012	<0.0001	0.001				
955	BS 955C	80.6	10.68	4.04	0.06	4.31	0.003	0.025	0.003	0.15	(<0.002)		0.012		(<0.002)			Ag: 0.014	

CDA	Number	Cu	Al	Fe	Mn	Ni	Pb	Si	Sn	Zn	As	C	P	S	Sb	Be	Co
-----	--------	----	----	----	----	----	----	----	----	----	----	---	---	---	----	----	----

ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER
110	17025	BS 110B	630	17025	BS 630C	922		BS 922B-5
110	17025	BS 110C	630		IARM 80D	927.1		32X SN1
110		IARM 70C	642	17025	BS 642B	929	17025	BS 929
122.2		CURM 09.03	642	17025	BS 642C	931 MOD		C71.34
125		CURM 09.02	642	17025	BS 642D	932	17025	BS 932F
145	17025	BS 14500	642		IARM 81B	932	17025	BS 932G
145	17025	BS 14500A	642		IARM Cu648-18	932	17025	BS 932H
145		IARM 278A	647		IARM Cu647-18	932		IARM 91E
172		BS 172Be-1	655		37X 65500	932		IARM Cu932-18
172	17025	BS 172Be-2	655		BS 655A	932 MOD		CTIF B23
172		CTIF 4872	655	17025	BS 655B	936	17025	BS 936
172		IARM Cu172-18	655	17025	BS 655C	936		CTIF B31
173		36X CBC4	655		IARM 82B	937		32X 93700
175	17025	BS 17500	655		IARM Cu655-18	937	17025	BS 937C
175.1		36x CBC5	673		31X HT37	937		CURM 50.02
175.1		BS 17510	675		BS 675	937		IARM 92C
180		36X 274	675		BS 675A	938		BS 938-1
181.50	17025	BS 18150	675	17025	BS 675B	941		IARM 184A
181.50	17025	BS 18150A	675		IARM 83B	945 MOD		CTIF B32
181.55		36X CCR1	687		BAM 368	947		IARM 267A
182		IARM 279A	693		ERM-EB393A	952.2		CTIF 2152-S
240		C30.07	693		IARM 313A	953		CTIF CA3
260		C48.06	702.6		37X 218	954		BS 954A
260		CURM 48.04	706		36X 70600A	954		BS 954B
261.3		C48.03	706		BS 706	954		BS 954C
274		C38.06	706		BS 706A	954		BS CC954
274		C38.06-1	706		BS 706B	954		IARM Cu954-18
280		C30.03	706	17025	BS 706C	954 MOD		IARM 204A
280		C30.12	706		CTIF CuNi 10	955		BS 955B
314		IARM 72B	706		IARM 84C	955		BS 955C
316		31X 7835-7	706		HRT CU2014	955		IARM 94B
360	17025	BS 360B	713		BAM 389	955		IARM Cu955-18
360	17025	BS 360C	715		36X 71500	955 MOD		CTIF CA10
360	17025	BS 360D	715		BS 715A	955.1		IARM 334A
360		IARM Cu360-18	715	17025	BS 715B	955.1		IARM 334B
360		SRM 1124	715	17025	BS 715C	955.1 MOD		CTIF CA22
370		31X B18	715		IARM 85C	956		32X CA12
371		C30.22	715		IARM Cu715-18	964		IARM 236A
464		BS 464A	715		IARM Cu715-20	976		IARM 298A
464	17025	BS 464B	715		SRM 1276a	Coinage Alloy		36X CN21
464		IARM 74A	767		C65.28	Coinage Alloy		36X CN23
464		IARM 74B	798.3		34X 79830	Cu IX		SRM C1252a
482		BS 482A	815		IARM 158B	Cu VIII		SRM C1251a
482		IARM 75B	815		IARM 158C	Cu X		SRM C1253a
482		IARM 75C	836	17025	BS 836B	Envirobrass 2-1		IARM 226A
485		BS 485a	836	17025	BS 836C	Envirobrass 2-2		IARM 227A
485		IARM 76D	836	17025	BS 836D	Envirobrass 2-3		IARM 228A
485		IARM Cu485-18	836 + Al		IMN BR1	Federalloy I-836		IARM 265A
486		IARM Cu486-18	838		33X GM8	Federalloy I-844		IARM 264A
510		32X PB20	855		31X B2N	Federalloy I-848A		IARM 263A
510		32X 51000	855		31X TB3	Federalloy III-932		IARM 266A
510		BS 510A	855		C38.01	Hiduron 130		IARM CuH130-18
510	17025	BS 510B	855		C38.02	Hiduron 191		IARM CuH191-18
510	17025	BS 510C	855		C38.03	NARloy-A		IARM 159A
510		IARM 77B	855		C38.04	NARloy-Z		IARM 160A
510		IARM Cu510-18	855		C38.05	Spinodal Alloy		36X SP1
512		32X 92100	857		BS 857B-1	Spinodal Alloy		36X SP2
521		32X 52100	857		BS 857B-2			
521		HRT CU2016	857		BS 857B-3			
524		C11.04	857		BS 857B-4			
544		33X 54400	862		CTIF LH7			
544	17025	BS 544B	863	17025	BS 863B			
544		BS 544C	863		IARM 88C			
544		IARM 78B	873		31X WSB6			
544		IARM Cu544-18	893.2, Magnolia B		IARM CuMB1-18			
544 MOD	17025	BS 544c	902		BAM 377			
610 MOD		31X B17	903		BS 903B			
614		32X 61400	903	17025	BS 903D			
615.5		36X CN22	903	17025	BS 903E			
622		CTIF 2154-V	903		IARM 89C			
623		32X CA7	905		BS 905A-1			
623		BS 623	903		IARM Cu903-18			
623		BS 623A	905		BS 905A-2			
623		IARM 79B	905		BS 905A-3			
623		IARM 79C	905		BS 905A-4			
624		32X ALB3	907		IARM 310A			
624	17025	BS 624	908		32X PB10			
624		C52.51	908		HRT CU2000			
624		CTIF 3011-G	910 MOD		CTIF B1			
624		CTIF CA21	922		BS 922B-1			
630		BS 630A	922		BS 922B-2			
630	17025	BS 630B	922		BS 922B-4			

Please use the Adobe Acrobat "search" function to find the complete chemistry of these samples listed within this catalog.

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
385.1		56.0-60.0	2.5-4.5	rem
385.9		56.5-60.0	.	.	<0.35	.	.	.	2.0-3.5	rem
386		56.0-59.0	.	.	<0.35	.	.	.	2.5-3.5	.	<0.02	.	.	rem
404		94.0-96.0	.	.	<0.05	.	.	.	<0.05	rem
405		94.0-96.0	.	.	<0.05	.	.	.	<0.05	rem
408.1		94.0-96.0	.	.	<0.05	.	.	.	<0.05	rem
408.2		94.5-96.5	.	.	0.08-0.12	.	.	.	<0.05	rem
408.5		>94.00	.	.	0.05-0.20	0.01-0.05	0.11-0.20	0.028-0.040	<0.05	0.20-2.50	0.02-0.25
408.6		94.5-96.5	.	.	0.05-0.20	0.02-0.04	0.05-0.20	0.02-0.04	<0.05	rem
408.8		94.0-96.0	.	.	0.01-0.05	.	0.05-0.20	0.02-0.04	<0.05	rem
409		92.0-94.0	.	.	<0.05	.	.	.	<0.05	rem
410		91.0-93.0	.	.	<0.05	.	.	.	<0.05	rem
411		89.0-92.0	.	.	<0.05	.	.	.	<0.10	rem
411.2		89.0-92.0	.	.	0.05-0.20	0.02-0.05	0.05-0.20	0.02-0.05	<0.05	rem
413		89.0-93.0	.	.	<0.05	.	.	.	<0.10	rem
415		89.0-93.0	.	.	<0.05	.	.	.	<0.10	rem
419		89.0-92.0	.	.	<0.05	.	.	.	<0.10	rem
420		88.0-91.0	.	.	<0.05	0.15-0.35	.	.	<0.25	rem
421		87.5-89.0	.	.	<0.05	.	.	.	<0.35	rem
422		86.0-89.0	.	.	<0.05	.	.	.	<0.35	rem
422.2		88.0-91.0	.	.	0.05-0.20	.	.	0.02-0.05	<0.05	rem
425		87.0-90.0	.	.	<0.05	.	.	0.02-0.05	<0.05	rem
425.2		88.0-91.0	.	.	0.05-0.20	0.02-0.04	0.05-0.20	0.02-0.04	<0.05	rem
426	Ni = Ni+Co	87.0-90.0	.	.	0.05-0.20	0.02-0.05	0.05-0.20	0.02-0.05	<0.05	rem
430		84.0-87.0	.	.	<0.05	.	.	.	<0.10	rem
432		85.0-88.0	.	.	<0.05	.	.	<0.35	<0.05	rem
434		84.0-87.0	.	.	<0.05	.	.	.	<0.05	rem
435		78.0-83.0	.	.	<0.05	.	.	.	<0.10	rem
436		80.0-83.0	.	.	<0.05	.	.	.	<0.10	rem
438		79.0-82.0	.	.	<0.05	.	.	.	<0.05	rem
442.5		73.0-76.0	.	.	<0.20	.	<0.20	<0.10	<0.07	0.50-1.50	0.02-0.06
443		70.0-73.0	.	.	<0.06	.	.	.	<0.07	.	0.02-0.10	.	.	rem
444		70.0-73.0	.	.	<0.06	.	.	0.02-0.10	<0.07	rem
445		70.0-73.0	.	.	<0.06	.	.	0.10-0.30	<0.07	rem
454.5		65.0-66.0	.	0.20-0.40	rem
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
462		62.0-65.0	.	<0.03	<0.10	.	.	.	<0.20	.	.	<0.50	0.50-1.00	rem
462.1		61.0-64.0	.	.	<0.10	.	.	.	<0.05	.	.	.	<1.00	rem
464		59.0-62.0	.	.	<0.10	.	.	.	<0.20	.	.	.	0.50-1.00	rem
464.2		61.0-63.5	.	.	<0.20	.	.	.	<0.20	.	.	.	1.0-1.4	rem
465		59.0-62.0	.	.	<0.10	.	.	.	<0.20	.	.	.	0.50-1.00	rem	0.02-0.06
466		59.0-62.0	.	.	<0.10	.	.	0.02-0.10	<0.20	.	0.02-0.10	.	0.50-1.00	rem
467		59.0-62.0	.	.	<0.10	.	.	.	<0.20	.	.	.	0.50-1.00	rem
470		57.0-61.0	.	<0.01	<0.10	.	.	.	<0.05	.	.	.	0.25-1.00	rem
472		49.0-52.0	.	.	<0.10	.	.	.	<0.50	.	.	.	3.0-4.0	rem
476		86.0-88.0	.	.	<0.05	0.05-0.15	.	0.03-0.07	1.8-2.2	.	.	.	1.8-2.2	rem
479.4	Ni = Ni+Co	63.0-66.0	.	.	0.10-1.00	.	0.10-0.50	.	1.0-2.0	.	.	.	1.2-2.0	rem
482		59.0-62.0	.	.	<0.10	.	.	0.40-1.00	<0.20	.	.	.	0.50-1.00	rem
485		59.0-62.0	.	.	<0.10	.	.	.	1.3-2.2	.	.	.	0.50-1.00	rem
485.1		59.0-62.0	1.0-2.5	.	.	.	0.7-1.5	rem	0.02-0.25
486		59.0-62.0	1.0-2.5	.	.	.	0.8-1.5	rem	0.02-0.25
490.8		49.0-52.0	.	<0.10	<0.50	.	.	.	3.0-4.0	rem
501		rem	.	.	<0.05	.	.	0.01-0.05	<0.05	.	.	.	0.50-0.80	rem
502		rem	.	.	<0.10	.	.	<0.04	<0.05	.	.	.	1.0-1.5	rem
505		rem	.	.	<0.10	.	.	0.03-0.35	<0.05	.	.	.	1.0-1.7	rem
505.1		rem	.	.	<0.10	.	0.15-0.40	0.02-0.07	<0.05	.	.	.	1.0-1.5	rem
505.8		rem	.	.	0.05-0.20	.	0.05-0.20	0.02-0.10	<0.05	.	.	.	1.0-1.7	rem
505.9		>97.00	.	.	0.05-0.40	.	.	0.02-0.15	<0.02	.	.	.	0.5-1.5	rem
507		rem	.	.	<0.10	.	.	<0.30	<0.05	.	.	.	1.5-2.0	rem
507.05		>96.50	.	.	0.10-0.40	.	.	0.04-0.15	<0.02	.	.	.	1.5-2.0	rem
507.1		rem	0.10-0.40	<0.15	1.7-2.3	rem
507.15		rem	.	.	0.05-0.15	.	.	0.025-0.040	<0.02	.	.	.	1.7-2.3	rem
507.25		>94.00	.	.	0.05-0.20	.	.	0.02-0.06	<0.02	.	.	.	1.5-2.5	rem
507.8		rem	.	.	0.05-0.20	.	0.05-0.20	0.020-0.100	<0.05	.	.	.	1.7-2.3	rem
508		rem	.	.	<0.10	.	.	0.01-0.07	<0.05	.	.	.	2.6-3.4	rem
509		rem	.	.	<0.10	.	.	0.03-0.30	<0.05	.	.	.	2.5-3.8	rem
510		rem	.	.	<0.10	.	.	0.03-0.35	<0.05	.	.	.	4.2-5.8	rem
510.8		rem	.	.	0.05-0.20	.	0.05-0.20	0.02-0.10	<0.05	.	.	.	4.8-5.8	rem
511		rem	.	.	<0.10	.	.	0.03-0.35	<0.05	.	.	.	3.5-4.9	rem
511.8		rem	.	.	0.05-0.20	.	0.11-0.20	0.02-0.10	<0.05	.	.	.	3.5-4.9	rem
511.9		rem	.	.	0.05-0.15	.	.	0.025-0.045	<0.02	.	.	.	3.0-6.5	rem	.	.	<0.15
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
958.2		>77.50		9.0-10.0 12.0-13.5	4.0-5.0 3.0-5.0	<1.50 <1.50	4.5-5.8 <0.50		<0.02			<0.10	<0.20	<0.20								
959	C <0.10, No <1.00	rem																				
962		rem																				
963	C <0.15, No 0.50-1.50	rem																				
964	C <0.15, No 0.50-1.50	rem																				
966		rem																				
967		rem																				
969	No 0.10-0.30, B <0.01	rem																				
969.15	No <0.10	rem																				
969.15	No <0.10	rem																				
973		53.0-56.0		<0.005	<1.50	<0.50	11.0-14.0	<0.05	8.0-11.0	<0.08	<0.35	<0.15	1.5-3.0	17.0-25.0								
974		58.0-61.0		<0.005	<1.50	<0.50	15.5-17.0	<0.05	4.5-5.5	<0.08	<0.25	<0.15	2.5-3.5	rem								
976		63.0-67.0		<0.005	<1.50	<1.00	19.0-21.5	<0.05	3.0-5.0	<0.08	<0.20	<0.15	3.5-4.5	3.0-9.0								
978		64.0-67.0		<0.005	<1.50	<1.00	24.0-27.0	<0.10	1.0-2.5	<0.08	<0.50	<0.15	4.0-5.5	1.0-4.0								
982		73.0-79.0			<0.70		<0.50	<0.10	21.0-27.0		<0.50		0.6-2.0	<0.50								
984		rem	<1.50		<0.70		<0.50	<0.10	26.0-33.0		<0.50		<0.50	<0.50								
986		60.0-70.0	<1.50		<0.35				30.0-40.0				<0.50	<0.10								
988		56.5-62.5	<5.50		<0.35			<0.02	37.5-42.5				<0.25									
988.2		rem			<0.35				40.0-44.0				1.0-5.0									
988.4		rem			<0.35				44.0-56.0				1.0-5.0									
993	Incramet 800	rem		10.7-11.5	0.40-1.00		13.5-16.5		<0.02			<0.02	<0.05					1.0-2.0				
993.5		rem		9.5-10.5	<1.00	<0.25	14.5-16.0		<0.15					7.5-9.5								
994		rem		0.50-2.00	1.0-3.0	<0.50	1.0-3.5		<0.25			0.50-2.00		0.50-5.00								
995		rem		0.50-2.00	3.0-5.0	<0.50	3.5-5.5		<0.25			0.50-2.00		0.50-2.00								
996	C <0.05	rem		1.0-2.8	<0.20	39.0-45.0	<0.20		<0.02			<0.10	<0.10	<0.20				<0.20				
997	No 4.0-6.0	>54.00		0.50-3.00	<1.00	11.0-15.0	4.0-6.0		<2.0				<1.00	19.0-25.0								
997.5		55.0-61.0		0.25-3.00	<1.00	17.0-23.0	<5.0		0.50-2.50				0.50-2.50	17.0-23.0								

These are specifications for reference purposes only, not samples for sale.

